

PREFACE

Artificial pinning centers in (Y, RE)-Ba-Cu-O superconductors: recent progress and future perspective

To cite this article: Timothy J Haugan *et al* 2020 *Supercond. Sci. Technol.* **33** 040301

View the [article online](#) for updates and enhancements.



IOP | ebooks™

Bringing you innovative digital publishing with leading voices to create your essential collection of books in STEM research.

Start exploring the **collection** - download the first chapter of every title for free.



Preface

Artificial pinning centers in (Y, RE)-Ba-Cu-O superconductors: recent progress and future perspective

Timothy J Haugan¹,
Teresa Puig²,
Kaname Matsumoto³ and
Judy Wu⁴

¹ Aerospace Systems Directorate,
US Air Force Research
Laboratory, Wright-Patterson
AFB, OH 45433, United States of
America

² Institut de Ciència de Materials
de Barcelona, ICMAB-CSIC,
08193 Bellaterra, Spain

³ Department of Materials
Science and Engineering,
Kyushu Institute of Technology,
804-8550 Japan

⁴ Department of Physics and
Astronomy, The University of
Kansas, Lawrence, KS 66045,
United States of America

Introduction

A microscopic understanding of vortex pinning in type II superconductors began with the theoretical discovery of magnetic vortices by Abrikosov, which received the 2003 Nobel Prize in Physics [1, 2]. When type II superconductors are exposed to magnetic fields (H), the magnetic field enters as quantized vortices, each with a fundamental flux $\varphi_0 = 2.07 \times 10^{-11} \text{ T cm}^{-2}$, or $2.07 \times 10^{-15} \text{ Wb}$. The vortex core size on the order of the superconducting coherence length can be very small, e.g. $\sim 1\text{--}2 \text{ nm}$ for the cuprate family of high-temperature superconductors (HTSs). The vortices electrically interact with each other by repelling, and act collectively together as a flux lattice that is affected by the intrinsic crystal lattice properties and microstructure defects. For superconducting power applications where applied magnetic fields are in the range of 0.1 T to $>30 \text{ T}$, the areal number density of the vortices can reach incredibly high values. For example, for an applied magnetic field of 5 T, the vortex areal density is around $2.5 \times 10^{11} \text{ cm}^{-2}$, which translates to inter-vortex spacing of about 20 nm (assuming a square lattice for vortices).

Somewhat surprisingly, if the crystal lattice for type II superconductors, such as HTS cuprates [3] is nearly perfect without any defects to pin vortices, the vortices can move collectively and almost freely in an applied magnetic field due to Lorentz forces, which results in electrical resistance at a fairly low critical current density $J_c(H, T)$ at an applied magnetic field (H) and temperature (T). In order to realize useful critical current densities in type II superconductors, imperfections and defects must be added to the crystal lattice to effectively pin vortices. The simplest example of this was achieved in the (Y, RE)Ba₂Cu₃O₇ (where RE is rare earth elements) family by depositing thin films, in which high densities of dislocations and other growth defects are added into the film microstructure and dramatically increase the critical current density $J_c(77 \text{ K}, H//c\text{-axis}) > 10^6 \text{ A cm}^{-2}$ compared to $J_c(77 \text{ K}) < 10^3 \text{ A cm}^{-2}$ for single crystals [4–6].

Artificial pinning centers

The research into artificial pinning centers (APCs) in HTS cuprates began shortly after discovery of the materials in 1986 [3]. For (Y, RE)Ba₂Cu₃O₇ materials, the addition of YBa₂CuO₅ (Y211) was considered for vortex pinning especially in the 1990s, but it was somewhat controversial whether increases of current density were from vortex pinning of Y211 additions or improved lattice structures [5]. Irradiation was shown to improve critical current densities of YBa₂Cu₃O₇ (YBCO); e.g. in a 1991 paper [4]. However the $J_c(H, T)$ increases were moderate.

The addition of nanophase defects, such as Y211 nanoparticles, into YBCO thin films was achieved from 2003 by several groups, with large increases of $J_c(H, T)$ [7–10]. Since then, intensive efforts were devoted to artificially generate secondary nanophases in the superconducting matrix for the different growth processes; pulsed laser deposition (PLD) [11–13], metal–organic chemical vapor deposition [14], and chemical solution deposition [15, 16].

It is generally understood that vortex pinning can be optimized in type II superconductors by adding ultra-high densities of defects into the crystal structure to match the number of vortices, and with sizes as close to the superconducting coherence length as possible. Precisely how this can be achieved is a fascinating and very complex experimental challenge, given the large number of superconductor processing methods used, and the hundreds of types of ultra-small defects demonstrated to be achievable. Theoretical modeling of the complex collective flux pinning phenomena has only recently achieved an initial understanding [17], and modeling studies are expected to remain limited for many years because of the difficulty of the work and large levels of computation power required.

Current status

Because of limited model understanding, the field of flux pinning in HTS cuprates has primarily progressed for over 30 years through thousands of Edisonian-type experimental studies. The general scientific field of flux pinning of HTSs is large, with 17 100 article citations since 1995 using the search term ‘flux pinning high temperature superconductors’ (Google Scholar, 19 August 2019).

The 14 papers in this Focus Issue present varying topics, including industrial processing, flux mechanisms for different pinning regimes at magnetic fields from 0–33 T and operation temperatures from 5 K to 90 K, and the optimization of different types of defects, such as BaMO_x phases ($M=\text{Sn, Zr, Hf, etc}$) [18–31]. The collection of papers provides a current snapshot of experimental studies, and several reviews are provided. A topical review by Feighan *et al* focuses on one of the remaining problems—how to design pinning in second-generation HTS coated conductors, specifically those made using physical vapor deposition methods (and in particular PLD), through an understanding of the materials science [20]. The review presented the potential for rapid *ex situ*, liquid assisted growth, which is likely to be a necessary universal approach for applications where low cost is critical [20]. Finally, a semi-empirical analysis of the types of defects studied thus far is presented, especially on how they strongly increase $J_c(H, T)$ for three different regimes: (i) $T > 65$ K, $H < 1$ T; (ii) $T = 30$ K–65 K, $H \sim 1$ –5 T; (iii) $T < 30$ K, $H > 5$ T. A review article by Huang and Wang provides a summary of magnetic pinning additions, which have differences and potentially advantages compared with defect pinning, as it pins the magnetic flux rather than the normal core vortices [21]. Four major pinning schemes including metal/YBCO, oxide/YBCO, nanocomposite/YBCO and nanoparticle-embedded/YBCO were reviewed, with some positive benefits [21].

C-axis aligned one-dimensional (1D) APCs remain the focus of many groups, as shown in the development of different 1D APCs (or nanorods) in different REBCO films through both experiments and modeling [18]. A study by Awaji *et al* finds that the low-temperature flux pinning behavior in 1D APCs introduced in $\text{Sm123} + 5.6 \text{ vol\%BaHfO}_3$ (BHO) films can be described as strong 1D APC pinning in the low field, and the coexistence of collective pinning from both nanorod pinning and random pinning in the high field [18]. In the ‘many-nanorod’ state in the high temperature region above the delocalization temperature, double peaks in the pinning force density F_p curves

appeared due to the coexistence of nanorod pinning and random pinning [18]. In the paper by Chepnikov *et al*, 2G HTS wires were fabricated in an industrial process by the PLD of $\text{GdBa}_2\text{Cu}_3\text{O}_7$ films doped with 6%, 12% and 18% (molar) of BaSnO_3 (BSO) and 6% (molar) of BaZrO_3 (BZO), and the $J_c(H, T)$ properties were systematically measured from 4.2 K to 77 K. For relatively high industrial processing rates, the 6% BSO-doped samples deposited at 560 and 375 nm min^{-1} and the 6% BZO-doped sample deposited at 750 nm min^{-1} showed up to an 80% improved critical current compared to the reference sample [19]. Yoshida *et al* reported a very high F_p of 1D APC/SmBCO up to 1.6 T N m^{-3} on single crystal substrates and 1.5 T N m^{-3} on metal substrates at 4.2 K. While c -axis aligned 1D APCs play a critical role in providing correlated pinning at H/c -axis, a pinning landscape with mixed APCs of different morphologies for strong and H -orientation independent pinning will require a microscopic design of APC microstructures. Towards this goal, Wu and Shi present an integrated study of modeling of elastic strain energy with considerations of APC/HTS interfacial strains and experimental demonstration of a mixed APC pinning landscape using microscale strain manipulation [30].

A review of flux pinning progress in (Y, RE)-Ba-Cu-O since 1995, and the impact for power applications, was studied by data mining in a topical review [32]. Development of strong APC HTS nanocomposites grown in solution-based processes is covered in both HTS films [25, 27] and larger scale coated conductors [22, 25] using solution processes that are potentially low cost. It is particularly worth mentioning that the suspension of pre-formed BZO and BHO nanoparticles (3D APCs) in high concentrations have been achieved to allow high-field applications of solution-processed coated conductors [25]. The 3D APCs have the advantage of providing a strong and isotropic pinning landscape as illustrated in the angular dependence of pinning by Palau *et al* [27]. A theoretical study of the pinning properties of the 3D APCs of different diameters in the range of two to four coherence lengths is presented by Willa *et al* to determine the limit of the applicability of the strong-pinning theory [29]. Different J_c-H behaviors are revealed on the 3D APCs at low and high concentrations. Considering the critical importance of experimentally controlling the 3D APC diameter in *in situ* processes, Sparing *et al* developed a PLD–inert gas condensation approach for the simultaneous control of the 3D BHO APC diameter and areal density in YBCO multilayers [28].

Impact and future directions

The field of (Y,RE)-Ba-Cu-O coated conductors for power applications was started in 1995, and manufacturing advances reached 1 km of length in ~ 2010 . The addition of APCs in fully manufactured films began in ~ 2011 , and has continually progressed since then, with many of the ~ 12 world-wide manufacturers studying different methods of APC additions. The implantation of flux pinning into (Y, RE)-Ba-Cu-O by manufacturers tries to duplicate the strong increases of $J_c(H, T, \theta)$ achieved in research laboratories. However, processing parameters in manufacturing can be different from that used in research; e.g. the deposition rates are typically much higher, which can strongly affect the microstructures achieved. Because of this, the $J_c(H, T, \theta)$ increases achieved by manufacturers are in general expected to be different from those in research laboratories.

The impact of (Y, RE) $\text{Ba}_2\text{Cu}_3\text{O}_7$ vortex pinning on improving applications can be substantial, and increases of $J_c(H, T, \theta)$ by 10–100 times have been achieved for varying temperatures and applied fields. The increases of the critical current density (or power density) can provide many benefits for power devices,

including significantly higher performance, enabling operation at temperatures >50 K where cryocoolers have ~ 100 times less weight and can be ~ 10 times more energy efficient, and can enable new capabilities not achievable with $(Y,RE)Ba_2Cu_3O_7$ not optimized for vortex pinning. The increases of the critical current density (or power density) is especially critical for industries such as aerospace, defense or energy with new compact fusion schemes, where the cost—weight—power—loss can determine or limit application viability and use.

While tremendous advances and improvements have been achieved so far with APCs, the advances do not follow the S-curve law of decreasing performance as time progresses. Some of the strongest advances of $J_c(H, T, \theta)$ from APC addition were achieved recently by several groups, by using novel and ultra-precise processing control of >10 vol% addition of defects [27, 33]. And the increases of $J_c(H, T)$ so far have generally only reached about 20%–30% of the upper limit of depairing current densities [34, 35]. Because of that, and the complexities of the microstructures and collective phenomena, it can be expected that with even more precise understanding and microscopic control, even further advances of $J_c(H, T, \theta)$ might be achievable. Such advances might come from nanoscale design engineering with DNA [36], or other techniques that might evolve over time.

ORCID iDs

Judy Wu  <https://orcid.org/0000-0001-7040-4420>

References

- [1] Abrikosov A A 1957 On the magnetic properties of superconductors of the second group *Sov. Phys. JETP-USSR* **5** 1174–83
- [2] Abrikosov A A 2004 Nobel lecture: type-II superconductors and the vortex lattice *Rev. Mod. Phys.* **76** 975–9
- [3] Bednorz J G and Muller K A 1986 Possible high- T_c superconductivity in the Ba-La-Cu-O system *Zeitschrift Fur Physik B* **64** 189–93
- [4] Civale L, Marwick A D, Worthington T K, Kirk M A, Thompson J R, Krusinbaum L, Sun Y, Clem J R and Holtzberg F 1991 Vortex confinement by columnar defects in $YBa_2Cu_3O_7$ crystals—enhanced pinning at high fields and temperatures *Phys. Rev. Lett.* **67** 648–51
- [5] Matsushita T 2000 Flux pinning in superconducting 123 materials *Supercond. Sci. Technol.* **13** 730–7
- [6] Matsumoto K and Mele P 2009 Artificial pinning center technology to enhance vortex pinning in YBCO coated conductors *Supercond. Sci. Technol.* **23** 014001
- [7] Haugan T, Barnes P N, Maartense I, Cobb C B, Lee E J and Sumption M 2003 Island growth of Y_2BaCuO_5 nanoparticles in $(211 \sim 1.5 \text{ nm})/(123 \sim 10 \text{ nm}) \times N$ composite multilayer structures to enhance flux pinning of $YBa_2Cu_3O_{7-\delta}$ films *J. Mater. Res.* **18** 2618–23
- [8] Haugan T, Barnes P N, Wheeler R, Meisenkothen F and Sumption M 2004 Addition of nanoparticle dispersions to enhance flux pinning of the $YBa_2Cu_3O_{7-x}$ superconductor *Nature* **430** 867–70
- [9] Macmanus-Driscoll J L, Foltyn S R, Jia Q X, Wang H, Serquis A, Civale L, Maiorov B, Hawley M E, Maley M P and Peterson D E 2004 Strongly enhanced current densities in superconducting coated conductors of $YBa_2Cu_3O_{7-x} + BaZrO_3$ *Nat. Mater.* **3** 439–43
- [10] Goyal A *et al* 2005 Irradiation-free, columnar defects comprised of self-assembled nanodots and nanorods resulting in strongly enhanced flux-pinning in $YBa_2Cu_3O_{7-\delta}$ films *Supercond. Sci. Technol.* **18** 1533–8
- [11] Kang S *et al* 2006 High-performance high- T_c superconducting wires *Science* **311** 1911–4
- [12] Mele P, Matsumoto K, Horide T, Ichinose A, Mukaida M, Yoshida Y, Horii S and Kita R 2008 Incorporation of double artificial pinning centers in $YBa_2Cu_3O_{7-\delta}$ films *Supercond. Sci. Technol.* **21** 015019
- [13] Yamada Y *et al* 2005 Epitaxial nanostructure and defects effective for pinning in $Y(RE)Ba_2Cu_3O_{7-x}$ coated conductors *Appl. Phys. Lett.* **87** 132502
- [14] Xu A, Braccini V, Jaroszynski J, Xin Y and Larbalestier D C 2012 Role of weak uncorrelated pinning introduced by $BaZrO_3$ nanorods at low-temperature in $(Y,Gd)Ba_2Cu_3O_x$ thin films *Phys. Rev. B* **86** 115416

- [15] Gutierrez J *et al* 2007 Strong isotropic flux pinning in solution-derived $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ nanocomposite superconductor films *Nat. Mater.* **6** 367–73
- [16] Miura M, Yoshizumi M, Izumi T and Shiohara Y 2010 Formation mechanism of BaZrO_3 nanoparticles in $\text{Y}_{1-x}\text{Sm}_x\text{Ba}_2\text{Cu}_3\text{O}_y$ -coated conductors derived from trifluoroacetate metal-organic deposition *Supercond. Sci. Technol.* **23** 014013
- [17] Kwok W K, Welp U, Glatz A, Koshelev A E, Kihlstrom K J and Crabtree G W 2016 Vortices in high-performance high-temperature superconductors *Rep. Prog. Phys.* **79** 116501
- [18] Awaji S, Tsuchiya Y, Miura S, Ichino Y, Yoshida Y and Matsumoto K 2017 C-axis correlated pinning mechanism in vortex liquid and solid phases for Sm123 film with well-aligned BaHfO_3 nanorods *Supercond. Sci. Technol.* **30** 114005
- [19] Chepikov V *et al* 2017 Introduction of BaSnO_3 and BaZrO_3 artificial pinning centres into 2G HTS wires based on PLD-GdBCO films. Phase I of the industrial R&D programme at super O_x *Supercond. Sci. Technol.* **30** 124001
- [20] Feighan J P F, Kursumovic A and MacManus-Driscoll J L 2017 Materials design for artificial pinning centres in superconductor PLD coated conductors *Supercond. Sci. Technol.* **30** 123001
- [21] Huang J J and Wang H Y 2017 Effective magnetic pinning schemes for enhanced superconducting property in high temperature superconductor $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$: a review *Supercond. Sci. Technol.* **30** 114004
- [22] Izumi T and Nakaoka K 2018 Control of artificial pinning centers in REBCO coated conductors derived from the trifluoroacetate metal-organic deposition process *Supercond. Sci. Technol.* **31** 034008
- [23] Matsumoto K, Nishihara M, Kimoto T, Horide T, Jha A K, Yoshida Y, Awaji S and Ichinose A 2017 Temperature dependence of critical currents in REBCO thin films with artificial pinning centers *Supercond. Sci. Technol.* **30** 104006
- [24] Motowidlo L R, Lee P J, Tarantini C, Balachandran S, Ghosh A K and Larbalestier D C 2018 An intermetallic powder-in-tube approach to increased flux-pinning in Nb_3Sn by internal oxidation of Zr *Supercond. Sci. Technol.* **31** 014002
- [25] Obradors X *et al* 2018 Epitaxial $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ nanocomposite films and coated conductors from BaMO_3 ($\text{M} = \text{Zr}, \text{Hf}$) colloidal solutions *Supercond. Sci. Technol.* **31** 044001
- [26] Pahlke P *et al* 2018 Influence of artificial pinning centers on structural and superconducting properties of thick YBCO films on ABAD-YSZ templates *Supercond. Sci. Technol.* **31** 044007
- [27] Palau A *et al* 2018 Disentangling vortex pinning landscape in chemical solution deposited superconducting $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ films and nanocomposites *Supercond. Sci. Technol.* **31** 034004
- [28] Sparing M, Reich E, Hanisch J, Gottschall T, Huhne R, Fahler S, Rellinghaus B, Schultz L and Holzapfel B 2017 Controlling particle properties in $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ nanocomposites by combining PLD with an inert gas condensation system *Supercond. Sci. Technol.* **30** 104007
- [29] Willa R, Koshelev A E, Sadovskyy I A and Glatz A 2018 Strong-pinning regimes by spherical inclusions in anisotropic type-II superconductors *Supercond. Sci. Technol.* **31** 014001
- [30] Wu J and Shi J 2017 Interactive modeling-synthesis-characterization approach towards controllable *in situ* self-assembly of artificial pinning centers in RE-123 films *Supercond. Sci. Technol.* **30** 103002
- [31] Yoshida Y, Miura S, Tsuchiya Y, Ichino Y, Awaji S, Matsumoto K and Ichinose A 2017 Approaches in controllable generation of artificial pinning center in $\text{REBa}_2\text{Cu}_3\text{O}_y$ -coated conductor for high-flux pinning *Supercond. Sci. Technol.* **30** 104002
- [32] Haugan T, Susner M and Sebastian M A 2019 Historical progress of artificial pinning center additions in (Y,RE)-Ba-Cu-O coated conductors, and impact on power device performance *Cryogenic Engineering Conference – International Cryogenic Materials Conference (Hartford, CT, 23 July 2019)* M2Or2B-03
- [33] Miura M *et al* 2017 Tuning nanoparticle size for enhanced functionality in perovskite thin films deposited by metal organic deposition *NPG Asia Mater.* **9** e447
- [34] Larbalestier D, Gurevich A, Feldmann D M and Polyanskii A 2001 High- T_c superconducting materials for electric power applications *Nature* **414** 368–77
- [35] 2005 DOE Workshop Report on Basic Research Needs for Superconductivity www.sc.doe.gov/bes/reports/abstracts.html#sc
- [36] Niemeyer C M 1999 Progress in ‘engineering up’ nanotechnology devices utilizing DNA as a construction material *Appl. Phys. A* **68** 119–24