# Journal of Materials Chemistry C



**View Article Online** 

# PAPER

Check for updates

Cite this: DOI: 10.1039/d0tc04356g

# Electronic, vibrational, and electron-phonon coupling properties in SnSe<sub>2</sub> and SnS<sub>2</sub> under pressure<sup>†</sup>

Gyanu Prasad Kafle, <sup>(D)</sup><sup>a</sup> Christoph Heil, <sup>(D)</sup><sup>b</sup> Hari Paudyal <sup>(D)</sup><sup>a</sup> and Elena R. Margine <sup>(D)</sup>\*<sup>a</sup>

The tin-selenide and tin-sulfide classes of materials undergo multiple structural transitions under high pressure leading to periodic lattice distortions, superconductivity, and topologically non-trivial phases, yet a number of controversies exist regarding the structural transformations in these systems. We perform first-principles calculations within the framework of density functional theory and a careful comparison of our results with available experiments on SnSe<sub>2</sub> reveals that the apparent contradictions among high-pressure results can be attributed to differences in experimental conditions. We further demonstrate that under hydrostatic pressure a  $\sqrt{3} \times \sqrt{3} \times 1$  superstructure can be stabilized above 20 GPa in SnS<sub>2</sub> via a periodic lattice distortion as found recently in the case of SnSe<sub>2</sub>, and that this pressure-induced phase transition is due to the combined effect of Fermi surface nesting and electronphonon coupling at a momentum wave vector  $\mathbf{q} = (1/3, 1/3, 0)$ . In addition, we investigate the contribution of nonadiabatic corrections on the calculated phonon frequencies, and show that the quantitative agreement between theory and experiment for the high-energy  $A_{1g}$  phonon mode is improved when these effects are taken into account. Finally, we examine the nature of the superconducting state recently observed in SnSe<sub>2</sub> under nonhydrostatic pressure and predict the emergence of superconductivity with a comparable critical temperature in SnS<sub>2</sub> under similar experimental conditions. Interestingly, in the periodic lattice distorted phases, the critical temperature is found to be reduced by an order of magnitude due to the restructuring of the Fermi surface.

Received 11th September 2020, Accepted 19th October 2020

DOI: 10.1039/d0tc04356g

rsc.li/materials-c

# I. Introduction

Tin-based binary compounds,  $Sn_xSe_y$  and  $Sn_xS_y$ , have emerged as promising candidates for electronic, optoelectronic, photovoltaic, and thermoelectric applications<sup>1–8</sup> as well as platforms for exploring exotic states of matter.<sup>9–13</sup> Similar to other layered metal chalcogenide materials,<sup>14–21</sup> it has been found that under increased pressure and/or temperature these compounds undergo substantial changes in their structural and electronic properties, special interest being paid to those materials that can host charge density wave (CDW), superconducting, or topologically non-trivial phases.<sup>9–13,19,22–28</sup>

In the dichalcogenide systems, pressure-induced structural phase transitions have been reported for both SnSe<sub>2</sub> and SnS<sub>2</sub>. For example, two theoretical studies have predicted that SnSe<sub>2</sub> becomes thermodynamically unstable above 18–20 GPa and

<sup>b</sup> Institute of Theoretical and Computational Physics, Graz University of Technology, NAWI Graz, 8010 Graz, Austria then decomposes into  $Sn_3Se_4$  (space group  $I\bar{4}3d$ ) and  $Se.^{10,22}$  A similar decomposition has been theoretically shown to take place in the sister compound  $SnS_2$ , which remains thermodynamically stable up to approximately 28 GPa.<sup>23</sup> We would like to note in passing that both 3:4 compounds have been recently predicted to be superconducting with  $T_c$  values of 3.3–4.7 K at 10 GPa,<sup>10,11</sup> and 21.9 K at 30 GPa,<sup>23</sup> respectively. Although the formation of  $Sn_3Se_4$  and  $Sn_3S_4$  has been reported in experiments,<sup>10,29</sup> the presence of a superconducting state in these materials still awaits experimental confirmation.

While  $\text{SnSe}_2$  is no longer on the convex hull tie-line at higher pressures and also becomes dynamically unstable, we have shown in a previous study<sup>19</sup> that it can be stabilized in a  $\sqrt{3} \times \sqrt{3} \times 1$  supercell through a periodic lattice distortion (PLD) and that it can, in fact, be realized in experiments. In particular, under applying pressure,  $\text{SnSe}_2$  becomes metallic in the 8–13 GPa range, with a typical metallic behavior above 17 GPa, and transitions to the PLD phase at around 17 GPa. The agreement between theory and experiment was very good, and the experimentally observed phase transition has been successfully ascribed to a combined effect of electron–phonon (e–ph) coupling and Fermi

<sup>&</sup>lt;sup>a</sup> Department of Physics, Applied Physics, and Astronomy, Binghamton University-SUNY, Binghamton, New York 13902, USA. E-mail: rmargine@binghamton.edu

<sup>†</sup> Electronic supplementary information (ESI) available. See DOI: 10.1039/d0tc04356g

surface (FS) nesting. This is in contrast to transition metal dichalcogenides (TMDs), where FS nesting is found to only play a minor role in creating the CDW instability.<sup>20,30–33</sup> Interestingly, in another recent high-pressure experimental study,<sup>28</sup> neither the proposed theoretical decomposition<sup>10,22</sup> nor the transformation to the PLD phase<sup>19</sup> were detected up to 46 GPa. Instead, electrical resistance measurements in compressed SnSe<sub>2</sub> showed an insulator-to-metallic transition above 15.2 GPa and the appearance of a superconducting state around 18.6 GPa.

In the present study, we first address the apparent contradiction among high-pressure experimental results in SnSe<sub>2</sub> above 20 GPa. Next, we explore whether a  $\sqrt{3} \times \sqrt{3} \times 1$  superstructure can also be stabilized in SnS<sub>2</sub> *via* a PLD by providing a detailed comparison of the electronic, vibrational, and e–ph properties of the two compounds. We expand on our previous work<sup>19</sup> to improve the quantitative agreement between theory and experiment with respect to the pressure dependence of the A<sub>1g</sub> phonon mode. In particular, we investigate the effect of LO–TO splitting and nonadiabatic corrections on the calculated phonon frequencies. Finally, we investigate the origin of the superconducting state recently observed in SnSe<sub>2</sub> under nonhydrostatic pressure, and shed light on the superconducting properties of SnS<sub>2</sub> and the PLD phases of the two systems at higher pressures.

### II. Methods

First-principles calculations were performed within the density functional theory (DFT) using the Quantum Espresso (QE)<sup>34</sup> code. We employed optimized norm-conserving Vanderbilt (ONCV) pseudopotentials<sup>35</sup> with the Perdew-Burke-Ernzerhof (PBE) exchange-correlation functional in the generalized gradient approximation,<sup>36</sup> where the Sn 4d<sup>10</sup>5s<sup>2</sup>5p<sup>2</sup>, Se 4s<sup>2</sup>4p<sup>4</sup>, and S 3s<sup>2</sup>3p<sup>4</sup> orbitals were included as valence electrons. To properly treat the long-range dispersive interactions, we used the non-local van der Waals (vdW) density functional optB86b-vdW.37,38 A plane wave kinetic-energy cutoff value of 60 Ry, a Marzari-Vanderbilt cold smearing<sup>39</sup> value of 0.01 Ry, and a  $\Gamma$ -centered 24  $\times$  24  $\times$  16 Monkhorst–Pack<sup>40</sup> k-mesh for the three-atom unit cell and 12 imes12 × 16 k-mesh for the nine-atom  $\sqrt{3} \times \sqrt{3} \times 1$  supercell were used for the Brillouin-zone (BZ) integration. The atomic positions and lattice parameters were optimized until the self-consistent energy was converged within 2.7  $\times$   $10^{-5}$  eV and the maximum Hellmann–Feynman force on each atom was less than 0.005 eV  $Å^{-1}$ . The dynamical matrices and the linear variation of the selfconsistent potential were calculated within density-functional perturbation theory (DFPT)<sup>41</sup> on the irreducible set of a regular  $6 \times 6 \times 4$  *q*-mesh for the three-atom unit cell and  $3 \times 3 \times 4$ *q*-mesh for the nine-atom  $\sqrt{3} \times \sqrt{3} \times 1$  supercell.

The EPW code<sup>42,43</sup> was used to compute e–ph interactions and related properties. The electronic wavefunctions required for the Wannier–Fourier interpolation<sup>44,45</sup> were calculated on a uniform  $\Gamma$ -centered 12 × 12 × 4 *k*-grid for the three-atom unit cell. Ten maximally localized Wannier functions (one s and three p orbitals for each Sn atom and three p orbitals for each chalcogen atom) were used to describe the electronic structure near the Fermi level ( $E_F$ ). A uniform  $300 \times 300 \times 200$  *k*-mesh was used to evaluate the adiabatic phonon self-energy and static bare susceptibility, while 2 million random *k* points were used to estimate the phonon spectral function in the nonadiabatic regime. Both sets of calculations were performed along a high-symmetry path in *q*-space with smearing values of 25 meV (electrons) and 0.05 meV (phonons). Uniform  $120 \times 120 \times 40$  *k*-point and  $60 \times 60 \times 20$  *q*-point grids were used for the superconductivity calculations in the three-atom unit cell (the in-plane meshes were reduced by a factor of three in the nine-atom supercell). The Matsubara frequency cutoff was set to 0.4 eV and the Dirac deltas were replaced by Lorentzians of width 25 meV (electrons) and 0.1 meV (phonons) when solving the Migdal–Eliashberg equations.

## III. Results

#### A. Crystal structure evolution under pressure

At ambient conditions, bulk  $SnSe_2$  and  $SnS_2$  crystallize in the hexagonal, close-packed  $CdI_2$ -type structure with space group  $P\bar{3}m1$  (no. 164).<sup>19,46</sup> The unit cell contains three atoms, where every Sn atom occupies the center of an octahedron formed by six chalcogen atoms (Se or S) [see Fig. 1(a)]. We refer to this high-symmetry structure as the H1 phase. Fig. 1(b–e) presents the optimized structural parameters as a function of pressure, together with available experimental data for comparison.<sup>19,28,47-50</sup>

As pointed out in previous studies,<sup>48–50</sup> the contraction of the unit cell under compression is highly anisotropic. According to our theoretical results for hydrostatic pressure, the lattice parameter along the *a* axis decreases almost linearly with increasing pressure, while that along the *c* axis shrinks quickly before beginning a slower descent. This anisotropic compression can be related to the rapid decrease in the inter-layer Se····Se/S···S distance (*i.e.*, the distance between the chalcogen atoms in adjacent layers) *versus* the intra-layer Se-Se/S–S and Sn–Se/Sn–S distances due to the weaker vdW inter-layer interaction relative to the stronger covalent intra-layer bonding.

Up to 10 GPa, there are no appreciable differences seen in the compressibility rates in the two systems. For instance, the lengths of the *a* and *c* axes at 10 GPa are reduced by about 3% and 11% with respect to their zero-pressure values in both cases. As the pressure increases, the compressibility rate along the *a* axis becomes slightly smaller in SnS<sub>2</sub> than in SnSe<sub>2</sub>, following the expected trend that a more covalent intra-layer bond is less compressible<sup>47</sup> [see Fig. S1 (ESI<sup>†</sup>)<sup>51</sup>]. The compressibility rate along the *c* axis, on the other hand, displays the opposite behavior. This can be empirically understood from the relatively more localized nature of the 3p orbitals of S<sup>2-</sup> compared to the 4p orbitals of Se<sup>2-</sup>, which gives rise to a weaker interaction across the vdW gap in SnS<sub>2</sub> and thus increased compressibility.

The present theoretical results for the pressure dependence of the cell parameters are in very good agreement with all experimental data in the low pressure region between 0 and 10 GPa [see Fig. 1]. Beyond this point, the pressure transmitting medium used in various experiments can cause considerable differences between the compressed lattice parameters. The



Fig. 1 (a) Crystal structures showing the intra-layer (Se–Se/S–S) and inter-layer (Se $\cdots$ Se/S $\cdots$ S) distances (top figure) and 1 × 1 and  $\sqrt{3} \times \sqrt{3}$  unit cells (bottom figure). Pressure dependence of (b), (c) the lattice parameters *a* and *c*, (d) the average bond lengths, and (e) the volume per formula unit for SnSe<sub>2</sub> and SnS<sub>2</sub>. Theoretical results are shown as black symbols and are compared with available experimental data.<sup>19,28,47–50</sup> Data for SnSe<sub>2</sub> and SnS<sub>2</sub> are presented with solid and open symbols.

largest deviation is observed for the compression of the *a* axis in  $SnSe_2$  beyond 10 GPa in ref. 28 and is attributed to nonhydrostatic pressure conditions in the experimental setup. A similar, but smaller effect, was also found in  $SnS_2$ .<sup>48,50</sup>

We next discuss the thermodynamic and dynamic stability of SnSe<sub>2</sub> and SnS<sub>2</sub> under compression. With respect to the full phase diagram, our calculations agree well with the findings reported in literature, namely that SnSe<sub>2</sub> and SnS<sub>2</sub> lie above the convex hull tie-line for pressures above approximately 20 and 40 GPa, respectively [see Fig. S2,  $(ESI^{\dagger})^{51}$ ]. The occurrence of a lattice instability is established by calculating the full phonon dispersion relations in the harmonic approximation in the three-atom H1 unit cell. As shown in Fig. S3 (ESI<sup>†</sup>),<sup>51</sup> the lowest-energy vibrational mode has an imaginary frequency at the K point of the BZ at 20 GPa, indicating that the two systems have become dynamically unstable. Based on the above results, it would be expected that the systems will either decompose into more stable products or undergo a crystal transformation into a nearby minima in the configuration space by following the eigenvector of a soft phonon mode.

The successful synthesis of  $Sn_3Se_4$  in laser-heated diamond anvil cells<sup>10</sup> points towards the first scenario, but no traces of the  $Sn_3Se_4$  phase were detected in the high-pressure synchrotron X-ray diffraction (XRD) patterns measured at room temperature in two other recent studies.<sup>19,28</sup> This implies that a relatively large activation barrier needs to be overcome for the system to decompose, requiring not only high pressures but also high temperatures.

Evidence for the second scenario has also been provided in our combined experimental and theoretical work on SnSe<sub>2</sub>.<sup>19</sup> Namely, the formation of a  $\sqrt{3} \times \sqrt{3} \times 1$  superlattice has been

revealed through the sudden appearance of several reflections at (1/3, 1/3, 0) in XRD patterns and of two new peaks in the Raman spectra above 17 GPa. In addition, it has been shown that energetically more stable structures with lower symmetry can be constructed as detailed below. Here we will refer to the derivatives of the undistorted  $\sqrt{3} \times \sqrt{3} \times 1$  H1 structure created via a PLD as H2. The fact that SnSe<sub>2</sub> has not been synthesized in the H2 structure in the study by Zhou *et al.*<sup>28</sup> suggests that the formation of this metastable phase is strongly dependent on the experimental conditions. While the NaCl powder used in our high-pressure XRD experiments ensured a quasihydrostatic pressure environment below 40 GPa,<sup>19</sup> the silicone oil used as a pressure transmitting medium by Zhou et al. produced nonhydrostatic pressures above 13.2 GPa.<sup>28</sup> A similar situation has been observed for TMDs, where different pressure conditions give rise to variations in the structural and electronic properties.<sup>52,53</sup> For instance, in the case of WS<sub>2</sub>, the transition from the 2H<sub>c</sub> to 2H<sub>a</sub> phase occurred under nonhydrostatic, but not under hydrostatic pressure.<sup>53</sup>

We now focus our attention on understanding whether a  $\sqrt{3} \times \sqrt{3} \times 1$  superstructure can also be stabilized in SnS<sub>2</sub> *via* a PLD. Since the *K* point of the  $1 \times 1 \times 1$  unit cell folds onto the  $\Gamma$  point in the  $\sqrt{3} \times \sqrt{3} \times 1$  supercell, dynamical stability calculations can be performed by determining the phonon frequencies at the  $\Gamma$  point of the nine-atom H1 structure. As pressure is increased, the two nearly degenerate lowest-energy phonon modes with A<sub>2g</sub> and A<sub>2u</sub> symmetry soften and become imaginary as shown in Fig. 2(a). The linear evolution of  $\omega^2$  with pressure [Fig. 2(a) inset] is a characteristic feature of a softmode phase transition,<sup>54,55</sup> enabling us to estimate the critical

To construct the energetically preferred structural derivatives of the original H1 phase, we follow the same strategy employed



**Fig. 2** (a) Calculated softening of the lowest-energy (degenerate) phonon modes in the  $\sqrt{3} \times \sqrt{3} \times 1$  H1 superlattice for SnSe<sub>2</sub> and SnS<sub>2</sub>, where imaginary phonon frequencies are shown as negative, illustrating the pressure-induced destabilization of the H1 phase. The inset shows the squared frequency of the modes. (b) Enthalpy difference for the considered H2 structures as function of pressure for SnSe<sub>2</sub> and SnS<sub>2</sub>, where the H1 phase was chosen as a reference.

in our previous work on  $\text{SnSe}_2$ .<sup>19</sup> We displace the atomic coordinates according to the eigenvectors of  $A_{2g}$  (H2-1 phase) and  $A_{2u}$  (H2-2 phase) modes as well as a linear combination of the two eigenvectors (H2-3 phase) to better explore the adiabatic potential energy surface. As for  $\text{SnSe}_2$ , the resulting distorted structures for the  $\sqrt{3} \times \sqrt{3} \times 1$  supercell are fully relaxed and found to converge to three distinct configurations based on the structure analysis performed with the MAISE package.<sup>56</sup> The lattice parameters, space groups, and Wyckoff positions of the H2 structures at 30 GPa are given in Table. S1 and the crystal structures are shown in Fig. S4 (ESI<sup>†</sup>).<sup>51</sup> Since H2-3 is an intermediate phase along the pathway that transforms H2-1 into H2-2, we will only concentrate on the H2-1 and H2-2 structures in our further discussion.

As can be appreciated from the pressure dependence plots of the relative enthalpy in Fig. 2(b), the H2 phases are energetically more favorable above 18 and 20 GPa for SnSe<sub>2</sub> and SnS<sub>2</sub>, respectively. This is in good agreement with our phonon calculations at 30 GPa, showing no imaginary frequencies and demonstrating the dynamical stability of the predicted H2 phases [Fig. 3]. We find the H2 derivatives to be virtually degenerate in enthalpy and no distinguishable differences between their phonon spectra. A comparison of the radial distribution functions (RDFs) shown in Fig. 4 along with an estimate of the similarity factor (defined as the RDF dot product between two structures) provide further evidence that the H2-1 and H2-2 configurations are indeed distinct despite having similar enthalpies. In this case, using a Gaussian spread of 0.008,<sup>56</sup> we find a similarity factor of 0.5358 and 0.6102 between the H2-1 and H2-2 structures for the SnSe<sub>2</sub> and SnS<sub>2</sub> systems, respectively. Noticeably, the main difference in the RDFs comes from the second-nearest neighbor, explaining the similar covalent network and, therefore, the very similar vibrational and electronic properties of the H2 derivatives. Based on the RDF analysis, we can establish that the distorted configurations are nearby local minima, a situation encountered in other systems.57



Fig. 3 Calculated phonon dispersion for the (a and d) H1 structure in the  $1 \times 1 \times 1$  unit cell and (b, c, e and f) H2 structures in the  $\sqrt{3} \times \sqrt{3} \times 1$  supercell of SnSe<sub>2</sub> (top row) and SnS<sub>2</sub> (bottom row) at 30 GPa. The H2-1 and H2-2 structures are derivatives of the undistorted  $\sqrt{3} \times \sqrt{3} \times 1$  H1 structure created *via* a PLD.



Fig. 4 Calculated radial distribution function of the H2 structures for (a-c) SnSe\_2 and (d-f) SnS\_2 at 30 GPa with MAISE.  $^{56}$ 

#### **B.** Electronic properties

In this section we systematically analyze the band structure of  $\text{SnSe}_2$  and  $\text{SnS}_2$  under hydrostatic and nonhydrostatic pressure. At zero pressure, both systems are found to be semiconducting with an indirect band gap of 0.62 eV in  $\text{SnSe}_2$  and 1.35 eV in  $\text{SnS}_2$ , respectively. As for bulk TMDs consisting of the same transition metal, the compound with the most electronegative chalcogen has the largest band gap.<sup>58–61</sup> While this is the correct trend, we need to keep in mind in our following discussion that the size of the band gaps are underestimated relative to those extracted from experiments<sup>62–66</sup> or calculated with the GW approximation or the HSE06 hybrid functional.<sup>65,67</sup>

Fig. 5 shows the calculated hydrostatic band structures for the H1 phase in the three-atom unit cell at 0, 6, and 20 GPa; band structures at other pressures are given in Fig. S5 (ESI<sup>+</sup>).<sup>51</sup> The bottom of the conduction band displays a mixture of Sn s with chalcogen (Se or S)  $p_{xy}$  orbitals along the in-plane directions and with chalcogen  $p_z$  orbitals along the out-of-plane directions. The top of the valence band, on the other hand, consists almost entirely of chalcogen pz orbitals. Under compression, the orbital character of the bands remains largely unaffected, but the bandwidths expand as indicated by the increase in the slope of the dispersion curves. Near the Fermi level, the most significant change takes place in the lowest conduction band level along the  $\Gamma$ -K segment. Due to a greater overlap between the chalcogen  $p_{xy}$  and Sn s orbitals, the band energy at the K point decreases, eventually dropping below the valence band maximum and closing the band gap. As a result, a pressure-induced semiconductor-to-metal transition is estimated to occur at 6 and 20 GPa in SnSe2 and SnS2, respectively.

The predicted metallization pressures are consistent with available theoretical results,<sup>19,22,50</sup> but lower than the experimental



Fig. 5 Calculated band structure for the H1 structure in the  $1 \times 1 \times 1$  unit cell of (a-c) SnSe<sub>2</sub> and (d-f) SnS<sub>2</sub> at 0, 6, and 20 GPa. The size of the symbols is proportional to the contribution of each orbital character.

#### Paper

values as anticipated from the underestimation of the band gaps in the PBE approximation. Additional changes in the metallization pressure are also expected under nonhydrostatic pressure conditions. DFT results show that a transition at a higher (lower) pressure is favored under in-plane (out-of-plane) uniaxial compressive strain [see Fig. S6 (ESI†)<sup>51</sup>]. This trend is in agreement with experimental resistivity measurements in SnSe<sub>2</sub> where a semiconductor-to-metal transition was observed between 8–13 GPa under quasi-hydrostatic pressure<sup>19</sup> compared to a transition above 15.2 GPa under nonhydrostatic pressure.<sup>28</sup> As can be seen in Fig. 1(b), the in-plane compression in the latter study is considerable smaller, thus pushing the metallization point to a higher pressure.

To get a better understanding of how the internal structural parameters of the layers, the inter-layer distance, and the choice of chalcogen atom affect the electronic transition, we calculate the electronic dispersions of (i) SnSe<sub>2</sub> structure at 0 GPa in which the Se atoms are substituted with S and the atomic coordinates are either kept unchanged (labeled as SnSe<sub>2</sub>-str-S) or allowed to relax (labeled as SnSe<sub>2</sub>-str-S-relaxed), and (ii) SnS<sub>2</sub> structure at 0 GPa in which the S atoms are substituted with Se and the atomic coordinates are either kept unchanged (labeled as SnSe<sub>2</sub>-str-S) or allowed to relax (labeled as SnS<sub>2</sub>-str-Se) or allowed to relax (labeled as SnS<sub>2</sub>-str-Se) or allowed to relax (labeled as SnS<sub>2</sub>-str-Se-relaxed).

As shown in Fig. S7 (ESI<sup>†</sup>),<sup>51</sup> the effect of replacing Se with S is an up-shift of the lowest conduction band states and, consequently, a slight increase in the band gap from 0.62 to 0.75 eV. Allowing the atoms to relax gives an additional up-shift of 0.15 eV since the intra-layer distance is reduced to almost the ideal value in SnS<sub>2</sub>. However this up-shift is still not large enough to reach the band gap value of SnS<sub>2</sub>. If, on the other hand, we use the SnS<sub>2</sub> structure with the Se pseudopotential, as in calculation (ii), we see an opposite trend since now the lowest conduction band states move down in energy. The band gap reduces from 1.35 to 0.90 eV without atomic relaxation and further to 0.22 eV once the atoms are allowed to relax. The reduction by a factor of almost three of the band gap relative to the value in ideal  $\text{SnSe}_2$  can be ascribed to the presence of slightly more charge in the vdW gap as the interlayer distance is compressed by almost 10%. Fig. S8 and S9  $(\text{ESI}^{\dagger})^{51}$  show total charge and charge redistribution plots for the configurations described above. Overall, the metallization process is driven by the cooperative effect of both chemical and structural factors.

We further study the evolution of the charge density with pressure. Similar to TMDs, we find that under compression more electronic charge moves away from the Sn atoms and accumulates along the intra-layer bonds formed by Sn with the chalcogen atoms<sup>68–70</sup> [Fig. S10 (ESI<sup>+</sup>)<sup>51</sup>]. This view is also supported by the increase in the in-plane average charge at the middle of the vdW gap under applied pressure [see Fig. S11 (ESI<sup>+</sup>)<sup>51</sup> that shows the in-plane average charge as a function of the perpendicular direction with respect to the layer]. This behavior is in contrast to intercalated carbon and boron layered compounds where, under applied pressure, the inter-layer charge from the intercalant atoms is forced out to the covalent sheets.<sup>71–73</sup>

Finally, in Fig. 6 we compare the electronic structure of H1 and H2 phases in the  $\sqrt{3} \times \sqrt{3} \times 1$  supercell for the two systems. As shown in our previous study on SnSe<sub>2</sub>,<sup>19</sup> the main difference lies in the lifting of electronic degeneracy near the Fermi level along the  $\Gamma$ -M and K- $\Gamma$ -A directions in the H2 structures. Compared to the parent H1 phase, there is an out-of-plane displacement of the Sn atoms resulting in a slight buckling of the Sn layers and a shift of the chalcogen atoms with respect to the center of the octahedron [see Fig. S4 (ESI†)<sup>51</sup>]. This modulation of



**Fig. 6** Calculated band structure for the (a and d) H1 and (b, c, e and f) H2 structures in the  $\sqrt{3} \times \sqrt{3} \times 1$  supercell of SnSe<sub>2</sub> (top row) and SnS<sub>2</sub> (bottom row) at 30 GPa. The H2-1 and H2-2 structures are derivatives of the undistorted  $\sqrt{3} \times \sqrt{3} \times 1$  H1 structure created *via* a PLD. The area indicated by the green box in (a and d) is to be compared to (b, e and c, f) where avoided crossing near the Fermi level can be observed in the H2 structures.

atomic positions leads to the avoidance of crossings between the bands with mixed Sn s and chalcogen  $p_{xy}$  orbitals and the band with chalcogen  $p_z$  character. Similarly to the phonon spectra in Fig. 3, there are no noticeable differences between the band structure plots of the H2 derivatives.

#### C. Vibrational properties

In low-dimensional or layered systems, the appearance of a superlattice is often the signature of a CDW transition, as for example in TMDs.<sup>31,32</sup> In these materials, it has been established that the wave vector dependence of the e–ph coupling is crucial in understanding the CDW formation, while the FS nesting has been found to only play a minor role.<sup>20,30–33</sup> As presented in our previous study on  $SnSe_2$ ,<sup>19</sup> the breaking of electronic degeneracies by a phonon-modulated lattice distortion, the reduction of the density of states (DOS) at the Fermi level, and the softening of a low-energy phonon are key signatures of a momentum-dependent e–ph coupling CDW instability. In this section, we want to investigate if the same reasoning is true for  $SnS_2$  as well.

To address the microscopic mechanism responsible for the phase transition and the origin of phonon softening at *K*, we calculate the adiabatic phonon self-energy  $(\Pi_{\mathbf{q}\nu}^{\mathrm{A}})$  for the lowest-energy phonon mode and the static bare susceptibility in the constant matrix approximation  $(\chi_{\mathbf{q}}^{0,\mathrm{CMA}})$  using the following equations<sup>43,74,75</sup>

$$\Pi_{\mathbf{q}\nu}^{\mathbf{A}} = 2 \sum_{nm} \int \frac{d\mathbf{k}}{\Omega_{\mathbf{B}\mathbf{Z}}} \left[ \frac{f_{n\mathbf{k}} - f_{m\mathbf{k}+\mathbf{q}}}{\varepsilon_{m\mathbf{k}+\mathbf{q}} - \varepsilon_{n\mathbf{k}}} \right]$$
(1)

$$\times g_{mn,\nu}(\mathbf{k},\mathbf{q}) \times g_{mn,\nu}(\mathbf{k},\mathbf{q})$$

$$\chi_{\mathbf{q}}^{0,\mathrm{CMA}} = 2 \sum_{mn} \int \frac{\mathrm{d}\mathbf{k}}{\Omega_{\mathrm{BZ}}} \left[ \frac{f_{n\mathbf{k}} - f_{m\mathbf{k}+\mathbf{q}}}{\varepsilon_{m\mathbf{k}+\mathbf{q}} - \varepsilon_{n\mathbf{k}}} \right]$$
(2)

Here, 2 is the spin degeneracy factor,  $\varepsilon_{n\mathbf{k}}$  and  $f_{n\mathbf{k}}$  represent singleparticle energies and Fermi–Dirac occupation factors, and  $\Omega_{\rm BZ}$  is the BZ volume. The screened e–ph matrix elements  $g_{mn,\nu}(\mathbf{k},\mathbf{q})$  were obtained as  $g_{nm,\nu}(\mathbf{k},\mathbf{q}) = \left\langle \psi_{m\mathbf{k}+\mathbf{q}} | \partial_{\mathbf{q}\nu} V | \psi_{n\mathbf{k}} \right\rangle / \sqrt{\hbar/2\omega_{\mathbf{q}\nu}}$ , where  $\psi_{n\mathbf{k}}$  represents the Kohn–Sham single-particle eigenstates,  $\partial_{\mathbf{q}\nu} V$  is the derivative of the self-consistent potential, and  $\omega_{\mathbf{q}\nu}$  is the phonon frequency associated with phonon branch  $\nu$  and wave vector  $\mathbf{q}$ . The bare matrix element  $g_{mn,\nu}^{b}(\mathbf{k},\mathbf{q})$  is calculated by multiplying the screened e–ph matrix elements  $g_{mn,\nu}(\mathbf{k},\mathbf{q})$  with the electronic dielectric function at  $\omega = 0$  [ $\varepsilon(\mathbf{q},\omega = 0)$ ]. Thus, the matrix elements  $g_{mn,\nu}^{b}(\mathbf{k},\mathbf{q}) \times g_{nm,\nu}^{*}(\mathbf{k},\mathbf{q})$  in eqn (1) can be replaced by  $|g_{mn,\nu}(\mathbf{k},\mathbf{q})|^2 \times \varepsilon(\mathbf{q},\omega = 0)$ .<sup>78</sup>

Both  $\chi_{\mathbf{q}}^{0,\text{CMA}}$  and  $\Pi_{\mathbf{q}\nu}^{A}$  are properties of the FS bands and those electronic states close to them, yet  $\chi_{\mathbf{q}}^{0,\text{CMA}}$  is purely electronic, while  $\Pi_{\mathbf{q}\nu}^{A}$  includes the fully anisotropic e-ph interaction. As can be appreciated in Fig. 7, we observe an increasing response of  $\Pi_{\mathbf{q}\nu}^{A}$  and  $\chi_{\mathbf{q}}^{0,\text{CMA}}$  at the *K* point in both systems with increasing pressure, meaning that both FS nesting as well as the e-ph coupling strength increase at the BZ regions close to *K* as the critical pressure for the phase transition is approached. This leads us to the conclusion that both FS nesting and strong e-ph interactions are providing important contributions in creating the PLD instability in SnS<sub>2</sub>, in close analogy to SnSe<sub>2</sub>.<sup>19,76,77</sup>



**Fig. 7** The adiabatic phonon self-energy for the soft phonon mode and the static bare susceptibility in the constant matrix approximation for the H1 structure in the  $1 \times 1 \times 1$  unit cell of (a–b) SnSe<sub>2</sub> and (c and d) SnS<sub>2</sub> as a function of pressure along a high-symmetry **q**-path. The dashed and dotted lines for SnSe<sub>2</sub> indicate pressures at which the material is in the metallic phase.<sup>77</sup> The  $\chi_{\mathbf{q}}^{0,CMA}$  values in (b) and (d) should be multiplied by a factor of  $10^4$  and  $10^3$ , respectively.

Having identified the PLD instability in  $SnS_2$  to be of the same origins as in  $SnSe_2$ , we carry on to compare the materials' Raman-active modes' frequencies as a function of pressure, as shown in Fig. 8. The high energy  $E_g$  mode increases monotonically as a function of pressure in both  $SnSe_2$  and  $SnS_2$ . The high energy  $A_{1g}$  mode, on the other hand, shows a noticeable change of slope at approximately 6 and 20 GPa in the case of  $SnSe_2$  and  $SnS_2$ , respectively. This can be related to the semiconductor-to-metal transition in both systems as also supported by Fig. S12 (ESI<sup>+</sup>).<sup>51</sup> After the phase transition, due to the in-plane tripling of the unit cell, two additional Raman-active modes appear at 17 GPa for  $SnSe_2$  and at 20 GPa for  $SnS_2$ , in good agreement with available experimental data.<sup>19</sup>

The pressure dependence of the high-energy  $E_{\rm g}$  mode for SnSe<sub>2</sub> is in very good agreement with the experimental results, however, the high-energy A<sub>1g</sub> mode, while reproducing nicely the qualitative trend, underestimates the phonon energies by ~0.5 meV at 0 GPa and ~3 meV at 6 GPa (the metallization pressure) compared to experiments.<sup>19</sup> Recent studies of other insulators and semiconductors show that the underestimation of phonon energies with respect to experiments can be due to the neglection of nonadiabatic effects in the theoretical approach.<sup>79-83</sup> In order to assess the effect of nonadiabatic corrections on the phonon dispersions in our systems, we employed a field-theoretic framework,<sup>74</sup> where the phonon selfenergy  $\Pi_{\mathbf{q}\nu}$  can be partitioned into adiabatic and nonadiabatic contributions, *i.e.*,  $\Pi(\omega) = \Pi^{\rm A} + \Pi^{\rm NA}(\omega)$ . Thus, the nonadiabatic corrections to the self-energy as a function of the phonon mode  $\nu$ and wave vector  $\mathbf{q}$  are given by:

$$\begin{aligned} \hbar\Pi_{\mathbf{q}\nu}^{\mathrm{NA}}(\omega) &= 2\sum_{nm} \int \frac{\mathrm{d}\mathbf{k}}{\Omega_{\mathrm{BZ}}} \times g_{nm,\nu}^{\mathrm{b}}(\mathbf{k},\mathbf{q}) \times g_{nm,\nu}^{*}(\mathbf{k},\mathbf{q}) \\ &\times \left[ \frac{f_{m\mathbf{k}+\mathbf{q}} - f_{n\mathbf{k}}}{\varepsilon_{m\mathbf{k}+\mathbf{q}} - \varepsilon_{n\mathbf{k}} - \hbar(\omega + i\eta)} - \frac{f_{m\mathbf{k}+\mathbf{q}} - f_{n\mathbf{k}}}{\varepsilon_{m\mathbf{k}+\mathbf{q}} - \varepsilon_{n\mathbf{k}}} \right] \end{aligned}$$
(3)



**Fig. 8** Calculated frequency dependence of the Raman-active modes at  $\Gamma$  as a function of pressure for (a) SnSe<sub>2</sub> and (b) SnS<sub>2</sub>. The theoretical results are shown as black symbols (H1), red symbols (H2-1), and blue symbols (H2-2) while the experimental results<sup>19,84,85</sup> are shown as olive symbols. For H1, the data before and after the phase transition are shown as filled and open symbols. The nonadibatically corrected frequency points are shown as filled magenta pentagons.

with  $\eta$  being a positive infinitesimal number. The nonadiabatic phonon spectral function<sup>86,87</sup> can then be calculated using

$$A_{\mathbf{q}\nu}^{\mathrm{NA}}(\omega) = \frac{1}{\pi} \mathrm{Im} \left[ \frac{2\hbar\omega_{\mathbf{q}\nu}}{\left(\hbar\omega\right)^2 - \left(\hbar\omega_{\mathbf{q}\nu}\right)^2 - 2\hbar\omega_{\mathbf{q}\nu}\Pi_{\mathbf{q}\nu}^{\mathrm{NA}}(\omega)} \right]$$
(4)

Eqn (4) reveals that a strong response of the system is expected at the nonadiabatic phonon frequency,  $\Omega_{q\nu}$ , when the denominator is very small or vanishes. The renormalized nonadiabatic phonon energy, that is, the phonon energy modified by the phonon self-energy of eqn (3) is thus given by

$$\Omega_{\mathbf{q}\nu}^2 \simeq \omega_{\mathbf{q}\nu}^2 + 2\omega_{\mathbf{q}\nu} \operatorname{Re}\Pi_{\mathbf{q}\nu}^{\mathrm{NA}}(\Omega_{\mathbf{q}\nu})$$
(5)

The nonadiabatic spectral functions and the nonadiabatic phonon dispersions obtained *via* eqn (4) and (5) at various pressures along the  $\Gamma$ -*M*-*K*- $\Gamma$  direction for SnSe<sub>2</sub> and SnS<sub>2</sub> are reported in Fig. 9. As can be appreciated from Fig. 9, the nonadiabatic effects are very small in both systems at ambient pressure. As the pressure increases (and the band gap decreases),

the renormalization of the  $A_{1g}$  mode energy becomes significant around 4 GPa in SnSe<sub>2</sub> and around 16 GPa in SnS<sub>2</sub>. In particular, the  $A_{1g}$  mode in SnSe<sub>2</sub> hardens by ~2 meV at 4 GPa [Fig. 9(c)], improving the quantitative agreement of our calculations with the experiments<sup>19</sup> [see also Fig. 8]. Similarly, the  $A_{1g}$  mode in SnS<sub>2</sub> hardens by ~3 meV at 16 GPa as shown in Fig. 9(f). For the  $E_{g}$ mode, where the agreement between experiments and theory has already been very good, the nonadiabatic corrections are found to be very small.

As SnSe<sub>2</sub> and SnS<sub>2</sub> are polar semiconductors at ambient and low pressures, we also want to address the topic of LO-TO splitting. At ambient pressure, we observe a LO-TO splitting of 7 meV for SnSe<sub>2</sub> and 11.8 meV for SnS<sub>2</sub> [see Fig. S13 (ESI $\dagger$ )<sup>51</sup>]. With increasing pressure, the band gap decreases and the value for the dielectric function increases. In turn, the magnitude of the LO-TO splitting decreases, in accordance with experimental measurements in other polar semiconductors.88,89 Interestingly, however, at the critical pressures above which our compounds become metallic, our calculations still yield finite values for the splitting (around 6.4 meV for SnSe<sub>2</sub> and 10 meV for SnS<sub>2</sub>). A possible explanation for the residuary LO-TO splitting is that in the pressure regions, where the materials pass through the semiconductor-metal phase transition, the charge carrier concentration is so low that the long-range Coulomb interactions are not fully screened, thus allowing for finite LO-TO splitting. In the fully metallic state at higher pressures, the long-range Coulomb interactions are screened completely leading to the degeneracy of LO and TO modes. Although highly interesting, resolving the intermediate bad metal phase would go beyond the scope of this work and is therefore the focus of future investigations.

#### D. Superconducting properties

Experimental evidence of pressure-induce superconductivity in  $\text{SnSe}_2$  has been recently provided based on electrical transport and synchrotron XRD measurements.<sup>28</sup> The superconducting state is observed to emerge at 18.6 GPa and to reach a maximum  $T_c$  of about 6.1 K, which remains nearly constant in a large pressure range between 30.1 and 50.3 GPa. Earlier studies have demonstrated superconductivity in bulk and thin films  $\text{SnSe}_2$  through intercalation and  $\text{gating}^{13,90-92}$  as well as interface superconductivity in  $\text{SnSe}_2/\text{jon-liquid}$  and  $\text{SnSe}_2/\text{graphene.}^{93,94}$ 

In this section we investigate the origin of the observed superconducting transition in SnSe<sub>2</sub> using the Migdal–Eliashberg (ME) formalism implemented in the EPW code.<sup>43,95</sup> To facilitate the comparison with the experimental results of Zhou *et al.*,<sup>28</sup> the superconducting properties are calculated at the experimental unit cell parameters for nonhydrostatic pressure points at 23 and 30 GPa while allowing the atomic positions to relax. The resulting electronic structure and phonon dispersion are shown in Fig. S14–S16 (ESI†).<sup>51</sup> A comparison with the plots under hydrostatic conditions at 20 and 30 GPa [Fig. 5, 6, and Fig. S3, ESI†] demonstrate that the electronic structure is highly insensitive to the crystal structure parameters while the phonon frequencies are slightly affected. For instance, according to

Paper



Fig. 9 Calculated nonadiabatic phonon spectral function and nonadiabatic renormalized phonon for the H1 structure in the  $1 \times 1 \times 1$  unit cell of (a–c) SnSe<sub>2</sub> and (d–f) SnS<sub>2</sub> at various pressures. The solid black and dashed blue lines represent the DFPT phonon and renormalized phonon dispersions, respectively. The color map corresponds to the nonadiabatic phonon spectral function.

our phonon calculations within the harmonic approximation a lattice instability starts developing at 20 and 30 GPa under hydrostatic and nonhydrostatic conditions, respectively. Since the pressure-dependence of the lowest acoustic mode at the K point is responsible for the dynamical instability in this compound, the reduced in-plane compressibility rate in the latter case leads to a decrease in the phonon softening rate and consequently an increase in the stability region up to 30 GPa. While this trend is in the right direction, the transition pressure is still underestimated compared to the nonhydrostatic experiments in ref. 28 that showed no structural phase transition or decomposition up to 46 GPa. The situation is reminiscent of the one encountered in NbSe<sub>2</sub> and NbS<sub>2</sub>, where the instability found at the harmonic level has been shown to be weakened or even removed when quantum anharmonic effects are taken into account, and therefore suppress the formation of the CDW phase.<sup>16,30</sup> A similar scenario occurring in SnSe<sub>2</sub> would extend the stabilization region to higher pressures as found in experiment. To check this point, we re-evaluated the phonons at the K point with a larger smearing value of 0.03 Ry and indeed found that the imaginary phonon mode is removed, thus preserving the dynamic stability [see dash line in Fig. S16(a)  $(ESI^{\dagger})^{51}$ ].

In order to understand the origin of the superconducting state, we evaluate the Eliashberg spectral function  $\alpha^2 F(\omega)$  and the corresponding e-ph coupling strength  $\lambda$ . A comparative analysis of the  $\alpha^2 F(\omega)$  and the atomically resolved phonon DOS (PHDOS) at the experimental lattice cell parameters at 23 GPa [Fig. S15 (ESI<sup>†</sup>)<sup>51</sup>] reveals that the low-frequency phonons below 8 meV associated with both Sn and Se vibrations contribute

60% of the total  $\lambda = 0.62$ , while the phonons in the highfrequency region between 17 and 32 meV dominated by Se atoms vibrations give approximately 30% of  $\lambda$  [Fig. 10(b)]. Using a typical value of  $\mu^* = 0.1$ , we predict a  $T_c$  of 2.5 and 3.3 K from the numerical solutions of the isotropic and anisotropic ME gap equations,<sup>43,95</sup> slightly below the 4.0 K onset temperature ( $T_c^{\text{onset}}$ ) of electrical resistance drop at 22 GPa reported in ref. 28. The results are almost unchanged when the calculations are performed at the experimental lattice cell parameters at 30 GPa [Fig. S16 (ESI†)<sup>51</sup>]. For the *K* point phonons computed at the larger smearing value of 0.03 Ry, we get  $\lambda = 0.59$  and an isotropic  $T_c = 2.3$  K with  $\mu^* = 0.1$ .

Considering that superconductivity in SnSe<sub>2</sub> has been achieved experimentally either in Se-deficient<sup>28</sup> or intercalated<sup>13,90-92</sup> samples, we further investigate the impact of doping on the predicted  $T_c$  via a rigid shift of  $E_{\rm F}$ , chosen to match particular features either in the valence or in the conduction band, for the structure at the experimental lattice cell parameters at 23 GPa. The results summarized in Fig. 10 can be rationalized in terms of the changes taking place at the FS upon raising or lowering the Fermi level. In the undoped systems, the momentum-resolved e-ph coupling strength  $\lambda_k$  on the FS displays a highly anisotropic distribution (between 0.3 and 1.1) where the lower and upper regions of the spectra can be associated with the  $\Gamma$  and K-centered pockets, respectively [Fig. 11(a and c)]. A continuous distribution with a sizable anisotropy is also found for the superconducting gap on the FS as shown in Fig. 11(b and d). When  $E_{\rm F}$  is moved up by 0.7 eV, the spread in  $\lambda_{\rm k}$  is reduced to a much narrower range of 0.3–0.5 since the  $\Gamma$ -centered holelike FS sheet vanishes. However, the spread goes back to the wider range

Paper

#### View Article Online



Fig. 10 Variations in (a) DOS at  $E_{\rm F}$ , (b)  $\lambda$ , and (c)  $T_{\rm c}$  as a function of a rigid shift of the Fermi level for the H1 structure in the 1 × 1 × 1 unit cell of SnSe<sub>2</sub> at the experimental unit cell parameters at 23 GPa. In (b), squares represent the total  $\lambda$ , while circles, triangles, and rhombuses represent the contribution of the low-, medium- and high-energy modes. In (c), circles and squares represent the  $T_{\rm c}$  obtained from the numerical solutions of the anisotropic and isotropic ME equations.



**Fig. 11** Calculated superconducting properties for the H1 structure in the  $1 \times 1 \times 1$  unit cell of SnSe<sub>2</sub> at the experimental unit cell parameters at 23 GPa. Energy distribution of the (a) e-ph coupling strength  $\lambda_{\mathbf{k}}$  and (b) superconducting gap  $\Delta_{\mathbf{k}}$ ; color coded by FS sheets:  $\Gamma$ -centered holelike pocket FS<sub> $\Gamma$ </sub> (blue), and K-centered electronlike pocket FS<sub> $\kappa$ </sub> (red). Momentum-resolved (c) e-ph coupling strength  $\lambda_{\mathbf{k}}$  and (d) superconducting gap  $\Delta_{\mathbf{k}}$  on the FS (top-view). Energy distribution of the (e) e-ph coupling strength  $\lambda_{\mathbf{k}}$ , and (f), (g) superconducting gap  $\Delta_{\mathbf{k}}$  at T = 1 K at various rigid shifts of the Fermi level with respect to the original data as shown in Fig. S14 (ESI<sup>+</sup>).<sup>51</sup>

once the system is doped until the Fermi level matches the first peak in the conduction band DOS as two additional FS sheets are introduced, thus opening extra scattering channels. This leads to an enhancement in both  $\lambda = 0.72$  and  $T_c \approx 5.2$  K, the latter in good agreement with the maximum  $T_c$  value found experimentally. Similar trends are also observed when the Fermi level is shifted down. It is also worth noting that the non-linear dependence of the total  $\lambda$  with doping correlates closely with that of the low-energy phonons [Fig. 10], indicating that these modes play a decisive role in raising the e–ph coupling strength and  $T_c$  in this system.

For completeness, we also analyze the superconducting properties of  $SnS_2$ . Assuming that the dynamical stability of  $SnS_2$  can be extended to higher pressures under nonhydrostatic compression as for  $SnSe_2$ , we perform superconductivity calculations at 30 GPa and used a smearing value of 0.04 Ry for the phonons at

the *K* point in order to remove the imaginary frequency. The calculated PHDOS and Eliashberg spectral function comprise of two well defined regions separated by a gap between the acoustic and optical branches [Fig. S18 (ESI<sup>†</sup>)<sup>51</sup>]. Integrating  $\alpha^2 F(\omega)$ , the strength of the e-ph coupling  $\lambda$  is estimated to be 1.08. From the solutions of the isotropic and anisotropic ME gap equations with  $\mu^* = 0.1$ , we obtain a  $T_c$  of 4.6 and 5.9 K, respectively [Fig. S19–S20 (ESI<sup>†</sup>)<sup>51</sup>]. The values of  $\lambda$  and  $T_c$  are twice larger than those in SnSe<sub>2</sub> due to the enhanced coupling of the acoustic phonons dominated by Sn vibrations with the electronic state present at the Fermi level. Similar to SnSe<sub>2</sub>, the strongest coupling takes place on the *K*-centered FS, but both  $\lambda_k$  and  $\Delta_k$  exhibit a much broader distribution profile. We also find that  $\lambda$  is strongly affected by changes in the FS topology when  $E_F$  is shifted up or down. Namely, the e-ph coupling drops

significantly as the contribution of the low-energy acoustic modes is drastically reduced and large doping is required to raise back the  $T_c$ .

Finally, we investigate SnSe<sub>2</sub> and SnS<sub>2</sub> compounds in the H2-1 structure as potential superconductors. The results are presented in Fig. S21–S23 (ESI<sup>+</sup>).<sup>51</sup> Despite the close resemblance between the DOS and PHDOS of the parent and superlattice structures, the  $T_c$  in H2-1 phase is found to be an order of magnitude lower than in the H1 phase. This can be linked to a decrease in the e-ph coupling over the full phonon range due to the reorganization that takes place at the FS. Looking at the electronic band structure in the  $\sqrt{3} \times \sqrt{3} \times 1$  supercell [region enclosed by the green box in Fig. 6], it can be seen that the  $\Gamma$ -centered FS sheet disappears as a gap opens in the electronic band dominated by Se  $p_z$  orbitals. An increase in the DOS at  $E_F$  is expected to produce a marked enhancement in T<sub>c</sub>, particularly under hole doping as multiple bands will cross the Fermi level. In  $SnSe_2$  a 0.3 eV down shift in  $E_F$  results in an isotropic  $T_c = 3.7$  K, while in  $SnS_2$  a 0.5 eV down shift leads to  $T_c = 3.5$  K.

## IV. Conclusions

In this work, we have performed a comparative study of SnSe<sub>2</sub> and SnS<sub>2</sub> at ambient conditions and pressures up to 40 GPa. We show that the apparent contradictions among high-pressure results on SnSe<sub>2</sub> can be attributed to differences in experimental conditions and that inclusion of nonadiabatic effects improves the quantitative agreement with the measured Raman-active phonon frequencies. We further demonstrate that a periodic lattice transition, of a similar origin to the one observed in SnSe<sub>2</sub>, also occurs in SnS<sub>2</sub> above 20 GPa. In addition, we examine the nature of the superconducting state recently observed in SnSe2 under nonhydrostatic pressure, and provide evidence that the superconducting transition can be explained within a standard phonon-mediated mechanism. The emergence of superconductivity with a comparable critical temperature in SnS2 under similar experimental conditions is also predicted. Finally, we show that in the high pressure PLD H2-1 phase the T<sub>c</sub> is reduced by an order of magnitude compared to the high-symmetry H1 phase in both systems, a fact that we attribute to a restructuring and suppression of large parts of the Fermi surface.

# Conflicts of interest

There are no conflicts to declare.

# Acknowledgements

The authors thank J. Ying, V. V. Struzhkin, and F. Caruso for useful discussions. C. H. acknowledges support by the Austrian Science Fund (FWF) Project No. P32144-N36 and the VSC-3 of the Vienna University of Technology. G. P. K., H. P., and E. R. M. acknowledge support from the National Science Foundation (Award No. OAC-1740263). This work used Spiedie cluster at Binghamton University and Comet cluster at the San Diego Supercomputer Center through allocation TG-DMR180071. Comet is a dedicated XSEDE cluster,<sup>96</sup> which is supported by National Science Foundation Grant No. ACI-1548562.

# References

- 1 F. Ke, J. Yang, C. Liu, Q. Wang, Y. Li, J. Zhang, L. Wu, X. Zhang, Y. Han, B. Wu, Y. Ma and C. Gao, High-pressure electrical-transport properties of SnS: experimental and theoretical approaches, *J. Phys. Chem. C*, 2013, **117**, 6033.
- 2 J. Vidal, S. Lany, M. d'Avezac, A. Zunger, A. Zakutayev, J. Francis and J. Tate, Band-structure, optical properties, and defect physics of the photovoltaic semiconductor SnS, *Appl. Phys. Lett.*, 2012, **100**, 032104.
- 3 P. Sinsermsuksakul, L. Sun, S. W. Lee, H. H. Park, S. B. Kim, C. Yang and R. G. Gordon, Overcoming efficiency limitations of SnS-based solar cells, *Adv. Energy Mater.*, 2014, 4, 1400496.
- 4 L.-D. Zhao, S.-H. Lo, Y. Zhang, H. Sun, G. Tan, C. Uher, C. Wolverton, V. P. Dravid and M. G. Kanatzidis, Ultralow thermal conductivity and high thermoelectric figure of merit in SnSe crystals, *Nature*, 2014, **508**, 373.
- 5 G. Ding, G. Gao and K. Yao, High-efficient thermoelectric materials: The case of orthorhombic IV-VI compounds, *Sci. Rep.*, 2015, **5**, 9567.
- 6 H. Yu, S. Dai and Y. Chen, Enhanced power factor via the control of structural phase transition in SnSe, *Sci. Rep.*, 2016, **6**, 26193.
- 7 L. D. Zhao, G. Tan, S. Hao, J. He, Y. Pei, H. Chi, H. Wang, S. Gong, H. Xu, V. P. Dravid and C. Uher, Ultrahigh power factor and thermoelectric performance in hole-doped single-crystal SnSe, *Science*, 2016, **351**, 141.
- 8 A. Dewandre, O. Hellman, S. Bhattacharya, A. H. Romero, G. K. H. Madsen and M. J. Verstraete, Two-step phase transition in SnSe and the origins of its high power factor from first principles, *Phys. Rev. B*, 2016, **117**, 276601.
- 9 X. Chen, P. Lu, X. Wang, Y. Zhou, C. An, Y. Zhou, C. Xian, H. Gao, Z. Guo, C. Park, B. Hou, K. Peng, X. Zhou, J. Sun, Y. Xiong, Z. Yang, D. Xing and Y. Zhang, Topological Dirac line nodes and superconductivity coexist in SnSe at high pressure, *Phys. Rev. B*, 2017, **96**, 165123.
- 10 H. Yu, W. Lao, L. Wang, K. Li and Y. Chen, Pressurestabilized tin selenide phase with an unexpected stoichiometry and a predicted superconducting state at low temperatures, *Phys. Rev. Lett.*, 2017, **118**, 137002.
- 11 G. Marini, P. Barone, A. Sanna, C. Tresca, L. Benfatto and G. Profeta, Superconductivity in tin selenide under pressure, *Phys. Rev. Mater.*, 2019, 3, 114803.
- 12 J. Zhou, S. Zhang and J. Li, Normal-to-topological insulator martensitic phase transition in group-IV monochalcogenides driven by light, *NPG Asia Mater.*, 2020, **12**, **1**.
- 13 H. Wu, S. Li, M. Susner, S. Kwon, M. Kim, T. Haugan and B. Lv, Spacing dependent and cation doping independent superconductivity in intercalated 1T two dimensional SnSe<sub>2</sub>, 2D Mater., 2019, 6, 045048.
- 14 Y. Qi, P. G. Naumov, M. N. Ali, C. R. Rajamathi, W. Schnelle,O. Barkalov, M. Hanfland, S.-C. Wu, C. Shekhar, Y. Sun,

V. Sü, M. Schmidt, U. Schwarz, E. Pippel, P. Werner, R. Hillebrand, T. Förster, E. Kampert, S. Parkin, R. J. Cava, C. Felser, B. Yan and S. A. Medvedev, Superconductivity in Weyl semimetal candidate MoTe<sub>2</sub>, *Nat. Commun.*, 2016, 7, 11038.

- 15 X. C. Pan, X. Chen, H. Liu, Y. Feng, Z. Wei, Y. Zhou, Z. Chi, L. Pi, F. Yen, F. Song, X. Wan, Z. Yang, B. Wang, G. Wang and Y. Zhang, Pressure-driven dome-shaped superconductivity and electronic structural evolution in tungsten ditelluride, *Nat. Commun.*, 2015, **6**, 7805.
- 16 M. Leroux, I. Errea, M. L. Tacon, S.-M. Souliou, G. Garbarino, L. Cario, A. Bosak, F. Mauri, M. Calandra and P. Rodiere, Strong anharmonicity induces quantum melting of charge density wave in 2H-NbSe<sub>2</sub> under pressure, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2015, **92**, 140303.
- B. Sipos, A. F. Kusmartseva, A. Akrap, H. Berger, L. Forró and E. Tutiš, From Mott state to superconductivity in 1T-TaS<sub>2</sub>, *Nat. Mater.*, 2008, 7, 960.
- 18 H. Paudyal, S. Poncé, F. Giustino and E. R. Margine, Superconducting properties of MoTe<sub>2</sub> from ab initio anisotropic Migdal-Eliashberg theory, *Phys. Rev. B*, 2020, **101**, 214515.
- 19 J. Ying, H. Paudyal, C. Heil, X. J. Chen, V. V. Struzhkin and E. R. Margine, Unusual pressure-induced periodic lattice distortion in SnSe<sub>2</sub>, *Phys. Rev. Lett.*, 2018, **121**, 027003.
- 20 M. Calandra and F. Mauri, Charge-density wave and superconducting dome in TiSe<sub>2</sub> from electron-phonon interaction, *Phys. Rev. Lett.*, 2011, **106**, 196406.
- 21 M. N. Ali, J. Xiong, S. Flynn, J. Tao, Q. D. Gibson, L. M. Schoop, T. Liang, N. Haldolaarachchige, M. Hirschberger, N. P. Ong and R. J. Cava, Large, non-saturating magneto-resistance in WTe<sub>2</sub>, *Nature*, 2014, **514**, 205.
- 22 K. Nguyen-Cong, J. M. Gonzalez, B. A. Steele and I. I. Oleynik, Tin-Selenium compounds at ambient and high pressures, *J. Phys. Chem.*, 2018, **122**, 18274.
- 23 J. M. Gonzalez, K. Nguyen-Cong, B. A. Steele and I. I. Oleynik, Novel phases and superconductivity of tin sulfide compounds, *J. Chem. Phys.*, 2018, **148**, 194701.
- 24 Y. A. Timofeev, B. V. Vinogradov and V. B. Begoulev, Superconductivity of tin selenide at pressures up to 70 GPa, *Phys. Solid State*, 1997, **39**, 207.
- 25 A. H. C. Neto, Charge density wave, superconductivity, and anomalous metallic behavior in 2D transition metal dichalcogenides, *Phys. Rev. Lett.*, 2001, **86**, 4382.
- 26 D. Kang, Y. Zhou, W. Yi, C. Yang, J. Guo, Y. Shi, S. Zhang, Z. Wang, C. Zhang, S. Jiang, A. Li, K. Yang, Q. Wu, G. Zhang, L. Sun and Z. Zhao, Superconductivity emerging from a suppressed large magnetoresistant state in tungsten ditelluride, *Nat. Commun.*, 2015, **6**, 7804.
- 27 T. Valla, A. V. Fedorov, P. D. Johnson, P.-A. Glans, C. McGuinness, K. E. Smith, E. Y. Andrei and H. Berger, Quasiparticle spectra, charge-density waves, superconductivity, and electron-phonon coupling in 2H-NbSe<sub>2</sub>, *Phys. Rev. Lett.*, 2004, **92**, 086401.
- 28 Y. Zhou, B. Zhang, X. Chen, C. Gu, C. An, Y. Zhou, K. Cai, Y. Yuan, C. Chen, H. Wu, R. Zhang, C. Park, Y. Xiong, X. Zhang, K. Wang and Z. Yang, Pressure-induced metallization and

robust superconductivity in pristine 1 T-SnSe<sub>2</sub>, *Adv. Electron. Mater.*, 2018, **4**, 1800155.

- 29 W. Albers and K. Schol, The P-T-X phase diagram of the system Sn-S, *Philips Res. Rep.*, 1961, **16**, 329.
- 30 C. Heil, S. Poncé, H. Lambert, M. Schlipf, E. R. Margine and F. Giustino, Origin of superconductivity and latent charge density wave in NbS<sub>2</sub>, *Phys. Rev. Lett.*, 2017, **119**, 087003.
- M. Calandra, I. Mazin and F. Mauri, Effect of dimensionality on the charge-density wave in few-layer 2H-NbSe<sub>2</sub>, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2009, **80**, 241108.
- 32 M. D. Johannes and I. I. Mazin, Fermi surface nesting and the origin of charge density waves in metals, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2008, 77, 165135.
- 33 F. Weber, S. Rosenkranz, J.-P. Castellan, R. Osborn, R. Hott, R. Heid, K.-P. Bohnen, T. Egami, A. H. Said and D. Reznik, Extended phonon collapse and the origin of the chargedensity wave in 2H-NbSe<sub>2</sub>, *Phys. Rev. Lett.*, 2011, **107**, 107403.
- 34 P. Giannozzi, O. Andreussi, T. Brumme, O. Bunau, M. B. Nardelli, M. Calandra, R. Car, C. Cavazzoni, D. Ceresoli and M. Cococcioni, *et al.*, Advanced capabilities for materials modelling with Quantum ESPRESSO, *J. Phys.: Condens. Matter*, 2017, **29**, 465901.
- 35 D. R. Hamann, Optimized norm-conserving Vanderbilt pseudopotentials, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2013, **88**, 085117.
- 36 J. P. Perdew, K. Burke and M. Ernzerhof, Generalized gradient approximation made simple, *Phys. Rev. Lett.*, 1996, 77, 3865.
- 37 J. Klimeš, D. R. Bowler and A. Michaelides, van der Waals density functionals applied to solids, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2011, 83, 195131.
- 38 J. Klimeš, D. R. Bowler and A. Michaelides, Chemical accuracy for the van der Waals density functional, *J. Phys.: Condens. Matter*, 2010, 22, 022201.
- 39 N. Marzari, D. Vanderbilt, A. De Vita and M. Payne, Thermal contraction and disordering of the Al (110) surface, *Phys. Rev. Lett.*, 1999, 82, 3296.
- 40 H. J. Monkhorst and J. D. Pack, Special points for Brillouin-zone integrations, *Phys. Rev. B: Solid State*, 1976, 13, 5188.
- 41 S. Baroni, S. de Gironcoli, A. D. Corso and P. Giannozzi, Phonons and related crystal properties from density-functional perturbation theory, *Rev. Mod. Phys.*, 2001, 73, 515.
- 42 F. Giustino, M. L. Cohen and S. G. Louie, Electron-phonon interaction using Wannier functions, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2007, 76, 165108.
- 43 S. Poncé, E. R. Margine, C. Verdi and F. Giustino, EPW: Electron-phonon coupling, transport and superconducting properties using maximally localized Wannier functions, *Comput. Phys. Commun.*, 2016, **209**, 116.
- 44 N. Marzari, A. A. Mostofi, J. R. Yates, I. Souza and D. Vanderbilt, Maximally localized Wannier functions: Theory and applications, *Rev. Mod. Phys.*, 2012, **84**, 1419.
- 45 G. Pizzi, V. Vitale, R. Arita, S. Bluegel, F. Freimuth, G. Géranton, M. Gibertini, D. Gresch, C. Johnson and T. Koretsune, *et al.*, Wannier90 as a community code: new features and applications, *J. Phys.: Condens. Matter*, 2020, **32**, 165902.

- 46 Y. Huang, E. Sutter, J. T. Sadowski, M. Cotlet, O. L. Monti, D. A. Racke, M. R. Neupane, D. Wickramaratne, R. K. Lake, B. A. Parkinson and P. Sutter, Tin disulfide-an emerging layered metal dichalcogenide semiconductor: materials properties and device characteristics, *ACS Nano*, 2014, 8, 10743.
- 47 Z. V. Borges, C. M. Poffo, J. C. de Lima, S. M. Souza, D. M. Trichôs and R. S. de Biasi, High-pressure angle-dispersive X-ray diffraction study of mechanically alloyed SnSe<sub>2</sub>, *J. Appl. Phys.*, 2018, **124**, 215901.
- 48 K. Knorr, L. Ehm, M. Hytha, B. Winkler and W. Depmeier, The High pressure behaviour of SnS<sub>2</sub>: X-Ray powder diffraction and quantum mechanical calculations up to 10 GPa, *Phys. Status Solidi*, 2001, **223**, 435.
- 49 R. M. Hazen and L. W. Finger, The crystal structures and compressibilities of layer minerals at high pressure. I. SnS<sub>2</sub>, berndtite, *Am. Mineral.*, 1978, **63**, 289.
- 50 M. Ø. Fils, E. Eikeland, J. Zhang, S. R. Madsen and B. B. Iversen, Atomic and electronic structure transformations in SnS<sub>2</sub> at high pressures: a joint single crystal X-ray diffraction and DFT study, *Dalton Trans.*, 2016, **45**, 3798.
- 51 See ESI† at [url] for Fig. S1–S23 and Table S1.
- 52 L. Yang, L. Dai, H. Li, H. Hu, K. Liu, C. Pu, M. Hong and P. Liu, Pressure-induced metallization in MoSe<sub>2</sub> under different pressure conditions, *RSC Adv.*, 2019, **9**, 5794.
- 53 S. Duwal and C.-S. Yoo, Shear-induced isostructural phase transition and metallization of layered tungsten disulfide under nonhydrostatic compression, *J. Phys. Chem. C*, 2016, **120**, 5101.
- 54 M. Fujimoto, *The Physics of Structural Phase Transitions*, Springer-Verlag, New York, 2nd edn, 2005.
- 55 A. N. Kolmogorov, S. Shah, E. R. Margine, A. K. Kleppe and A. P. Jephcoat, Pressure-driven evolution of the covalent network in CaB<sub>6</sub>, *Phys. Rev. Lett.*, 2012, **109**, 075501.
- 56 S. Hajinazar, A. Thorn, E. D. Sandoval, S. Kharabadze and A. N. Kolmogorov, MAISE: Construction of neural network interatomic models and evolutionary structure optimization, *Comput. Phys. Commun.*, 2020, DOI: 10.1016/j.cpc.2020.107679.
- 57 S. Shah and A. N. Kolmogorov, Stability and superconductivity of Ca-B phases at ambient and high pressure, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2013, 88, 014107.
- 58 J. Gusakova, X. Wang, L. L. Shiau, A. Krivosheeva, V. Shaposhnikov, V. Borisenko, V. Gusakov and B. K. Tay, Electronic properties of bulk and monolayer TMDs: theoretical study within DFT framework (GVJ-2e method), *Phys. Status Solidi A*, 2017, **214**, 1700218.
- 59 A. Zunger and A. J. Freeman, Band structure and lattice i Mbility of TiSe<sub>2</sub>, *Phys. Rev. B: Solid State*, 1978, **17**, 1839.
- 60 F. J. Di Salvo, D. E. Moncton and J. V. Waszezak, Electronic properties and superlattice formation in the semimetal TiSe<sub>2</sub>, *Phys. Rev. B: Solid State*, 1976, **14**, 4321.
- 61 A. H. Reshak and S. Auluck, Electronic and optical properties of the 1T phases of TiS<sub>2</sub>, TiSe<sub>2</sub>, and TiTe<sub>2</sub>, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2003, 68, 245113.
- 62 G. Domingo, R. S. Itoga and C. R. Kannewurf, Fundamental optical absorption in SnS<sub>2</sub>, and SnSe<sub>2</sub>, *Phys. Rev.*, 1966, **143**, 536.

- 63 L. A. Burton, T. J. Whittles, D. Hesp, W. M. Linhart, J. M. Skelton, B. Hou, R. F. Webster, G. O'Dowd, C. Reece, D. Cherns, D. J. Fermin, T. D. Veal, V. R. Dhanak and A. Walsh, Electronic and optical properties of single crystal SnS<sub>2</sub>: an earth-abundant disulfide photocatalyst, *J. Mater. Chem. A*, 2016, 4, 1312.
- 64 P. Manou, J. A. Kalomiros, A. N. Anagnostopoulos and K. Kambas, Optical properties of SnSe<sub>2</sub> single crystals, *Phys. Rev.*, 1966, **143**, 536.
- 65 Y. Kumagai, L. A. Burton, A. Walsh and F. Oba, Electronic Structure and Defect Physics of Tin Sulfides: SnS, Sn<sub>2</sub>S<sub>3</sub>, and SnS<sub>2</sub>, *Phys. Rev. Appl.*, 2016, 6, 014009.
- 66 Z. R. Kudrynskyi, X. Wang, J. Sutcliffe, M. A. Bhuiyan, Y. Fu, Z. Yang, O. Makarovsky, L. Eaves, A. Solomon, V. T. Maslyuk, Z. D. Kovalyuk, L. Zhang and A. Patané, van der Waals  $SnSe_{2(1-x)}S_{2x}$  alloys: composition-dependent bowing coefficient and electron-phonon interaction, *Adv. Funct. Mater.*, 2020, **30**, 1908092.
- 67 J. M. Gonzalez and I. I. Oleynik, Layer-dependent properties of SnS<sub>2</sub> and SnSe<sub>2</sub> two-dimensional materials, *Phys. Rev. B*, 2016, 94, 125443.
- 68 H. Guo, T. Yang, P. Tao, Y. Wang and Z. Zhang, High pressure effect on structure, electronic structure, and thermoelectric properties of MoS<sub>2</sub>, *J. Appl. Phys.*, 2013, **113**, 013709.
- 69 V. Rajaji, U. Dutta, P. C. Sreeparvathy, S. Ch Sarma, Y. A. Sorb, B. Joseph, S. Sahoo, S. C. Peter, V. Kanchana and C. Narayana, Structural, vibrational, and electrical properties of 1T-TiTe<sub>2</sub> under hydrostatic pressure: experiments and theory, *Phys. Rev. B*, 2018, **97**, 085107.
- 70 A. P. Nayak, S. Bhattacharyya, J. Zhu, J. Liu, X. Wu, T. Pandey, C. Jin, A. K. Singh, D. Akinwande and J.-F. Lin, Pressureinduced semiconducting to metallic transition in multilayered molybdenum disulphide, *Nat. Commun.*, 2014, 5, 1.
- 71 L. Zhang, Y. Xie, T. Cui, Y. Li, Z. He, Y. Ma and G. Zou, Pressure-induced enhancement of electron-phonon coupling in superconducting CaC<sub>6</sub> from first principles, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2006, 74, 184519.
- 72 J. S. Kim, L. Boeri, R. K. Kremer and F. S. Razavi, Effect of pressure on superconducting Ca-intercalated graphite CaC<sub>6</sub>, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2006, 74, 214513.
- 73 M. Calandra, A. N. Kolmogorov and S. Curtarolo, Search for high  $T_c$  in layered structures: The case of LiB, *Phys. Rev. B:* Condens. Matter Mater. Phys., 2007, 75, 144506.
- 74 F. Giustino, Electron-phonon interactions from first principles, *Rev. Mod. Phys.*, 2017, 89, 015003.
- 75 P. Zhang, S. G. Louie and M. L. Cohen, Nonlocal Screening, Electron-Phonon Coupling, and Phonon Renormalization in Metals, *Phys. Rev. Lett.*, 2005, **94**, 225502.
- 76 We want to note at this point that there has been a mistake in the calculation of  $\Pi_{\mathbf{q}\nu}^{\mathrm{a}}$  and  $\chi_{\mathbf{q}}^{\mathrm{0,CMA}}$  in ref. 19, related to the wannierization of the Fermi surface bands. We have repeated all calculations and found that while the corrected results differ quantitatively, the qualitative characteristics and the conclusions drawn remain valid.
- 77 In the case of those pressures, where SnSe<sub>2</sub> is in the metallic phase,  $g^{\rm b}_{mn,\nu}({\bf k},{\bf q}) \times g^*_{mn,\nu}({\bf k},{\bf q})$  has been approximated using

the standard expression  $|g_{mn,\nu}(\mathbf{k},\mathbf{q})|^2$  due to the fact that  $\varepsilon(\mathbf{q},\omega=0)$  diverges for metals.

- 78 Due to the layered structure of the considered compounds, the dielectric function exhibits a slight anisotropy with respect to its in-plane and out-of-plane components, as shown in Fig. S13 (ESI<sup>†</sup>).<sup>51</sup> The differences between calculations using the in-plane, the out-of-plane or an average of the two are negligible. For simplicity and consistency, all results presented in the paper where therefore obtained using the in-plane value of the dielectric function.
- 79 S. Pisana, M. Lazzeri, C. Casiraghi, K. S. Novoselov, A. K. Geim, A. C. Ferrari and F. Mauri, Breakdown of the adiabatic Born–Oppenheimer approximation in graphene, *Nat. Mater.*, 2007, 6, 198.
- 80 N. Caudal, A. M. Saitta, M. Lazzeri and F. Mauri, Kohn anomalies and nonadiabaticity in doped carbon nanotubes, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2007, 75, 115423.
- 81 M. Calandra, M. Lazzeri and F. Mauri, Anharmonic and nonadiabatic effects in MgB<sub>2</sub>: Implicationsfor the isotope effect and interpretation of Raman spectra, *Phys. C*, 2007, **456**, 38.
- 82 A. M. Saitta, M. Lazzeri, M. Calandra and F. Mauri, Giant Nonadiabatic Effects in Layer Metals: Raman Spectra of Intercalated Graphite Explained, *Phys. Rev. Lett.*, 2008, 100, 226401.
- 83 M. Calandra, G. Profeta and F. Mauri, Adiabatic and nonadiabatic phonon dispersion in a Wannier function approach, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2010, 82, 165111.
- 84 S. V. Bhatt, M. P. Deshpande, V. Sathe and S. H. Chaki, Effect of pressure and temperature on Raman scattering and an anharmonicity study of tin dichalcogenide single crystals, *Solid State Commun.*, 2015, **201**, 54.
- 85 A. N. Utyuzh, Y. A. Timofeev and G. N. Stepanov, Effect of pressure on Raman spectra of SnS<sub>2</sub> single crystals, *Phys. Solid State*, 2010, **52**, 352.
- 86 P. B. Allen, Neutron spectroscopy of superconductors, *Phys. Rev. B: Solid State*, 1972, 6, 2577.
- 87 F. Caruso, M. Hoesch, P. Achatz, J. Serrano, M. Krisch, E. Bustarret and F. Giustino, Nonadiabatic Kohn Anomaly

in Heavily Boron-Doped Diamond, Phys. Rev. Lett., 2017, 119, 017001.

- 88 J.-M. Wagner and F. Bechstedt, Pressure dependence of the dielectric and lattice-dynamical properties of GaN and A1N, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2000, **62**, 4526.
- 89 A. R. Goñi, H. Siegle, K. Syassen, C. Thomsen and J.-M. Wagner, Effect of pressure on optical phonon modes and transverse effective charges in GaN and AlN, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2001, 64, 035205.
- D. O'Hare, H. V. Wong, S. Hazell and J. W. Hodby, Relatively isotropic superconductivity at 8.3 K in the Lamellar organometallic intercalate SnSe<sub>2</sub>{Co(η-C<sub>5</sub>H<sub>5</sub>)<sub>2</sub>}<sub>0.3</sub>, *Adv. Mater.*, 1992, 4, 658.
- 91 Z. Li, Y. Zhao, K. Mu, H. Shan, Y. Guo, J. Wu, Y. Su, Q. Wu, Z. Sun, A. Zhao, X. Cui, C. Wu and Y. Xie, Molecule-confined engineering toward superconductivity and ferromagnetism in two-dimensional superlattice, *J. Am. Chem. Soc.*, 2017, 139, 16398.
- 92 Y. Song, X. Liang, J. Guo, J. Deng, G. Gao and X. Chen, Superconductivity in Li-intercalated 1 T-SnSe<sub>2</sub> driven by electric field gating, *Phys. Rev. Mater.*, 2019, 3, 054804.
- 93 J. Zeng, E. Liu, Y. Fu, Z. Chen, C. Pan, C. Wang, M. Wang, Y. Wang, K. Xu, S. Cai, X. Yan, Y. Wang, X. Liu, P. Wang, S. J. Liang, Y. Cui, H. Y. Hwang, H. Yuan and F. Miao, Gateinduced interfacial superconductivity in 1T-SnSe<sub>2</sub>, *Nano Lett.*, 2018, **18**, 1410.
- 94 Y. M. Zhang, J. Q. Fan, W. L. Wang, D. Zhang, L. Wang, W. Li, K. He, C. L. Song, X. C. Ma and Q. K. Xue, Observation of interface superconductivity in a SnSe<sub>2</sub>/epitaxial graphene van der Waals heterostructure, *Phys. Rev. B*, 2018, **98**, 220508(R).
- 95 E. R. Margine and F. Giustino, Anisotropic Migdal-Eliashberg theory using Wannier functions, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2013, 87, 024505.
- 96 J. Towns, T. Cockerill, M. Dahan, I. Foster, K. Gaither, A. Grimshaw, V. Hazlewood, S. Lathrop, D. Lifka, G. D. Peterson, R. Roskies, J. R. Scott and N. Wilkins-Diehr, XSEDE: Accelerating scientific discovery, *Comput. Sci. Eng.*, 2014, 16, 62.