

Decellularization following fixation of explanted aortic valves as a strategy for preserving native mechanical properties and function

Manisha Singh^{1†}, Clara Park^{2†}, Ellen T. Roche^{1,2*}

¹Institute for Medical Engineering and Science, Massachusetts Institute of Technology, Cambridge, MA, USA

²Department of Mechanical Engineering, Massachusetts Institute of Technology, Cambridge, MA, USA

[†]These authors have contributed equally to this work and share first authorship

***Correspondence:**
Corresponding Author
etr@mit.edu

Keywords: decellularization, aortic valves, hydrodynamic testing, mechanical properties, aldehyde fixation

Abstract

Mechanical or biological aortic valves are incorporated in physical cardiac simulators for surgical training, educational purposes, and device testing. They suffer from limitations including either a lack of anatomical and biomechanical accuracy or a short lifespan, hence limiting the authentic hands-on learning experience. Medical schools utilize hearts from human cadavers for teaching and research, but these formaldehyde-fixed aortic valves contort and stiffen relative to native valves. Here, we compare a panel of different chemical treatment methods on explanted porcine aortic valves and evaluate the microscopic and macroscopic features of each treatment with a primary focus on mechanical function. A surfactant-based decellularization method after formaldehyde fixation is shown to have mechanical properties close to those of the native aortic valve. Valves treated in this method were integrated into a custom-built left heart cardiac simulator to test their hemodynamic performance. This decellularization, post-fixation technique produced aortic valves which have ultimate stress and elastic modulus in the range of the native leaflets. Decellularization of fixed valves reduced the valvular regurgitation by 60% compared to formaldehyde-fixed valves. This fixation method has implications for scenarios where the dynamic function of preserved valves is required, such as in surgical trainers or device test rigs.

Introduction

Cardiovascular benchtop models with mock circulatory loops are increasingly used for surgical training (Ramphal et al. 2005, Mchale and Fago 2017, Feins et al. 2017), as educational platforms (Gehron et al. 2019, Villanueva, Xiong, and Rajput 2020), and for research purposes (Chinchoy et al. 2000, Maglio et al. 2021). These systems are typically composed of a mock circulatory loop connected to a pulsatile pump, but often lack anatomical representations and mechanical properties of the components of the heart (Wu et al. 1996, Timms et al. 2005, Taylor and Miller 2012). Some cardiac

simulators utilize *ex vivo* heart tissue to realistically recapitulate the anatomy and flow response (Vismara et al. 2016, Leopaldi et al. 2012), but the shelf-life of freshly explanted tissue without any chemical preservation or perfusion is limited to approximately 4 hours. A new class of *in vitro* cardiac simulators use chemically preserved explanted heart tissue to maintain anatomic fidelity (Park et al. 2020), but competent valves are required for utility as *in vitro* cardiovascular simulators for education and training. Therefore, we screened methods that would preserve valves, and ultimately surrounding intracardiac tissue, while ensuring their competency to enable physiological biomechanics and hemodynamics. Hence, there is an unmet need for tissue engineering techniques or chemical treatment methods for native tissues to — (i) extend their post-explant longevity, (ii) enable practical use in mock-circulatory benchtop models, (iii) retain biomechanical properties.

Tissue engineering techniques, such as decellularization via surfactants, can successfully produce tissue scaffolds with mechanical properties similar to native valves, but the resulting scaffolds require special storage conditions (e.g., 4°C, or slow cooling medium, etc.) for their long-term usage and may not be suitable for benchtop applications (Urbani et al. 2017, Maghsoudlou et al. 2013, Gupta, Mishra, and Dhasmana 2017). Chemical-induced crosslinking (e.g., through aldehydes or carbodiimides) subsequent to surfactant processing has also been reported to enhance the life-span and storage of the decellularized tissues (Liu et al. 2019) at room temperature. Although thin valve leaflets can easily be decellularized and crosslinked with immersion techniques, successful decellularization of a whole heart requires complex perfusion bioreactors (Guyette et al. 2014).

Human cadaveric heart specimens, which are often chemically treated with formaldehyde, are commonly available in medical schools but stiffen due to crosslinking and are rendered immobile, limiting their use to demonstrating gross heart anatomy and preventing them from being reanimated in mock loops. Chemical preservation of valves utilizes aldehyde-based fixatives which alter the mechanical properties of aortic valve leaflets, hence affecting the function of the valves, and thus the biomimicry of any simulator in which they are installed (Christie 1992). Glutaraldehyde fixed leaflets have been reported to be about 100 times stiffer than native leaflets (Talman and Boughner 1995). Therefore, we screened methods that would improve biomimicry of already preserved valves, and ultimately surrounding intracardiac tissue, while ensuring their competency to enable physiological biomechanics and hemodynamics.

In this study, we compare fixation via formaldehyde and decellularization via surfactants. We limit the scope to aortic valve leaflets and specifically examine treatment effects on the multiscale structure and mechanical properties. We hypothesize that a combination of aldehyde-fixation followed by surfactant-based decellularization may preserve the mechanical properties of native aortic leaflets for use in high fidelity mock circulatory loops and cardiac simulators. For this work, formaldehyde crosslinking has been chosen over glutaraldehyde owing to (i) faster crosslinking, (ii) availability of formaldehyde-fixed cadaveric hearts in hospitals and medical schools, and (iii) fewer concerns of formaldehyde induced toxicity for *in vitro* applications. Many studies have investigated surfactant-based decellularization involving ionic (e.g., sodium dodecyl sulfate, sodium deoxycholate), non-ionic (e.g., Triton X-100), and a combination thereof (Luo et al. 2019, Zhou et al. 2010). For our purposes, we selected a combination of ionic sodium deoxycholate (SD) and a non-ionic surfactant (Triton X-100) to restore the mechanical function of fixed valves due to superior efficiency in cell removal and matrix preservation over other techniques (Kasimir et al. 2003, Luo et al. 2019). Herein, we assess the impact of SD/Triton X-100 decellularization on formaldehyde-fixed valvular leaflets and compare the mechanical properties of the resulting leaflets with their native counterpart. Furthermore, the effects of

surfactants on the micromechanics and morphology of fixed valves were evaluated with Fourier transform infrared spectroscopy (FTIR) and scanning electron microscopy (SEM) and compared with native porcine valves. Next, a physiologically relevant left heart cardiac simulator was custom-built to house the chemically treated aortic valves and their hemodynamic performance was compared to native, fixed, and decellularized valves. At present, cardiac hemodynamics and biomechanics are mainly taught using textbooks and computational models (Mittal et al. 2016). Here, we identify a process that may enable realistic recapitulation of valve function on the bench which enables hands-on cardiac biomechanics education. These chemical treatment techniques have the potential to preserve biomimicry and biomechanics of aortic leaflets while extending their shelf-life so they can be installed in cardiac simulators as an educational or research tool.

Materials and Methods

Treatment of porcine aortic valves

Fresh porcine hearts with intact ascending aorta were purchased from Sierra for Medical Science Inc., (California, USA). A 3 cm long segment of the aorta with valves attached at the annulus was dissected from the hearts. Before processing, valves were thoroughly washed with 1X phosphate-buffered saline (PBS) of pH 7.4 to remove all blood and blood clots. For aldehyde-based fixation, the explanted aortic valves (n=3) were submerged in 200 mL of 10 % Neutral-buffered Formalin (Sigma Aldrich) over a gentle shaker for 18 hours at 25°C and thoroughly washed in 1X PBS thereafter. For decellularization, the explanted valves (n=3) were treated in a 200 mL mixture of 5 % (or 10% for increased surfactant concentration) w/v Sodium Deoxycholate (Sigma Aldrich) and 5 % (or 10 % for increased surfactant concentration) w/v Triton X-100 (Thermo Fisher Scientific) in 1X PBS over gentle shaking for a total of 48 hours at 25°C. The solution was refreshed after 24 hours during decellularization. For the combination of fixation and decellularization, the valves were first fixed in formaldehyde followed by the surfactant-based decellularization as mentioned above. The fresh, formaldehyde-treated, decellularized aortic valves, and those that were decellularized after fixation are referred to as ‘native’, ‘fixed’, ‘decel’, and ‘fixed-decel’ respectively throughout the text. Two different concentrations of 5 and 10 w/v% of the surfactants were used and referred to as ‘fixed-decel 5%’ and ‘fixed-decel 10%’, respectively.

Fourier Transform Infrared Spectroscopy (FTIR)

Dried fresh (n=3) and chemically-treated porcine aortic valves (n=3) were studied using infrared spectroscopy in Attenuated Total Reflection mode using a Thermo Fisher FTIR6700 Fourier Transform Infrared Spectrometer. Data were acquired at a resolution of 4 cm⁻¹ with 64 scans and a scan range of 4000-500 cm⁻¹.

Scanning Electron Microscopy (SEM)

Fresh (n=3) and chemically treated valves (n=3) were immersed in 2.5 % glutaraldehyde for 1 hour, dehydrated with ethanol, and then dried for 12 hours before embedding in paraffin wax for cross-sectional evaluation. Prior to imaging with a scanning electron microscope, the samples were sputter-coated (50 nm) with gold. Images were acquired by Zeiss Merlin high-resolution electron microscope at an acceleration voltage of 1 kV and a working distance of 4-6 mm.

Mechanical performance

The valve leaflets were cut from fresh and chemically treated aortic segments. The leaflets of each type of valve (n=3) were stretched uniaxially in the radial direction at a rate of 10 mm min⁻¹ using an Instron 5944 mechanical tester equipped with a 2-kN load cell. Prior to testing, the thickness and size of each leaflet were measured using a micrometer and vernier caliper respectively to calculate stress and strain from the recorded force vs. displacement data. From literature, it is evident that the strength of an aortic valve leaflet is weaker in the radial direction than circumferential. Testing in the weaker (i.e., radial) direction was performed as it represented the worst case condition for cyclic hydrodynamic testing.

Hydrodynamic assessment

A mock circulatory loop representing the left heart circulation was built in-house for hydrodynamic evaluation of the aortic valves. A pulsatile pump (Harvard Apparatus, USA) was connected to the loop to create a pulsatile flow at 60 beats per min under physiological conditions at a cardiac output of 3.6 L min⁻¹. The aortic valve was sutured on a sewing ring on a 3D-printed adaptor and mounted onto the circuit. Hydrodynamic parameters were measured in real-time using pressure sensors (PendoTECH) before and after the valve and an ultrasonic flow probe (Transonic) placed after the valve and connected to a T420 multi-channel research console (Transonic). An endoscopic camera (NIDAGE wireless) was used to record real-time valve function and leaflet motion. Sensor output was acquired for approximately 10 beats per sample using PowerLab (ADInstruments). A total of three samples were used for each valve type except for the mechanical valve. Only one specimen was used for mechanical valve due to its high repeatability and robustness.

Statistical analysis

All data are presented as mean $\pm$ Std Dev, with n=3, unless stated otherwise. The p-values (*p < 0.05) are calculated using one-way ANOVA with Tukey correction in Origin Pro 2019 (64-bit) and ns denotes no statistical difference.

Results

Micromechanics and surface characterization of valve leaflets

Aortic valves function in a mechanically demanding environment that requires micromechanical remodeling of the leaflet tissue. Explanted valves require chemical treatments to match the inherent mechanical properties of the native valvular tissue. Among various chemical treatments, aldehyde-based fixation is considered the gold standard but causes the aortic valves to stiffen and mechanically deform (**Figure 1A**). Decellularization is an alternative technique but results in a weak scaffold that is prone to material failure. In this study, we have adopted a combination of aldehyde-based fixation and surfactant-based decellularization to yield mechanically strong yet soft leaflets that mimic the native valves closely (**Figure 1A**). The native leaflets are thin, flexible, and mainly comprised of collagen and elastin fibers. The collagen fibers are corrugated and arranged in the circumferential direction whereas elastin fibers are positioned in the radial direction (**Figure 1B**). During diastole, continuous stretching of elastin occurs which causes the initially crimped collagen fibers to uncrimp from a wavy configuration to straight. To detect any conformational and structural alterations in the collagen and elastin fibers due to various chemical treatments, Fourier Transform Infrared Spectroscopy (FTIR) was performed. The overlay of FTIR spectra of treated and control samples showed no new absorption peaks but detected changes in peak intensity and positions (**Figure 1C**). The wide band from 3500-3200 cm⁻¹ corresponds to the symmetric and asymmetric stretching vibrations of -OH and -NH functional groups. The wide peak intensity was reduced by 85 % for fixed samples, indicating covalent

interactions of amine and hydroxyl groups through aldehyde crosslinking. The asymmetric and symmetric $-\text{CH}_2$ stretching bands from elastin and collagen structures are located at $2950\text{--}2850\text{ cm}^{-1}$. The absence of an aldehyde characteristic peak in fixed and fixed-decel samples at 1730 cm^{-1} indicates that no free aldehyde groups are present, and leaflets have been washed thoroughly. The 40 % increase in the intensity of amide I ($-\text{CO-NH- I}$) and amide II ($-\text{CO-NH- II}$) peaks at 1630 cm^{-1} and 1550 cm^{-1} for fixed-decel samples indicates the conformation and orientation changes in the secondary protein's structure of collagen and elastin as compared to fixed groups.

FTIR surface characterization is also supported by the morphology of the valvular leaflets (**Figure 2**). The crimping of collagen and elastin fibers is observed in the case of fixed samples when imaged under a scanning electron microscope from the surface (**Figure 2B**). No obvious difference in pore size was observed for native, decel, and fixed-decel groups (**Figure 2A, 2C, 2D**). The decel group showed thinner fiber structures and loose surface texture when compared to native valves (**Figure 2D**). This is likely due to detergent-mediated solubilization and dissociation of cell membranes. Cross-sectioned morphology exhibits that the fibers in the fixed group are much more tightly packed than the fixed-decel samples (**Figure 2F-2G**). The increased porosity in fixed-decel samples could be attributed to the solubilization of membrane proteins by surfactants. SEM also confirmed that the cells were removed from the decel group, therefore causing the collagen fibers to loosen to a porous structure (**Figure 2H**).

Combination of fixation and decellularization yields native tissue-mimicking mechanical properties

Due to the circumferential orientation of collagen fibers, leaflets are stiffer in the circumferential direction than the radial while exhibiting more extensibility in the radial direction. To compare the mechanical properties of chemically-treated leaflets with native, a uniaxial tensile test was performed in the radial direction (**Figure 3A**). Prior to mounting the samples in a mechanical tester, the thickness of each leaflet was measured with a digital micrometer. The thickness of fixed specimens increased by 67 % whereas it decreased by 45 % for decellularized samples when compared to native aortic valves (**Figure 3B**). The combination of fixed and decellularization resulted in a thickness comparable to the native tissue. As the weight of surfactants for decellularization was increased from 5 to 10 %, a further reduction of 16 % was noted in the mean value of thickness for fixed-decel groups, although it is not statistically significant according to one-way ANOVA with Tukey correction. Fixed samples have the highest ultimate stress of $755 \pm 17\text{ kPa}$ which is significantly higher than the native porcine aortic valves $677 \pm 36\text{ kPa}$ (**Figure 3B**). Combination of fixation and decellularization yielded ultimate stress of $683 \pm 44\text{ kPa}$ and $640 \pm 54\text{ kPa}$ for 5 and 10 % surfactant concentration, respectively. Decellularization alone reduced the maximum stress at the failure to $538 \pm 29\text{ kPa}$, which is significantly weaker than native leaflets. Similar trends were observed in the modulus of elasticity (calculated under 5% strain levels) where fixation alone resulted in significantly stiffer ($1.4 \pm 0.09\text{ MPa}$) samples as compared to native tissue ($1 \pm 0.05\text{ MPa}$) (**Figure 3C**). Fixed-decel groups yielded an elastic modulus of $1.2 \pm 0.2\text{ MPa}$ and $1 \pm 0.08\text{ MPa}$ for 5 and 10 % surfactant concentration respectively, both of which matched closely ($p > 0.05$; one-way ANOVA with Tukey correction) with native tissues. Decellularized groups exhibited the lowest modulus of elasticity $0.8 \pm 0.02\text{ MPa}$. There is no statistically significant difference between the ultimate strain of native aortic valves $120 \pm 8\%$ to that of fixed-decel $124 \pm 6\%$ and $119 \pm 7\%$ for 5 and 10 %, respectively (**Figure 3C**). Fixed samples exhibited ultimate tensile strains of $94 \pm 5\%$, which is 1.3 times lower than the native group. Ultimate stress and elastic modulus are plotted for a two-dimensional comparison of chemically treated groups with native control (**Figure 3D**). An overlap in the mechanical properties was observed for fixed-decel samples whereas the pristine decel and fixed samples showed a contrasting difference in comparison

to native leaflets. From the data above, it can be concluded that the combination of fixation and decellularization techniques matches the mechanical properties of native aortic tissues whereas the controls of fixation and decellularization alone are either too stiff or weak.

Hydrodynamic assessment of chemically treated aortic valves

For evaluating the hydrodynamic performance of chemically treated aortic valves, we built a benchtop setup with a pulsatile mock circulatory loop mimicking the left heart circulation (**Figure 4A**). Along with the anatomically accurate aortic valves, our custom-built flow setup houses a reservoir to store the fluid, a compliance chamber to mimic the aortic compliance, and a pulsatile pump to displace fluid at physiologically relevant ventricular stroke volumes (SV) and heart rates. Left ventricular (0-120 mmHg) (LVP) and aortic (60-120 mmHg) pressure (AoP) conditions are simulated by controlling the resistance valves in the flow circuit. Two pressure sensors were placed before and after the valves to acquire the real-time pressures during valve performance testing. A flow probe was placed downstream of the aortic valve to record any changes in the forward and backward flow. The recorded left ventricle and aortic pressures and flow for native porcine valves at 60 bpm and SV of 60 mL over a few cardiac cycles are shown in **Figure 4B, 4C**. Based on LVP and AoP readings, the mean transvalvular systolic pressure gradients for native porcine valves were calculated and plotted in **Figure 4D**. Aortic flow data was used to calculate the regurgitation %, which represents the ratio of the regurgitant volume and the stroke volume, expressed in percentage. An endoscopic camera records the real-time leaflet motion during systole and diastole phases (**Figure 4E, Video 1**). Normalized orifice area determines the ratio of the geometrical opening area of the valves at peak systole and the cross-sectional area of the attached aorta. The geometrical opening area of the valves was calculated using ImageJ (Abràmoff, Magalhães, and Ram 2004) from the recorded endoscope camera videos. The representative images in **Figure 4E** and **Video 1** qualitatively compare the opening (during systole) and closing (during diastole) of chemically treated valves relative to the native/fresh aortic valve and a mechanical St. Jude valve. The aldehyde-based crosslinking continues over time, and treated tissues turn stiffer with age (Sacks and Liao 2018). In order to account for the stiffening of fixed valves with time, we included an additional control group comprising of one-year-old fixed aortic valves. As seen in **Figure 4E**, the fixed valves turn stiff and do not completely close at diastole. The mechanically deformed area related to the partial closure is highlighted by red dotted circles, which is more apparent in the one-year-old samples. When the fixation was combined with decellularization for the same valves, no gaps were visible between the valve leaflets during diastole (**Figure 4E**). Mean transvalvular pressure gradients (ΔP) also support this observation and ΔP required for complete closure are significantly different in the case of chemically-treated valves relative to the native (**Figure 4F**). The recorded ΔP for fixed and decel groups are 4.6 ± 0.4 and 2.8 ± 0.3 mmHg, respectively which are statistically different ($p < 0.05$; one-way ANOVA with Tukey correction) when compared to native 3.7 ± 0.4 mmHg and fixed-decel 3.9 ± 0.3 mmHg groups. One-year-old (y/o) formaldehyde-fixed groups exhibited an ΔP of 13.0 ± 1.8 mmHg, which was reduced to 8.0 ± 0.6 mmHg when followed by decellularization. Fixation after decellularization clearly reduced the transvalvular pressure gradients relative to fixed groups, but no significant differences ($p > 0.5$) were noted in the normalized orifice area opening at peak systole of fixed vs. fixed-decel groups (**Figure 4G**). However, owing to the synergistic effect of reduced stiffness and ultimate strain (**Figure 3C**) for fixed-decel versus fixed groups, complete closure of fixed-decel groups was observed at peak diastole relative to fixed groups (**Figure 4E**). This observation is also in line with the regurgitant flow calculations (**Figure 4G**). The fixed groups showed the highest regurgitation of 15 ± 2 % which was lowered to 6 ± 0.9 % for fixed-decel groups that match closely with native 5.7 ± 1 % groups (**Figure 4G**).

253 Discussion

254 In this work, we have demonstrated that hemodynamic function and biomechanical properties of
 255 formaldehyde-fixed aortic valve tissues can be improved when treated with a combination of sodium
 256 deoxycholate (SD)/ Triton X-100 surfactants. We have compared several chemical treatment methods
 257 on explanted porcine aortic valves and evaluated microscopic and macroscopic features of each
 258 treatment with a primary focus on mechanical function. Our results show that the decellularization
 259 process lowers the ultimate strength and elastic modulus of aldehyde-fixed valve leaflets. This
 260 reduction in mechanical strength (i.e., ultimate stress and elastic modulus) of the fixed tissues may be
 261 attributed to (i) modification of structural components, such as collagen and/ or elastin fiber
 262 rearrangements (**Figure 2**), (ii) solubilization and dissociation of cell membranes by the detergents
 263 (**Figure 1C**), or (iii) a combination thereof.

264 The resulting valves with biomimicking mechanical properties can be directly employed in cardiac
 265 simulators for educational and training purposes, as shown in our left heart pulsatile flow loop equipped
 266 with real-time hydrodynamic readings and intravascular imaging. Using this technique to restore the
 267 mechanics of preserved tissues can potentially be extended to high-fidelity physical heart simulators
 268 with utility in medical education or procedural planning. For instance, human cadaveric heart
 269 specimens, which are commonly used in anatomy labs in medical schools to teach gross anatomy
 270 (James et al. 2019), may be restored to have competent valve function and attached to a mock
 271 circulatory loop. Further, the preserved hearts can potentially be reanimated using a biohybrid approach
 272 (Park et al. 2020) to produce an interactive, beating heart model which would complement the current
 273 educational tools with an enhanced learning and training experience. In the future, this technique can
 274 potentially be employed for building accurate *in vitro* prototypes to experimentally validate
 275 computational models, such as fluid-structure interaction with dynamic function of the aortic valve
 276 (Dumont et al. 2004) or for device testing and procedural planning purposes.

277 Several limitations of the current study should be noted — (i) the panel of treatment options did not
 278 include decellularization followed by fixation, which is commonly used for bioprosthetic valves made
 279 from pericardium for implantation but was excluded from our work as we wish to extend the treatment
 280 process to the whole heart, including the vessels and myocardial tissue, ideally without using
 281 reperfusion bioreactors for ease of manufacturability; (ii) for a proof-of-concept, we selected one
 282 protocol for decellularization (i.e., the combination of SD and Triton X-100) and our current study
 283 lacks a detailed comparison of the several other alternative decellularization methods described in the
 284 literature; (iii) since this work focuses on restoring native valve mechanical properties in aldehyde-
 285 fixed valves for benchtop applications, the degree of cell removal has not been assessed. Before
 286 adaptation of this work for any *in vivo* or tissue engineering application, detailed characterization on
 287 cell removal and toxicity is required; (iv) preliminary hydrodynamic testing use water which does not
 288 mimic the density and viscosity of blood. A monoethylene glycol-based blood-mimicking fluid as
 289 described in our previous work (Singh et al. 2021) could improve the hydrodynamic accuracy; (v) since
 290 the valves were manually sutured to an adaptor to align them normal to the flow circuit, the natural
 291 annulus size and tension applied to the leaflets may have been altered, potentially leading to variability
 292 in the normalized orifice area; (vi) preliminary hydrodynamic testing does not include the fatigue
 293 performance of the valves under pulsatile physiological loading and is part of our future work.

294 In conclusion, we find that a surfactant-based decellularization technique can restore the native
 295 biomechanical properties of aldehyde-fixed aortic valves. The ability to retrospectively decellularize
 296 fixed valves and reanimate them in benchtop simulators to recapitulate biomechanics has utility in
 297 cardiovascular education, training, and research.

298 Conflict of Interest

299 The authors declare that the research was conducted in the absence of any commercial or financial
300 relationships that could be construed as a potential conflict of interest.

301 Funding

302 This research was funded in part by the Department of Mechanical Engineering at Massachusetts
303 Institute of Technology and in part by a CAREER Award to ETR from the National Science Foundation
304 (1847541).

305 Acknowledgments

306 The authors would like to acknowledge the Materials Science and Engineering Center at the
307 Massachusetts Institute of Technology (MIT), for use of their material analysis and electron
308 microscopy facilities. Figures and digital illustrations are created with Adobe Illustrator and
309 BioRender.com. The data is plotted and evaluated with the software OriginPro 2019.

310 Data Availability Statement

311 The original contributions presented in the study are included in the article, further inquiries can be
312 directed to the corresponding author/s.

313 Author contribution statement

314 MS and CP contributed equally to this study. MS, CP, and ETR designed the study and wrote the
315 manuscript. MS and CP performed the experiments and analyzed the data. All authors contributed to
316 the manuscript, read, and approved the submitted version.

317 References

- 318 Abràmoff, Michael D, Paulo J Magalhães, and Sunanda J Ram. 2004. "Image processing with ImageJ."
319 *Biophotonics international* 11 (7):36-42.
- 320 Chinchoy, Edward, Charles L Soule, Andrew J Houlton, William J Gallagher, Mark A Hjelle, Timothy
321 G Laske, Josée Morissette, and Paul A Iaizzo. 2000. "Isolated four-chamber working swine
322 heart model." *The Annals of thoracic surgery* 70 (5):1607-1614.
- 323 Christie, GW. 1992. "Anatomy of aortic heart valve leaflets: the influence of glutaraldehyde fixation
324 on function." *European journal of cardio-thoracic surgery* 6 (Supplement_1):S25-S33.
- 325 Dumont, K., J. M. A. Stijnen, J. Vierendeels, F. N. van de Vosse, and P. R. Verdonck. 2004. "Validation
326 of a Fluid–Structure Interaction Model of a Heart Valve using the Dynamic Mesh Method in
327 Fluent." *Computer Methods in Biomechanics and Biomedical Engineering* 7 (3):139-146. doi:
328 10.1080/10255840410001715222.
- 329 Feins, Richard H, Harold M Burkhart, John V Conte, Daniel N Coore, James I Fann, George L Hicks
330 Jr, Jonathan C Nesbitt, Paul S Ramphal, Sharon E Schiro, and K Robert Shen. 2017.
331 "Simulation-based training in cardiac surgery." *The Annals of thoracic surgery* 103 (1):312-
332 321.
- 333 Gehron, Johannes, Julian Zirbes, Markus Bongert, Stefan Schäfer, Martin Fiebich, Gabriele Krombach,
334 Andreas Böning, and Philippe Grieshaber. 2019. "Development and validation of a life-sized

- 335 mock circulatory loop of the human circulation for fluid-mechanical studies." *ASAIO Journal*
336 65 (8):788-797.
- 337 Gupta, Sweta K, Narayan C Mishra, and Archana Dhasmana. 2017. "Decellularization methods for
338 scaffold fabrication." In *Decellularized Scaffolds and Organogenesis*, 1-10. Springer.
- 339 Guyette, Jacques P, Sarah E Gilpin, Jonathan M Charest, Luis F Tapias, Xi Ren, and Harald C Ott.
340 2014. "Perfusion decellularization of whole organs." *Nature protocols* 9 (6):1451-1468.
- 341 James, H K, A W Chapman, G T R Pattison, D R Griffin, and J D Fisher. 2019. "Systematic review of
342 the current status of cadaveric simulation for surgical training." *British Journal of Surgery* 106
343 (13):1726-1734. doi: 10.1002/bjs.11325.
- 344 Kasimir, M-T, E Rieder, G Seebacher, G Silberhumer, E Wolner, G Weigel, and P Simon. 2003.
345 "Comparison of different decellularization procedures of porcine heart valves." *The*
346 *International journal of artificial organs* 26 (5):421-427.
- 347 Leopaldi, A. M., R. Vismara, M. Lemma, L. Valerio, M. Cervo, A. Mangini, M. Contino, A. Redaelli,
348 C. Antona, and G. B. Fiore. 2012. "In vitro hemodynamics and valve imaging in passive beating
349 hearts." *J Biomech* 45 (7):1133-9. doi: 10.1016/j.jbiomech.2012.02.007.
- 350 Liu, Jing, Huimin Jing, Yibo Qin, Binhan Li, Zhiting Sun, Deling Kong, Xigang Leng, and Zhihong
351 Wang. 2019. "Nongluteraldehyde fixation for off the shelf decellularized bovine pericardium
352 in anticalcification cardiac valve applications." *ACS Biomaterials Science & Engineering* 5
353 (3):1452-1461.
- 354 Luo, Yu, Dong Lou, Lie Ma, and Changyou Gao. 2019. "Optimizing detergent concentration and
355 processing time to balance the decellularization efficiency and properties of bioprosthetic heart
356 valves." *Journal of Biomedical Materials Research Part A* 107 (10):2235-2243.
- 357 Maghsoudlou, Panagiotis, Fanourios Georgiades, Athanasios Tyraskis, Giorgia Totonelli, Stavros P
358 Loukogeorgakis, Giuseppe Orlando, Panicos Shangaris, Peggy Lange, Jean-Marie Delalande,
359 and Alan J Burns. 2013. "Preservation of micro-architecture and angiogenic potential in a
360 pulmonary acellular matrix obtained using intermittent intra-tracheal flow of detergent
361 enzymatic treatment." *Biomaterials* 34 (28):6638-6648.
- 362 Maglio, S, C Park, S Tognarelli, A Menciassi, and ET Roche. 2021. "High fidelity physical organ
363 simulators: from artificial to bio hybrid solutions." *IEEE Transactions on Medical Robotics*
364 *and Bionics*.
- 365 Mchale, Jonathon, and Frank Fago. 2017. Beating heart controller and simulator. Google Patents.
- 366 Mittal, Rajat, Jung Hee Seo, Vijay Vedula, Young J Choi, Hang Liu, H Howie Huang, Saurabh Jain,
367 Laurent Younes, Theodore Abraham, and Richard T George. 2016. "Computational modeling
368 of cardiac hemodynamics: current status and future outlook." *Journal of Computational*
369 *Physics* 305:1065-1082.
- 370 Park, Clara, Yiling Fan, Gregor Hager, Hyunwoo Yuk, Manisha Singh, Allison Rojas, Aamir Hameed,
371 Mossab Saeed, Nikolay V Vasilyev, and Terry WJ Steele. 2020. "An organosynthetic dynamic
372 heart model with enhanced biomimicry guided by cardiac diffusion tensor imaging." *Science*
373 *robotics* 5 (38).
- 374 Ramphal, P. S., D. N. Coore, M. P. Craven, N. F. Forbes, S. M. Newman, A. A. Coye, S. G. Little, and
375 B. C. Silvera. 2005. "A high fidelity tissue-based cardiac surgical simulator." *Eur J*
376 *Cardiothorac Surg* 27 (5):910-6. doi: 10.1016/j.ejcts.2004.12.049.

- 377 Sacks, Michael S, and Jun Liao. 2018. *Advances in Heart Valve Biomechanics: Valvular Physiology,*
378 *Mechanobiology, and Bioengineering*: Springer.
- 379 Singh, Manisha, Claudia E Varela, William Whyte, Markus A Horvath, Nigel CS Tan, Chee Bing Ong,
380 Patric Liang, Marc L Schermerhorn, Ellen T Roche, and Terry WJ Steele. 2021. "Minimally
381 invasive electroceutical catheter for endoluminal defect sealing." *Science Advances* 7
382 (14):eabf6855.
- 383 Talman, E. A., and D. R. Boughner. 1995. "Glutaraldehyde fixation alters the internal shear properties
384 of porcine aortic heart valve tissue." *Ann Thorac Surg* 60 (2 Suppl):S369-73. doi:
385 10.1016/0003-4975(95)00250-o.
- 386 Taylor, Charles E, and Gerald E Miller. 2012. "Mock circulatory loop compliance chamber employing
387 a novel real-time control process." *Journal of medical devices* 6 (4).
- 388 Timms, D., M. Hayne, K. McNeil, and A. Galbraith. 2005. "A complete mock circulation loop for the
389 evaluation of left, right, and biventricular assist devices." *Artif Organs* 29 (7):564-72. doi:
390 10.1111/j.1525-1594.2005.29094.x.
- 391 Urbani, Luca, Panagiotis Maghsoudlou, Anna Milan, Maria Menikou, Charlotte Klara Hagen, Giorgia
392 Totonelli, Carlotta Camilli, Simon Eaton, Alan Burns, and Alessandro Olivo. 2017. "Long-term
393 cryopreservation of decellularised oesophagi for tissue engineering clinical application." *PloS*
394 *one* 12 (6):e0179341.
- 395 Villanueva, Claudia, Jess Xiong, and Siddharth Rajput. 2020. "Simulation-based surgical education in
396 cardiothoracic training." *ANZ journal of surgery* 90 (6):978-983.
- 397 Vismara, R., A. M. Leopaldi, M. Piola, C. Asselta, M. Lemma, C. Antona, A. Redaelli, F. van de
398 Vosse, M. Rutten, and G. B. Fiore. 2016. "In vitro assessment of mitral valve function in
399 cyclically pressurized porcine hearts." *Med Eng Phys* 38 (4):346-53. doi:
400 10.1016/j.medengphy.2016.01.007.
- 401 Wu, Z. J., B. Z. Gao, J. H. Slonin, and N. H. Hwang. 1996. "Bileaflet mechanical heart valves at low
402 cardiac output." *Asaio j* 42 (5):M747-9. doi: 10.1097/00002480-199609000-00088.
- 403 Zhou, Jianye, Olaf Fritze, Martina Schleicher, Hans-Peter Wendel, Katja Schenke-Layland, Csaba
404 Harasztosi, Shengshou Hu, and Ulrich A Stock. 2010. "Impact of heart valve decellularization
405 on 3-D ultrastructure, immunogenicity and thrombogenicity." *Biomaterials* 31 (9):2549-2554.

406 Figure captions

407 **Figure 1.** Overall scheme and study design. (A) Porcine aortic valves are explanted and either
408 chemically crosslinked with fixative Formaldehyde (fixed), or decellularized with surfactants Triton
409 X-100/ sodium deoxycholate (decel) or treated with a combination of fixative and surfactants (fixed-
410 decel) to optimize the biomechanical properties. Digital photos of the cut leaflets show that decel and
411 fixed-decel groups were discolored due to the removal of cell and related membrane proteins by the
412 surfactants. Fixed leaflets appear to be distorted in shape relative to the native valve and the original
413 shape was recovered when fixed leaflets were decellularized (fixed-decel). (B) Digital pictures and a
414 cross-section schematic of an aortic valve showing composition and orientation of collagen and elastin
415 fibers in different layers during systole and diastole. (C) Fourier Transform Infrared Spectroscopy
416 (FTIR) spectra indicate the peak intensity and location of characteristic chemical groups.

417 **Figure 2.** Surface characterization using scanning electron microscopy (SEM). (A-D) SEM
418 micrographs showing the morphology of leaflets from the surface. (E-H) Micrographs showing cross-

sectional morphology of leaflets that have been fixed, decellularized, and a combination thereof including the native control. The scale bar is 10 μ m for all.

Figure 3. Evaluation of mechanical properties. (A) Set up of uniaxial tensile test performed in the radial direction. (B) Comparison of leaflet thickness and maximum stress at failure (C) Comparison of elastic modulus (i.e., stiffness) and maximum strain at failure. (D) two-dimensional comparison (Elastic modulus vs. ultimate stress at break) of mechanical properties among fixed, decellularized, and a combination thereof, including the native control groups. Data presented as mean $\pm$ Std Dev, n = 3, p-values are calculated using one-way ANOVA with Tukey correction, *p < 0.05 in Origin Pro 2019 (64-bit); ns denotes no statistical difference.)

Figure 4. Hydrodynamic assessment. (A) Custom-built benchtop setup with a pulsatile mock circulatory loop representing left heart circulation. (B-C) Representative pressure and flow waveforms for native aortic valves at 60 bpm and cardiac output of 3.6 L/min. (D) Representative transvalvular pressure gradients for native valves over a few cardiac cycles. (E) Digital images were captured using an endoscope camera for different groups of aortic valves at peak systole and diastole. (F) Comparison of mean transvalvular pressure gradients (Δ P) among fixed, decellularized, and a combination thereof, including the native and commercially available mechanical (St. Jude) control groups. (G) Comparison of regurgitant flow and opening orifice area at peak systole. Data presented as mean $\pm$ Std Dev, p-values are calculated using one-way ANOVA with Tukey correction, *p < 0.05 in Origin Pro 2019 (64-bit), ns denotes no statistical difference.