

Superconductivity in Li-B-C system at 100 GPa

Feng Zheng¹, Yang Sun^{1,2,3*}, Renhai Wang⁴, Yimei Fang¹, Feng Zhang^{2,5}, Shunqing Wu^{1†},
Cai-Zhuang Wang^{2,5}, Vladimir Antropov^{2,5}, Kai-Ming Ho²

¹*Department of Physics, OSED, Key Laboratory of Low Dimensional Condensed Matter
Physics (Department of Education of Fujian Province), Jiujiang Research Institute, Xiamen
University, Xiamen 361005, China.*

²*Department of Physics, Iowa State University, Ames, Iowa 50011, United States*

³*Department of Applied Physics and Applied Mathematics, Columbia University, New York,
NY, 10027, USA*

⁴*School of Physics and Optoelectronic Engineering, Guangdong University of Technology,
Guangzhou 510006, China*

⁵*Ames Laboratory, U.S. Department of Energy, Ames, Iowa 50011, USA*

Abstract

Layer Li-B-C compounds have been shown to have feasible superconductivity. Using the adaptive genetic algorithm, we predict the structures of the Li-B-C system at 100 GPa. We identify several low-enthalpy metallic phases with stoichiometries of LiB₂C, LiB₃C, Li₂BC₂, Li₃B₂C₃, Li₃BC, and Li₅BC. Using a fast screening method of electron-phonon interaction, we find that LiB₃C is a promising candidate for superconductivity. The consecutive calculations using the full Brillouin zone confirm the existence of the strong electron-phonon coupling in this system. The anharmonic B-C phonon modes near the zone center provide the major contribution to the electron-phonon coupling. The electron-phonon coupling constant is 1.40, and the estimated critical temperature is 22 K. Our study indicates superconductivity can also happen without a layered structural motif in the Li-B-C system. It also demonstrates an effective strategy for crystal structure prediction of superconducting materials.

*yangsun@iastate.edu

†wsq@xmu.edu.cn

1. Introduction

Exploring high-temperature superconductors is an important research goal in physics, chemistry, and material science. Inspired by the discovery of a superconducting transition around 40 K in the rather simple MgB_2 compound [1-3], extensive research has been conducted on its related materials [4-9] (graphitelike layered materials intercalated with alkali or alkali-earth) to obtain new possible superconductors. Among them, graphitelike layered Li-B-C compounds have been the subject of sustained interest, because these structures with light elements may have strong covalent bonding and significant phonon frequencies, underling high- T_c (conventional) superconductivity [10, 11]. LiBC with $P6_3/mmc$ symmetry [12, 13] has a similar crystal structure to MgB_2 . However, unlike MgB_2 , LiBC exhibits an insulating nature [13]. According to Bardeen-Cooper-Schrieffer (BCS) theory [14], metallicity is an important requirement for a conventional superconductor. Therefore, to achieve superconductivity in LiBC, Rosner *et al.* suggested metalizing LiBC by introducing vacancies at Li sites [15]. Based on the DFT calculations, they found that $\text{Li}_{0.5}\text{BC}$ becomes superconducting at about 100 K. However, no experimental efforts have reported superconductivity of the Li-deficient LiBC compounds above 2 K [16-19]. Further research shows that the absence of superconductivity of Li_xBC can be attributed to structural instability in the B-C layer at low Li deficiency, which leads to a dramatic change in electronic structure [20]. Considering that hole doping by introducing Li vacancies will cause structural instability in Li_xBC , Gao *et al.* designed a freestanding LiB_2C_2 trilayer [5]. Due to no vacancies involved in trilayer LiB_2C_2 , the structural distortion in the B-C layer may be prevented. And first-principles calculations predict that this trilayer LiB_2C_2 is a superconductor with T_c about 92 K. Furthermore, partially replacing carbons with borons in LiBC-type compounds was also proposed, such as $\text{LiB}_{1.1}\text{C}_{0.9}$ [21], $\text{Li}_3\text{B}_4\text{C}_2$ [22], $\text{Li}_2\text{B}_3\text{C}$ [22] and $\text{Li}_4\text{B}_5\text{C}_3$ [7], which have all been predicted to be superconductors. More recently, Quan *et al.* reported the superconductivity in the honeycomb structure $\text{Li}_{2x}\text{BC}_3$ at $x = 0.5$ by the theoretical calculations [23]. The calculated superconducting critical temperature T_c is comparable

to that in MgB_2 . These results show that the design of stoichiometric constituents of graphitelike layered Li-B-C compounds provides a feasible route to induce superconductivity.

So far, most attention has been focused on elucidating the nature of superconductivity of Li-B-C compounds with a graphitelike layered structure. A natural question remains whether there is any other Li-B-C structure that can lead to superconductivity. To answer this question, a comprehensive investigation of the crystal structures and superconductivity of the Li-B-C system should be carried out. These studies can help establish correlations of structural stability and superconducting properties with different structural motifs in the Li-B-C system, which, in turn, can be used to guide other researchers to reveal more promising superconductors. On the other hand, it has been shown that high pressure offers another effective strategy for identifying structural motifs for superconductivity [24-27]. Because high pressure conditions can enhance the interatomic interaction, tune electronic properties, and metalize materials. Furthermore, the application of pressure also can access unusual chemistry and stable structures that cannot be realized under ambient conditions [28], which may raise the possibility of finding superconducting materials. Therefore, in this paper, we investigate the structural and superconducting properties of the Li-B-C system at 100 GPa with crystal structure predictions. We employ a recently developed frozen-phonon method of electron-phonon coupling calculations [29] to fast screen possible Li-B-C superconductors.

2. Computational methods

The crystal structures of B-C, Li-C, and Li-B-C at 100 GPa were determined by using the adaptive genetic algorithm (AGA) method [30], which combines fast structure exploration by auxiliary classical potentials and accurate *ab initio* calculations adaptively and iteratively. In the GA-loop, the initial atomic position of the Li, B and C atoms were randomly generated without any assumption on the Bravais lattice type, symmetry, atom basis, or unit cell dimensions. The total structure pool in our GA search was set to 128. The structure search with auxiliary interatomic potentials was performed

in 400 consecutive GA generations. Then, the 16 lowest-enthalpy structures at the end of each GA search were selected for single-point DFT calculations according to the AGA procedure [30], whose energies, force, and stress are used to adjust the interatomic potential parameters for the next iteration of GA search. A total of 40 adaptive iterations were performed to obtain the final structures.

Here, the embedded-atom method (EAM) [31] was used as classical auxiliary potential. In EAM, the total energy of an N -atom system was evaluated by

$$E_{total} = \frac{1}{2} \sum_{i,j(i \neq j)}^N \phi(r_{ij}) + \sum_i F_i(n_i), \quad (1)$$

where $\phi(r_{ij})$ denotes the pair repulsion between atoms i and j with a distance of r_{ij} , $F_i(n_i)$ is the embedded term with electron density term $n_i = \sum_{j \neq i} \rho_j(r_{ij})$ at the site occupied by atom i . The potential fitting is performed by the force-matching method with a stochastic simulated annealing algorithm as implemented in the POTFIT code [32, 33].

The first-principles calculations were performed by using the projector-augmented wave (PAW) [34] representations with density functional theory as implemented in the Vienna *ab initio* simulation package (VASP) [35, 36]. The exchange and correlation energy was treated within the spin-polarized generalized gradient approximation (GGA) and parameterized by Perdew-Burke-Ernzerhof (PBE) formula [37]. Wave functions were expanded in plane waves up to a kinetic energy cutoff of 520 eV. Brillouin-zone integrations were approximated using special k -point sampling of the Monkhorst-Pack scheme [38] with a k -point mesh resolution of $2\pi \times 0.03 \text{\AA}^{-1}$. Lattice vectors and atomic coordinates were fully relaxed until the force on each atom was less than $0.01 \text{ eV} \cdot \text{\AA}^{-1}$. The fast screening of electron-phonon coupling (EPC) constant λ_{Γ} at the Brillouin zone center was carried out based on the frozen-phonon method [29]. The zone-center phonon was computed by the PHONOPY software [39, 40], with a finer k -point sampling grid of $2\pi \times 0.02 \text{\AA}^{-1}$ spacing and a criterion of self-consistent calculation 10^{-8} eV .

The full Brillouin-zone EPC calculation were performed with the Quantum ESPRESSO (QE) code [41, 42] based on density-functional perturbation theory

(DFPT) [43]. The ultra-soft pseudopotentials from the PSLibrary1.0.0 (high accuracy) [44] for PBE functional were used, with $2s^1$, $2s^22p^1$, and $2s^22p^2$ as valence electrons of Li, B, and C, respectively. The kinetic energy cutoffs were 75 Ry for wave functions and 576 Ry for potentials. The charge densities were determined on a k mesh of $24 \times 24 \times 24$. The dynamical matrices were calculated on a q mesh of $6 \times 6 \times 6$. The convergence threshold for self-consistency was 1×10^{-12} Ry.

The calculations of superconducting T_c are based on the Eliashberg spectral equation $\alpha^2F(\omega)$ [45, 46] defined commonly now as

$$\alpha^2F(\omega) = \frac{1}{2\pi N(E_f)} \sum_{qv} \frac{\gamma_{qv}}{\hbar\omega_{qv}} \delta(\omega - \omega_{q,v}), \quad (2)$$

where $N(E_f)$ is the density of states at the Fermi level, ω_{qv} denotes the phonon frequency of the mode v with wave vector $\mathbf{q}$. γ_{qv} is the phonon linewidth defined as

$$\gamma_{qv} = \frac{2\pi\omega_{qv}}{\Omega_{BZ}} \sum_{ij} \int d^3k |g_{k,qv}^{ij}|^2 \delta(\epsilon_{q,i} - E_f) \delta(\epsilon_{k+q,j} - E_f), \quad (3)$$

where $\epsilon_{q,i}$ and $\epsilon_{k+q,j}$ are eigenvalues of Kohn-Sham orbitals at given bands and vectors. $\mathbf{q}$ and $\mathbf{k}$ are wave vectors, and i and j denote indices of energy bands. $g_{k,qv}^{ij}$ is the EPC matrix element, which describes the probability amplitude for the scattering of an electron with a transfer of crystal momentum $\mathbf{q}$, determined by

$$g_{k,qv}^{ij} = \left(\frac{\hbar}{2M\omega_{qv}}\right)^{1/2} \left\langle \Psi_{i,k} \left| \frac{dV_{SCF}}{d\hat{\mu}_{qv}} \cdot \hat{e}_{qv} \right| \Psi_{i,k+q} \right\rangle, \quad (4)$$

where M is the atomic mass, $\hat{e}_{qv}$ is the phonon eigenvector. $dV_{SCF}/d\hat{\mu}_{qv}$ measures the change of self-consistent potential induced by atomic displacement. $\Psi_{i,k}$ and $\Psi_{i,k+q}$ are Kohn-Sham orbitals. The EPC constant λ can be determined through summation over the first Brillouin zone or integration of the spectral function in frequency space,

$$\lambda = \sum_{qv} \lambda_{qv} = 2 \int \frac{\alpha^2F(\omega)}{\omega} d\omega, \quad (5)$$

where the EPC constant λ_{qv} for mode v at wave vector $\mathbf{q}$ using Eq. (5) can be written as

$$\lambda_{qv} = \frac{\gamma_{qv}}{\pi\hbar N(E_f)\omega_{qv}^2}. \quad (6)$$

The superconducting T_c is determined with the analytical McMillan equation modified by the Allen-Dynes formula [47, 48],

$$T_c = \frac{\omega_{log}}{1.2} \exp\left[\frac{-1.04(1+\lambda)}{\lambda(1-0.62\mu^*)-\mu^*}\right], \quad (7)$$

where μ^* is the effective screened Coulomb repulsion constant whose values is generally between 0.1 and 0.15 [49, 50], and ω_{log} is the logarithmic average frequency

$$\omega_{log} = \exp\left[\frac{2}{\lambda} \int \frac{d\omega}{\omega} \alpha^2 F(\omega) \log \omega\right]. \quad (8)$$

3. Results and discussion

3.1 AGA search of Li-B-C ternary phases at 100 GPa

Before we discuss ternary compounds in the Li-B-C system, the structural stability of elements and binary phases should be first clarified. At 100 GPa, calculations show that the ground-state phases of elemental Li, B and C adopt the *Pbca* [51, 52], *Cmca* (α -Ga structure) [53] and *Fd $\bar{3}m$* (diamond) [54] symmetry, respectively. For the Li-B binary phase, because previous crystal structure searches [55, 56] have already covered the current study's pressure, we did not perform additional structure searches of Li-B compounds. We re-calculated the enthalpies of these crystal structures. Our results show that five compounds with Li_6B (*R $\bar{3}$*), Li_2B (*Cmcm*), Li_3B_2 (*R $\bar{3}m$*), LiB (*Fd $\bar{3}m$*) and LiB_4 (*I4/mmm*) are stable at 100 GPa. For the B-C compounds, Jay *et al* investigated from ambient pressure to 80 GPa [57]. We performed the AGA search at 100 GPa and found no B-C binary compound was stable at 100 GPa, similar to Jay *et al.*'s high-pressure results [57]. For the Li-C system, our AGA searches indicate that Li_4C (*P2 $_1$ /c*), Li_8C_3 (*R $\bar{3}m$*) and Li_2C_3 (*Cmcm*) compounds are the ground-state phases at 100 GPa. More details of AGA searches in B-C and Li-C systems can be found in Supplemental Material [58]. The stable crystal structures of these elements and binary phases are shown in Figure S3 of the Supplemental Material [58] and their structural parameters are listed in Supplementary Table S1 [58].

In Figure 1, we present ternary compounds of Li-B-C at 100 GPa from the AGA searches. For simplicity, all chemical formulae are expressed as Li/B/C reduced ratios. For example, 111 represents the compound with LiBC . During the structural search, we select a range of different stoichiometries (i.e., 111, 112, 121, 211, 113, 122, 131, 212,

221, 311, 114, 123, 132, 141, 213, 231, 312, 321, 411, 115, 124, 133, 142, 151, 214,
 223, 232, 241, 313, 322, 331, 412, 421, 511, 116, 125, 134, 143, 152, 161, 215, 233,
 251, 314, 323, 332, 341, 413, 431, 512, 521 and 611) with 2 or 4 formula units to
 perform the AGA search. The relative stability of these predicted Li-B-C compounds
 was investigated under the corresponding pressure, depending on the calculated
 formation enthalpies,

$$H_f = \frac{H(\text{Li}_x\text{B}_y\text{C}_z) - xH(\text{Li}) - yH(\text{B}) - zH(\text{C})}{x+y+z} \quad (9)$$

where $H(\text{Li}_x\text{B}_y\text{C}_z)$ is the total enthalpy of the $\text{Li}_x\text{B}_y\text{C}_z$ compound. $H(\text{Li})$, $H(\text{B})$ and $H(\text{C})$ are the enthalpy of the ground state of Li, B and C at 100 GPa. Here, H_d is introduced as the enthalpy above the convex hull to represent the relative stability on the phase diagram. Ground-state phases have $H_d = 0$.




Figure 1. The convex hull of the Li-B-C system at 100 GPa.

As shown in Figure 1, LiBC is the only ternary ground-state compound at 100 GPa. The crystal structure is the same as the experimental structure of LiBC ($P6_3/mmc$ symmetry) determined by Woerle *et al.* at ambient pressure [12]. This indicates that the

ambient-pressure LiBC phase is stable up to 100 GPa, which agrees with previous studies [59]. Figure 2(a) shows the atomic structure of hexagonal LiBC at 100 GPa. This structure is the same as the MgB_2 with alternating graphene-like B-C and Li layers. The detailed structural parameters are listed in Supplementary Table S2 [58]. The calculated phonon spectrum confirms that this phase is dynamically stable at 100 GPa (Supplemental Material, Figure S4 (a) [58]). The electronic density of state (DOS) in Figure S4 (b) of the Supplemental Material [58] shows that LiBC is an insulating phase at 100 GPa.

Besides the ternary ground-state LiBC structure, we also identify a few low-enthalpy metastable structures with enthalpy very close to the convex hull ($H_d < 100$ meV/atom), namely LiB_2C , LiB_3C , Li_2BC_2 , $\text{Li}_3\text{B}_2\text{C}_3$, Li_3BC and Li_5BC . The H_d are so small that these compounds may be realized in experiments. We compute the Gibbs free energy of formation for one of the structures (LiB_3C) to examine the effect of temperature on structural stability with the quasiharmonic approximation. The results suggest that the temperature may improve the stability of LiB_3C (see Supplementary Note 2 [58]). The crystal structures of these Li-B-C compounds are shown in Figure 2(b)-(g). The LiB_2C in Figure 2(b) adopts the orthorhombic structure with $Cmcm$ symmetry. This structure is a 3D framework with PbO-type [60] layers of B_2 and C chains, separated by Li atoms, which is similar to $Cmcm$ CeNiSi_2 . The Cm LiB_3C also has a PbO-type layered motif of B_3C , and Li atoms locate between two PbO-type layers as shown in Figure 2(c). This structure is similar to the BaFe_2As_2 phase [61]. The Li_2BC_2 ($Pbam$) and $\text{Li}_3\text{B}_2\text{C}_3$ (Pm) in Figure 2(d)-(e) both have B-C layered structures with five- and eight-membered rings and five-, six- and eight-membered rings, respectively. The Cm Li_3BC (Figure 2(f)) is found to form B-C nanoribbons structure, while, for $P-1$ Li_5BC (Figure 2(g)), B and C atoms connect to form chains. The structural parameters of these phases are listed in Supplementary Table S2 [58]. Figure S5-S10 of the Supplemental Material [58] show the phonon dispersions, and DOS for these metastable Li-B-C phases. The results show that, unlike the insulating LiBC, these low-enthalpy Li-B-C compounds are metallic. Furthermore, phonon calculations confirm that these Li-B-C compounds are dynamic stability at 100 GPa. It should be

noted that the LiB_3C structure has minor imaginary frequencies near the Γ point (Supplemental Material, Figure S6(a) [58]). However, it does not mean the dynamical instability of this material. Since the phonon calculations are based on the harmonic approximation, the presence of imaginary phonon frequencies may also be associated with a strongly anharmonic effect, which will be discussed later.




Figure 2. Atomic structures of (a) $P6_3/mmc$ LiBC, (b) $Cmcm$ LiB₂C, (c) Cm LiB₃C, (d) $Pbam$ Li₂BC₂, (e) Pm Li₃B₂C₃, (f) Cm Li₃BC, and (g) $P-1$ Li₅BC at 100 GPa. The light green rectangle denotes PbO-type motifs.

3.2 Fast screening of superconductivity of Li-B-C compounds

Motivated by the metallic properties of these metastable Li-B-C compounds, we further investigated their superconductivity. To determine the phonon-mediated superconductivity, it is usually based on the calculations of electron-phonon coupling in the full Brillouin zone. However, these calculations are time-consuming, particularly

in complicated systems, which impedes the high-throughput superconducting material studies. Therefore we first employ a fast screening of these phases with the zone-center EPC strength λ_{Γ} based on the frozen phonon method [29]. Here, the λ_{Γ} can be defined by

$$\lambda_{\Gamma v} = \frac{\tilde{\omega}_{\Gamma v}^2 - \omega_{\Gamma v}^2}{4\omega_{\Gamma v}^2}, \quad (10)$$

where the $\omega_{\Gamma v}$ and $\tilde{\omega}_{\Gamma v}$ are screened and unscreened phonon frequencies of mode v at zone-center, respectively. Using this method, we find only LiB_3C has a high $\sum_v \lambda_{\Gamma v}$ (the summation of zone-center EPC of all modes) as shown in Figure 3(a). The high $\sum_v \lambda_{\Gamma v}$ of LiB_3C can be attributed to the large difference between screened and unscreened phonon frequencies of mode 4 and mode 5 as shown in Figure 3(b).




Figure 3. (a) The enthalpy above the convex hull (H_d) versus EPC constant $\sum_v \lambda_{\Gamma v}$ at the Brillouin zone center. (b) The screened and unscreened phonon frequency (top panel) and zone-center EPC strength (bottom panel) in LiB_3C phase at 100 GPa.

To further quantify the electron-phonon interaction in LiB_3C , we investigate its EPC with full Brillouin-zone calculations. Figure 4(a) shows the γ_{qv} -weighted phonon spectrum with DFPT calculations. Now one can see that phonon mode 4 and mode 5 have a large contribution to the phonon linewidth and correspondingly to the electron-

1 phonon interaction near the Γ point, which agrees well with the fast screening results.
 2 These two modes mainly involve vibrations of boron and carbon atoms as shown in
 3 Figure 4(b). Their vibrational configurations at the Γ point are shown in Figure 4(d)
 4 and Figure 4(e), respectively. Mode 4 corresponds to stretching vibrations of B2, B3,
 5 and C atoms in the a - b plane. And for mode 5, B2-B3 atoms and B1-C atoms both show
 6 symmetric stretching vibrations in the a - b plane. The calculated Eliashberg function
 7 $\alpha^2F(\omega)$ is shown in Figure 4(c). The integrated EPC parameter λ is 1.40. The $\omega_{\log}$ can
 8 be obtained from equation (8), which is 197.31 K. We predict $T_c = 22$ K ($\mu^* = 0.1$) for
 9 the LiB_3C . As a comparison, we also compute the full EPC for the LiB_2C phase with
 10 $Cmcm$ symmetry, which is not expected to show a strong EPC from zone-center EPC
 11 calculations. We obtain $\lambda = 0.37$ and $T_c = 3$ K ($\mu^* = 0.1$) for LiB_2C (see Figure S12 of
 12 the Supplemental Material [58]), indicating the accuracy of the zone-center EPC
 13 screening method.




Figure 4. (a) Phonon spectrum of LiB₃C. Red solid circles represent the phonon linewidth (γ_{qv}) with a radius proportional to the strength. (b) projected phonon DOS. (c) Eliashberg spectral function $\alpha^2F(\omega)$ with integrated EPC parameter $\lambda(\omega)$. The vibrational patterns for (d) mode 4 and (e) mode 5 at the Γ point.

3.3 Anharmonic effect of LiB₃C

As mentioned above, there are small imaginary phonon frequencies contributed in LiB₃C shown in Figure 4(a) and Figure S6(a) of the Supplemental Material [58]. Specifically, we find the frequency of mode 4 shows a strong dependence on the magnitude of displacement in the frozen phonon calculations. To further investigate this behavior, we calculated the energy changes as all atoms displaced along the eigenmodes of mode 4 at the Γ point in Figure 5. The displacement for atom i is $\mathbf{D}_i = u \frac{\mathbf{v}_i}{\sqrt{m_i}}$, where u is the displacement amplitude, $\mathbf{v}_i$ is the eigenvector, m_i is the atomic mass. To compare, we also plot mode 8, which is a harmonic mode mainly contributed by the Li vibration. Compared to the harmonic mode, the potential well of mode 4 is very flat at small displacement and increases rapidly at large displacement. It can only be fit to $E(u) = A_2u^2 + A_4u^4$ with a vanishing A_2 and a large A_4 as shown in Figure 5(a). This indicates that mode 4 has unusually large anharmonicity and the conventional harmonic phonon calculations are in a nonperturbative regime. Therefore, the current harmonic energy, 1.10 THz or 4.56 meV, should be much lower than the actual energy. The correct treatment of anharmonic effects on superconductivity can be complicated. But such large anharmonicity has been seen previously and its influence on EPC and T_c has also been discussed in the literature [62, 63]. The EPC constant λ can be expected in general to be somewhat smaller. However, the influence of this change on T_c is not unique due to the significant increase of $\omega_{\log}$ when the anharmonicity is included. Due to such cancellation effects, different formulas can produce the increase or decrease of T_c , however overall this effect seems to be small [62]. The phonon dispersions of LiB₃C are also computed at 0 GPa and 50 GPa (see Figure S13 in the Supplemental Material

[58]). No negative frequency is found, suggesting that LiB₃C is dynamically stable at low pressures.




Figure 5. Frozen-phonon calculation of the total energy change as a function of atomic displacement for two zone-center modes. (a) The anharmonic mode 4 and (b) harmonic mode 8. The red curve shows the fitting.

4. Conclusions

In summary, we use the AGA method to study the Li-B-C system at 100 GPa. We identify several low-enthalpy metallic phases with stoichiometries of LiB₂C, LiB₃C, Li₂BC₂, Li₃B₂C₃, Li₃BC, and Li₅BC. By a fast evaluation of zone-center electron-phonon interactions in these metallic Li-B-C structures, we identify that LiB₃C can be a promising candidate for superconductivity. The calculations of EPC in the full Brillouin and analysis with Eliashberg function $\alpha^2 F(\omega)$ verify the superconductivity of LiB₃C with EPC constant $\lambda = 1.40$ and $T_c = 22$ K. The electron-phonon interactions are mainly contributed by low-frequency anharmonic phonon modes involving vibrations of boron and carbon atoms. Our results indicate rich structural motifs in the Li-B-C system at high pressure, and the superconductivity in this system can happen in the

phases without layered structure. This work also demonstrates an effective strategy to combine crystal structure prediction and fast screening for conventional superconductors that can be used in many other systems.

Acknowledgments

Work at Xiamen University was supported by the National Natural Science Foundation of China (11874307). R. Wang was supported by the Guangdong Basic and Applied Basic Research Foundation (Grant No. 2021A1515110328 & 2022A1515012174). Y. Sun and V. Antropov were supported by National Science Foundation Awards No. DMR-2132666. C.Z. Wang and F. Zhang were supported by the U.S. Department of Energy (DOE), Office of Science, Basic Energy Sciences, Materials Science and Engineering Division. Ames Laboratory is operated for the U.S. DOE by Iowa State University under Contract No. DE-AC02-07CH11358, including the grant of computer time at the National Energy Research Supercomputing Center (NERSC) in Berkeley.

References

- [1] J. Nagamatsu, N. Nakagawa, T. Muranaka, Y. Zenitani, J. Akimitsu, *Nature*, **410**, 63 (2001).
- [2] Y. Kong, O.V. Dolgov, O. Jepsen, O.K. Andersen, *Phys Rev B*, **64**, 020501 (2001).
- [3] T. Yildirim, O. Gulseren, J.W. Lynn, C.M. Brown, T.J. Udovic, Q. Huang, N. Rogado, K.A. Regan, M.A. Hayward, J.S. Slusky, et al., *Phys Rev Lett*, **87**, 037001 (2001).
- [4] N. Emery, C. Herold, M. d'Astuto, V. Garcia, C. Bellin, J.F. Mareche, P. Lagrange, G. Louprias, *Phys Rev Lett*, **95**, 087003 (2005).
- [5] M. Gao, X.-W. Yan, Z.-Y. Lu, T. Xiang, *Phys Rev B*, **101**, 094501 (2020).
- [6] E. Haque, M.A. Hossain, C. Stampfl, *Phys Chem Chem Phys*, **21**, 8767 (2019).
- [7] T. Bazhironov, Y. Sakai, S. Saito, M.L. Cohen, *Physical Review B*, **89**, 045136 (2014).
- [8] T.E. Weller, M. Ellerby, S.S. Saxena, R.P. Smith, N.T. Skipper, *Nature Physics*, **1**, 39 (2005).
- [9] W. Hayami, T. Tanaka, *Aip Advances*, **10**, 065213 (2020).
- [10] J.M. An, W.E. Pickett, *Phys Rev Lett*, **86**, 4366 (2001).
- [11] S. Di Cataldo, S. Qulaghasi, G.B. Bachelet, L. Boeri, *Phys Rev B*, **105**, 064516 (2022).
- [12] M. Worle, R. Nesper, G. Mair, M. Schwarz, H.G. Vonschnering, *Z Anorg Allg Chem*, **621**, 1153 (1995).
- [13] P.F. Karimov, N.A. Skorikov, E.Z. Kurmaev, L.D. Finkelstein, S. Leitch, J. MacNaughton, A. Moewes, T. Mori, *J Phys-Condens Mat*, **16**, 5137 (2004).
- [14] J. Bardeen, L.N. Cooper, J.R. Schrieffer, *Physical Review*, **108**, 1175 (1957).
- [15] H. Rosner, A. Kitaigorodsky, W.E. Pickett, *Physical Review Letters*, **88**, 127001 (2002).

-
- 1 [16] A. Bharathi, S.J. Balaselvi, M. Premila, T.N. Sairam, G.L.N. Reddy, C.S. Sundar, Y. Hariharan,
 - 2 Solid State Commun, **124**, 423 (2002).
 - 3 [17] D. Souptel, Z. Hossain, G. Behr, W. Loser, C. Geibel, Solid State Commun, **125**, 17 (2003).
 - 4 [18] A.M. Fogg, P.R. Chalker, J.B. Claridge, G.R. Darling, M.J. Rosseinsky, Phys Rev B, **67**, 245106
 - 5 (2003).
 - 6 [19] A.M. Fogg, J.B. Claridge, G.R. Darling, M.J. Rosseinsky, Chem Commun, **12**, 1348 (2003).
 - 7 [20] A.M. Fogg, J. Meldrum, G.R. Darling, J.B. Claridge, M.J. Rosseinsky, J Am Chem Soc, **128**,
 - 8 10043 (2006).
 - 9 [21] R. Miao, J. Yang, M. Jiang, Q. Zhang, D. Cai, C. Fan, Z. Bai, C. Liu, F. Wu, S. Ma, Journal of
 - 10 Applied Physics, **113**, 133910 (2013).
 - 11 [22] M. Gao, Z.Y. Lu, T. Xiang, Phys Rev B, **91**, 045132 (2015).
 - 12 [23] Y. Quan, W.E. Pickett, Phys Rev B, **102**, 144504 (2020).
 - 13 [24] A.P. Drozdov, P.P. Kong, V.S. Minkov, S.P. Besedin, M.A. Kuzovnikov, S. Mozaffari, L. Balicas,
 - 14 F.F. Balakirev, D.E. Graf, V.B. Prakapenka, et al., Nature, **569**, 528 (2019).
 - 15 [25] A.P. Drozdov, M.I. Eremets, I.A. Troyan, V. Ksenofontov, S.I. Shylin, Nature, **525**, 73 (2015).
 - 16 [26] M. Somayazulu, M. Ahart, A.K. Mishra, Z.M. Geballe, M. Baldini, Y. Meng, V.V. Struzhkin, R.J.
 - 17 Hemley, Physical Review Letters, **122**, 027001 (2019).
 - 18 [27] E. Snider, N. Dasenbrock-Gammon, R. McBride, X. Wang, N. Meyers, K.V. Lawler, E. Zurek, A.
 - 19 Salamat, R.P. Dias, Phys Rev Lett, **126**, 117003 (2021).
 - 20 [28] H.K. Mao, X.J. Chen, Y. Ding, B. Li, L. Wang, Rev Mod Phys, **90**, 015007 (2018).
 - 21 [29] Y. Sun, F. Zhang, C.-Z. Wang, K.-M. Ho, I.I. Mazin, V. Antropov, Physical Review Materials, **6**,
 - 22 074801 (2022).
 - 23 [30] S.Q. Wu, M. Ji, C.Z. Wang, M.C. Nguyen, X. Zhao, K. Umemoto, R.M. Wentzcovitch, K.M. Ho,
 - 24 J Phys Condens Matter, **26**, 035402 (2014).
 - 25 [31] S.M. Foiles, M.I. Baskes, M.S. Daw, Phys Rev B Condens Matter, **33**, 7983 (1986).
 - 26 [32] P. Brommer, F. Gahler, Philos Mag, **86**, 753 (2006).
 - 27 [33] P. Brommer, F. Gahler, Model Simul Mater Sc, **15**, 295 (2007).
 - 28 [34] G. Kresse, D. Joubert, Physical Review B, **59**, 1758 (1999).
 - 29 [35] G. Kresse, J. Furthmuller, Phys Rev B, **54**, 11169 (1996).
 - 30 [36] G. Kresse, J. Furthmuller, Comp Mater Sci, **6**, 15 (1996).
 - 31 [37] J.P. Perdew, K. Burke, M. Ernzerhof, Phys Rev Lett, **77**, 3865 (1996).
 - 32 [38] S. Froyen, Phys Rev B Condens Matter, **39**, 3168 (1989).
 - 33 [39] A. Togo, F. Oba, I. Tanaka, Physical Review B, **78**, 134106 (2008).
 - 34 [40] A. Togo, I. Tanaka, Scripta Mater, **108**, 1 (2015).
 - 35 [41] P. Giannozzi, S. Baroni, N. Bonini, M. Calandra, R. Car, C. Cavazzoni, D. Ceresoli, G.L.
 - 36 Chiarotti, M. Cococcioni, I. Dabo, et al., J Phys Condens Matter, **21**, 395502 (2009).
 - 37 [42] P. Giannozzi, O. Andreussi, T. Brumme, O. Bunau, M.B. Nardelli, M. Calandra, R. Car, C.
 - 38 Cavazzoni, D. Ceresoli, M. Cococcioni, et al., J Phys-Condens Mat, **29**, 465901 (2017).
 - 39 [43] S. Baroni, S. de Gironcoli, A. Dal Corso, P. Giannozzi, Rev Mod Phys, **73**, 515 (2001).
 - 40 [44] A. Dal Corso, Comp Mater Sci, **95**, 337 (2014).
 - 41 [45] G.M. Eliashberg, Sov. Phys. JETP, **11**, 696 (1960).
 - 42 [46] G.M. Eliashberg, Sov. Phys. JETP, **12**, 1000 (1961).
 - 43 [47] P.B. Allen, Phys Rev B, **6**, 2577 (1972).
 - 44 [48] P.B. Allen, R.C. Dynes, Phys Rev B, **12**, 905 (1975).

-
- 1 [49] C.F. Richardson, N.W. Ashcroft, Phys Rev Lett, **78**, 118 (1997).
2 [50] K.H. Lee, K.J. Chang, M.L. Cohen, Phys Rev B Condens Matter, **52**, 1425 (1995).
3 [51] J. Lv, Y. Wang, L. Zhu, Y. Ma, Phys Rev Lett, **106**, 015503 (2011).
4 [52] C.J. Pickard, R.J. Needs, Phys Rev Lett, **102**, 146401 (2009).
5 [53] A.R. Oganov, J.H. Chen, C. Gatti, Y.Z. Ma, Y.M. Ma, C.W. Glass, Z.X. Liu, T. Yu, O.O.
6 Kurakevych, V.L. Solozhenko, Nature, **457**, 863 (2009).
7 [54] T. Yamanaka, S. Morimoto, Acta Crystallogr B, **52**, 232 (1996).
8 [55] F. Peng, M. Miao, H. Wang, Q. Li, Y. Ma, J Am Chem Soc, **134**, 18599 (2012).
9 [56] A. Hermann, A. McSorley, N.W. Ashcroft, R. Hoffmann, J Am Chem Soc, **134**, 18606 (2012).
10 [57] A. Jay, O.H. Duparc, J. Sjakste, N. Vast, Journal of Applied Physics, **125**, 185902 (2019).
11 [58] See Supplemental Material at <http://link.aps.org/supplemental/10.1103/PhysRevB.xx.xxxxxx> for
12 the AGA search of B-C and Li-C systems at 100 GPa, the effect of temperature on the structural stability
13 of LiB₃C, crystallographic data of stable and metastable phases, phonon spectra, the density of states and
14 Eliashberg spectral function.
15 [59] M.G. Zhang, Europhys. Lett, **114**, 16001 (2016).
16 [60] D.E. Bugaris, M. Sturza, F. Han, J. Im, D.Y. Chung, A.J. Freeman, M.G. Kanatzidis, European
17 Journal of Inorganic Chemistry, **2015**, 2164 (2015).
18 [61] F. Rullier-Albenque, D. Colson, A. Forget, P. Thuéry, S. Poissonnet, Phys Rev B, **81**, 224503
19 (2010).
20 [62] M. Dogan, S. Oh, M.L. Cohen, Phys Rev B, **105**, L020509 (2022).
21 [63] A.M. Shipley, M.J. Hutcheon, R.J. Needs, C.J. Pickard, Physical Review B, **104**, 054501 (2021).
22