

Educational Series: Turning Monomers into Crosslinked Polymer Networks

M. A. Sachini N. Weerasinghe,^a Obed J. Dodo,^a Chamoni W. H. Rajawasam,^a Ibrahim O. Raji,^a Shiwanka V, Wanasinghe,^a Dominik Konkolewicz^{a,*}, Nethmi De Alwis Watuthanthrige^{b,*}

- a. Department of Chemistry and Biochemistry, Miami University, 651 E High St, Oxford, OH, 45056, United States
- b. Laboratory of Polymeric Materials, Department of Materials, ETH Zurich, Vladimir-Prelog-Weg 5, Zurich 8093, Switzerland

*Correspondence:

DK: d.konkolewicz@miamiOH.edu


NDAW: nethmi.dealwis@mat.ethz.ch

Abstract

Multifunctional monomers enable the synthesis of polymer networks by adapting the polymerization methods used for conventional linear polymer synthesis. Both step and chain polymerization methods can be combined with multifunctional monomers to generate networks with essentially infinite molecular weight. Traditional networks are held together through covalent crosslinks that derive from the multifunctional monomers. Additional approaches to network like materials involve polymer phase separation, forming non-covalent crosslink-points. This contribution provides an overview of the approaches and chemistries available for polymer network synthesis, and serve as a resource for researchers exploring polymer networks or attempting alternative approaches to network development.

Introduction

Polymer networks are used in many applications, ranging from high performance thermosets, elastomers, adhesives, and hydrogels which can have biological uses. Crosslinks are the key feature of polymer networks, which distinguishes them from other types of polymeric structures.^{1,2} These crosslinks bind the polymer chains together creating a percolated, or space occupying mesh.³ This generates a polymer where in principle the macroscopic scale polymer is a single molecule, with an incredibly high molecular weight that approaches infinity. In addition to generating a very high molecular weight polymer, the crosslinks between polymer chains alter the materials properties. Unlike conventional isolatable macromolecules, polymer networks are no longer soluble, but rather only capable of swelling in a good solvent.⁴ Networks also resist flow and maintain structural stability, even above any melting or glass transition temperatures. This makes polymer networks appealing for high performance applications, but the presence of crosslinks can make their synthesis substantially more challenging, and additionally, many of the characterization tools favored by chemists are no longer applicable.⁵



Scheme 1: Synthesis of Bakelite by condensation of phenol and formaldehyde.⁶

The first synthesis of polymer networks coincides with the generally accepted first synthesis of Bakelite in 1909. Bakelite is synthesized by the condensation of phenol with formaldehyde, as shown in **Scheme 1**. Subsequently, various approaches have been developed for the synthesis of crosslinked macromolecules. The common building blocks used to synthesize polymer network are multifunctional monomers. These multifunctional monomers act as branching points, which eventually connect multiple polymer chains to form crosslinked networks. Networks can be synthesized by both chain and step polymerizations. In chain polymerization, also called addition or chain growth polymerization, there is an active end group, such as a radical, anion, cation or metal, that adds monomer and transforms the previously active monomer to an inert unit and converts the monomer to the same type of active end group. In step polymerizations, also called step growth polymerization, the monomers react with each other without requiring a specific active end group, and the generated oligomers typically react with one another to create even higher molecular weight polymers. Note that IUPAC terminology separates step polymerization into polycondensation or polyaddition, depending on whether there is a small molecule released upon polymer coupling.^{7,8}


Although both chain and step polymerization processes have been used to synthesize linear polymers, the addition of multifunctional monomers, transitions from the synthesis of linear chains towards branched and eventually crosslinked polymers. In this series of 2 articles, an overview of the synthesis and characterization of polymer networks is presented. The synthetic approaches to polymer networks through various methods and estimates of the transition from soluble (sol) to gelled (gel) state are given by various syntheses. Common chemistries used in network synthesis are highlighted. In the second contribution to this series, the methods used to characterize networks are presented.⁵ These two articles on polymer networks together are designed as a framework for researchers to design their own polymer networks and an overview on the methods available to evaluate their properties. These two articles can serve as a first entry points into polymer networks and complement many excellent reviews in the field,^{1,3,9} which can serve as sources for detailed characterization or synthesis beyond the focus of these shorter contributions.

Overview of Synthesis of Polymer Networks

The synthesis of polymer networks has facilitated the design and instigation of multifunctionality in polymeric materials, making them highly appealing for a wide range of demanding emerging applications including coatings, self-healing materials, shape memory systems, optical indicators and sensors.¹⁰

A crosslinked polymer network possesses a minimum of two pathways connecting most points within the polymers. The extensive crosslinking fosters the development of three-dimensional mesh-like structures, thereby introducing multifunctionality into polymer chains (**Scheme 2a**).

This transition in topology entails a shift from linear chains to branched polymers and ultimately leads to the formation of networks with more intricate architectures such as single double and triple networks.¹¹ Further, network structures can be varied in perfection, resulting in perfect, almost perfect to imperfect networks (*Scheme 2b*).²



Scheme 2: a) Schematic, drawing of polymer structures, linear, branched and crosslinked. b) Types of networks

The synthesis of polymer networks involves either polymerization with a multifunctional monomer or a pre-synthesized polymer featuring crosslinkable units in the backbone or at the chain ends. Crosslinks between these monomers or pre-polymers can be established through various bond types, including static covalent bonds, dynamic covalent bonds (disulfide linkages, Diels-Alder, transamination, transesterification, olefin metathesis), as well as physical interactions (hydrophobic interactions, van der Waals interaction, metal ligand coordination and coulombic interactions).¹² These bond types can be utilized individually or in combinations to enhance the functionality of the polymer networks.¹³ The resulting properties of the networks, range from gels and elastomers to thermosets and thermoplastic elastomers, depending on the monomers and chemistries employed.³


Crosslinking can be facilitated through a diverse range of techniques such as light irradiation, thermal conditions, pH, addition of salts, electrochemistry, sonochemistry.^{1,2,14–17} However, the network properties fundamentally rely on the selection of appropriate chemistries and optimization of the crosslinking conditions, and control over the crosslink density.

This overview primarily focuses on four distinct synthetic routes for polymer network formation. The four routes discussed are: step polymerization of multifunctional monomers, chain polymerization in the presence of a multifunctional crosslinker; polymerization of functional

monomers coupled with crosslinking through step growth mechanisms, self-assembly processes exemplified by urethanes.


Step Polymerization Processes

In step polymerization, bifunctional or multifunctional monomers with mutually reactive groups react with each monomer in the absence of activating groups. Monomers first form dimers, trimers, oligomers and eventually form high molecular weight polymers.^{18,19} At the initial stages of polymerization, monomers consume rapidly with the initial low degree of polymerization due to formation of short fragments. These fragments grow continuously throughout coupling steps increasing the degree of polymerization. Step polymerization can occur through condensation with the elimination of small molecules or addition by rearrangement and without the elimination of small molecules.²⁰ Polyesters, polyamides and polyethers are some of common examples for polymers made by condensation, while polyurethanes and epoxy resins are some important polymers made by addition. Step polymerization is capable of forming both linear polymers and polymer networks based on the functionality of the monomer/monomers. Linear step polymerization is extensively applied to synthesize commercially important polymers such as poly(ethylene terephthalate) and nylon.^{21,22} In linear step polymerization, as depicted in *Scheme 3*, difunctional monomers (such as AB or A₂+B₂) undergo stepwise reactions, resulting in the formation of difunctional dimers, trimers, tetramers, or oligomers with reactive end groups at both ends. These entities then proceed to grow into linear polymer chains.¹⁸



Scheme 3: Schematic of conventional step polymerization to yield linear polymers using difunctional (a) AB and (b) A₂+B₂ monomers. Formation of difunctional dimers, trimers and tetramers are shown in (a) Reactive functional groups are represented as A and B.

Crosslinked network polymers can be synthesized using multifunctional monomers including A₃+B₂, A₃+B₃ or A₄+B₂ in step polymerization and as schematically drawn in *Scheme 4*.²¹ Polymer chains grow similar to that in linear polymer formation. However, resulting oligomers can have the same number or even more numbers of reactive end groups than the original monomer, thus potentially accelerating the growth of that macromolecule compared to linear step polymerization. Each time a multifunctional monomer incorporates into the backbone and reacts with monomers a branch point is form. These branch points act as crosslinks and ultimately result a crosslinked polymer network as shown in *Scheme 4*.



Scheme 4: Schematic of conventional step polymerization to yield polymer networks using multifunctional (a) A_3+B_2 (b) A_3+B_3 and (c) A_4+B_2 monomers.

Further, as the reaction progresses the number averaged molecular weight (x_n) increases and can be approximated under ideal conditions using Flory theory as shown below for step polymerization.^{21,23,24}

$$x_n = \frac{f \left(1 - p + \frac{1}{r} \right) + 2p}{f \left(1 - p + \frac{1}{r} - 2p_A \right) + 2p} \quad (1)$$

Where x_n is the number average molecular weight, p is the conversion of functional groups, p_A is the extent of reaction of the A functional groups, r is the ratio between initial A and B functional groups present and f is the average functionality of monomers.

$$(\alpha_A \alpha_B)_{gel} = \frac{1}{(f_A - 1)(f_B - 1)} \quad (2)$$

Where α_A and α_B are the conversion of A and B functional groups respectively and f_A and f_B are the functionality of A and B functional groups respectively.

As indicated in the equation above at a critical conversion, x_n approaches infinity and at this point gelation occurs and forms the first network. This point is known as the gel point, at this point a flowy liquid reaction mixture turns into a gel resulting an immobilized polymer network.¹⁸ The conversion at the gel point can be determined by following the equation (2). Further, the formation of loops can be expected in practical situations removing reactive end groups and in that case the conversion needed to reach gelation will be higher than that predicted by the equation above.

Many commercially used polymers such as epoxy-amine networks,^{25–27} poly(urethane) networks,²⁸ and formaldehyde networks²⁹ are synthesized using multifunctional step polymerization. Structures and synthesis of those polymer networks are illustrated in **Scheme 5**.

Usually, difunctional monomers are reacted with monomers with functionality greater than 2 and mostly either one of them are prepolymers with two/multiple functional groups. Epoxy-amine networks are synthesized by first reacting epichlorohydrin and bisphenol A to prepare prepolymers with epoxide end groups followed by reacting the prepolymer with multifunctional amine monomers through addition reaction between epoxide and amine.^{25,26} Diisocyanates and multifunctional alcohols (polyols prepolymers) are utilized to prepare poly(urethane) networks which are important as elastomers and for their application in synthetic forms.²⁷ Similar to epoxy-amine and poly(urethane) network synthesis, usually difunctional formaldehydes react with phenol, urea, or melamine with functionality higher than 2 to result phenol-formaldehyde networks, urea-formaldehyde networks, or melamine-formaldehyde networks respectively. Bakelite is a well-known thermosetting polymer which made from phenol and formaldehyde condensation.²⁹ In addition to these traditional polymer networks made by step polymerization, various approaches such as thiol-ene or thiol-yne polymerization are developed recently to prepare network polymers by reacting multifunctional thiol monomers with ene or yne monomers as shown in **Scheme 5**.³⁰ Further, it is noted that these new approaches are capable of forming a highly crosslink polymer network with a delayed gel point and a homogeneous network through a radical mediated step growth mechanism.³¹⁻³³


Free radical polymerization (FRP) proceeds via consecutive addition of monomers (almost exclusively vinyl monomers) to an active free-radical center.³⁴ The reaction can be initiated by thermal, chemical, or photoactive initiator molecules. FRP begins at the initiation stage which involves two steps. Initially, the initiator undergoes homolytic splitting into two free radicals and in the second step, one of the free radicals adds on to a monomer. Propagation is the next stage of FRP, and it involves a sequentially rapid addition of monomers to the active free-radical center of a polymer leading to growth of the polymer chain. In the termination stage, growth of a polymer chain is terminated by destruction of the active center either through a process called bimolecular reaction or disproportionation (*Scheme 6b*).

Cationic polymerization of vinyl monomers occurs by the creation of cationic active centers from the reaction of monomers with electrophiles at the initiation stage.³⁵ Propagation proceeds predominantly via successive head-to-tail addition of vinyl monomers to a carbocation active center and forming a new carbocation in the process. This process continues until available monomers are consumed or until growing polymer chains terminates, which is the final stage. Unlike FRP where active centers bear no electronic charge, in cationic polymerization, termination can occur by either unimolecular rearrangement of ion pair or by chain transfer.

In anionic polymerization, initiation involves a nucleophilic attack on a monomer by an electron rich or anionic (negatively charged group) initiator resulting in the formation of a reactive carbanion. Hence initiation can be achieved by addition of either a negative (Nu^-) or neutral ($\text{Nu}:$) nucleophile to a monomer and a good example for this process is the addition of amide to styrene. Termination can be achieved by proton abstraction. In the case of a growing styrene chain, termination occurs by chain transfer to solvent, wherein proton is abstracted from ammonia leading to termination of chain growth.³⁶

Olefin metathesis is catalyzed in the presence of a transition metal complex and *Scheme 6c* gives a generally representation of the reaction.³⁷ Ring-opening metathesis polymerization (ROMP) however employs the use of metal carbenes in the presence of homogenous catalysts to prepare uniform and stereoregular linear polymers and copolymer chains from cyclic unsaturated alkenes such as cyclobutene, cyclopentene, norbornene, etc.

Ring-opening polymerization (ROP) is another form of chain polymerization that can be used to prepare polymers that are not easily accessible by other methods.³⁸ For this process, terminal end group of the polymer chain acts as the active center responsible for the addition of cyclic monomers by ring-opening reactions. Relief of steric repulsion and bond-angle strain are the main driving force for ring-opening in cyclic monomers. ROP typically requires an initiator and proceeds various mechanisms including anionic, cationic, free-radical, and metathesis polymerizations.



It is important to note that not all chain growth mechanisms are equal since they produce polymers with varying backbone uniformity. FRP gives networks with relatively low uniformity, due to fast reaction rates, leading to pockets of high crosslink density and pockets of long chains connecting the densely crosslinked clusters. Reversible-deactivation radical polymerization (RDRP) can be used to achieve better control of chain growth leading to uniformity in chain length of polymer backbone.³⁹ In RDRP, the active site of the polymer chain is not lost after deactivation, instead, it can resume propagation leading to increased chain length when reacting with monomers. Typically, this process involves a simultaneous initiation of chain growth leading to a narrow molar mass distribution of polymer chains in contrast to the broader distributions observed in FRP. Examples of RDRP techniques include reversible-addition-fragmentation chain-transfer radical

polymerization (RAFT) and atom-transfer radical polymerization (ATRP). *Scheme 8a* gives the distinction in polymer synthesis using the aforementioned RDRP methods in comparison to FRP. Up until now, several groups have published detailed reviews presenting in-depth discussion of RDRP methods, along with multiples examples from the literature.^{40,4142}

Gelation or gel transition in non-linear polymers is a key factor to consider under chain polymerization. This usually occurs in branched or network polymer wherein continued linking leads to an immobilized single macroscopic molecule at a point now referred to as gel point.⁴³ At this point, the gel loses fluidity and becomes highly viscous, resulting in a gel network that swells in contrast to dissolving in solvent.⁴⁴ Gelation can be predicted by several approaches which include the Carothers theory of gelation and the Flory–Stockmayer (FS) theory of gelation now adapted as the statistical approach.⁴⁵ In free radical polymerization involving a mixture mono vinyl monomers (MVM) and divinyl monomers (DVMs), the critical vinyl group conversion at the gel point ($\mathcal{X}_c$) can be estimated using the equation (3).⁴⁶

$$\mathcal{X}_c = \frac{1}{r\rho_0\bar{X}_2} \quad (3)$$


In this equation, ρ_0 represents the initial molar fraction of the vinyl groups contributed by the DVMs, $\bar{X}_2$ denotes the average chain length of the primary molecule and r signifies the unequal reactivity of the vinyl groups between MVM and DVM.

Through application of the FS theory, the theoretical gel point of the RDRP systems can be calculated by using the equation (4).^{47,48}

$$P_c = \sqrt{\frac{[PC]_t}{2[X]_0\mathfrak{D}}} \quad (4)$$

Where, P_c represents the conversion of the vinyl bonds at gel point, $[PC]_t$ denotes the instantaneous concentration of the primary chains at the gel point, $[X]_0$ and $\mathfrak{D}$ represent the initial concentration of the crosslinker and the dispersity of the primary chains in the absence of the crosslinks respectively.


Examples of chain growth polymerization mostly focus on divinyl polymerization, often by radical polymerization due to simplicity of use. Industrially used examples of chain polymerization leading to crosslinked networks includes hydrogels such as contact lenses, polyacrylamide gels, ion exchange resins, dental resins (*Scheme 8b*), and GPC column packing materials.^{3,49}



Scheme 8: Schematic diagram of a) synthesis of poly(styrene) via FRP, RAFT and ATRP. b) Crosslinking of DVMs for dental resins⁵⁰


Post polymerization crosslinking

Crosslinking of polymers is an essential process in the field of polymer science that transforms branched or linear polymer chains into polymeric network structures.⁵¹ Post-polymerization crosslinking is a highly effective processes of forming polymeric network structures after the primary chain is synthesized.⁵² Crosslinking after polymerization can be successfully accomplished on polymers containing pendant reactive groups (Scheme 9).




Scheme 9: Schematic of polymers containing pendant reactive groups.

These polymers are generally designed to include reactive pendant groups along the polymer chain's backbone.⁵³ Epoxy groups are an example that can be used as pendant group in polymer chain due to their shelf stability and ability to efficiently react with suitable nucleophiles like amines and alcohols.⁵⁴ The crosslinking degree can be modulated to attain desired qualities via controlling crosslinking agent's stoichiometry and conditions of reaction.⁵³ Additionally, post-polymerization can be achieved through polymer with reactive terminal groups as in telechelic polymer.⁵⁵



Scheme 10: Schematic diagrams of polymers containing terminal reactive groups a) with another polymer with terminal reactive groups, b) with the addition of a multifunctional crosslinker.

Similar to polymers with pendant reactive groups, these terminal groups enable highly regulated crosslinking and post-polymerization crosslinking can be attained through a variety of methods. This could be accomplished through reacting the terminal group with a crosslinking agent to form a crosslinked network (*Scheme 10b*) or interaction between terminal groups on different polymer chains (*Scheme 10a*).⁵⁵ The advantage of the telechelic polymer approach is that the molecular weight between crosslinks can be regulated by the primary polymer length. Selecting suitable functional groups that comprise the pendant or reactive group is an important feature of these approaches. They should not only be stable during and after the initial polymerization, but they should also have high reactivity for post-polymerization crosslinking.^{51–53} Generally, isocyanates,⁵⁶ amines,⁵⁷ and epoxides⁵⁴ are some of the suitable functional groups that have been extensively explored for post-polymerization crosslinking resulting in polymer networks with unique properties for targeted applications.




Scheme 11: Schematic diagram of vulcanization of rubber using sulfur

An industrially relevant example of post polymerization crosslinking is the vulcanization of rubber which involves crosslinking of polyisoprene (rubber) with sulfur to obtain a material with improved durability (Scheme 11).⁵⁸

Networks by phase separation

Polymer network like properties can be achieved in the absence of covalent crosslinks by leveraging phase separation and microaggregation of polymer chains through non-covalent interactions. A material consisting of immiscible or poorly miscible polymer components, leads to the formation of distinct regions or microaggregates. These microaggregates effectively connect the polymer chains through weak physical interactions such as Van der Waals forces, ionic interactions, hydrogen bonding, and aromatic stacking. As a result, the material exhibits network-like behavior, including enhanced mechanical properties. Notable examples include polyurethanes, which intrinsically form hard and soft domains from their backbone units and multiblock thermoplastic elastomers based on hard-soft-hard triblock copolymers.

Polyurethane structure, illustrated in Scheme 12a, consists of a hard segment and a soft segment. Phase separation in polyurethanes primarily relies on hydrogen bonding. The degree of phase separation is influenced by the lengths of the hard and soft segments as well as the hydrogen bonding interactions and temperature. Significantly, the strength the material stem from the hydrogen bonding between the N-H and C=O groups within the hard domain.^{59,60} By modulating these factors, physical and mechanical properties of these polyurethane can be tailored, allowing for wide range of applications such as coatings, adhesives, textile and medical applications.⁶¹



Scheme 12 :a) polyurethane networks and b) self-assembly of ABA triblock copolymers into different domains (spherical, cylindrical, gyroid, and lamella) through physical crosslinks.

Another notable example of materials exhibiting network like behavior is multiblock thermoplastic elastomers, especially ABA triblock copolymers. These elastomers consist of a soft midblock and two hard, glassy blocks at the ends (ABA structure). The monomer chosen for the hard blocks typically has glass transition temperature above room temperature, while the soft polymer's has a glass transition temperature far below room temperature. As a result of the incompatibility between these polymer units, microphase separation occurs, leading to the formation of two distinct domains: one rich in the hard block and the other rich in the soft block as shown in **Scheme 12b**. Prominent examples of such triblock elastomers include polystyrene-poly(butadiene)-polystyrene (SBS)⁶² and polystyrene-poly(isoprene)-polystyrene (SIS).^{63,64} In these copolymers, the π - π stacking of the styrene blocks creates a physically crosslinked material, while the elastomeric behavior is provided by the soft midblock. Recent advancements have introduced new ABA thermoplastic elastomers with enhanced properties, such as self-healing⁶⁵ and degradability.⁶⁶ Adjusting the length and composition of the blocks allows the mechanical properties to be modulated for specific applications.⁶⁷

Conclusions

There are many approaches to the synthesis of polymer networks, although they generally adapt from the traditional step and chain polymerization approaches. Multifunctionality is key to

network formation, since the polymerized multifunctional monomers serve as crosslinks in the network. Once the polymers cross the gel-point the material has effectively infinite molecular weight, with there being a pathways of covalent bonds connecting any two parts of the polymer gel. Phase separation can enhance materials properties and in certain cases also lead to network like properties from linear chains. Due to the insolubility caused by the effectively infinite molecular weight of polymer networks, their characterization is more complex than soluble polymers and will be highlighted in a subsequent contribution.

Author Contributions

D.K. and N.D.A.W were involved in conceptualization and project administration. S.V.W., M.A.S.N.W., O.J.D., I.O.R., C.W.H.R, N.D.A.W and D.K. were involved in visualization. M.A.S.N.W., O.J.D., I.O.R., C.W.H.R, N.D.A.W and D.K. were involved in writing the original draft. All authors were involved in editing.

Acknowledgements

We thank Dr. John Matson for discussion of chain vs step mechanisms. M.A.S.N.W. and D.K. were supported by the National Science Foundation (CHE-2203727) for description of step polymerization processes and overview of network materials. I.O.R. was supported by the National Science Foundation (DMR-1749730) for descriptions of Post Polymerization Crosslinking. This work was partially supported by United States Department of Energy, Office of Science, Basic Energy Sciences, under Award No. DE-SC0018645 (Supporting C.W.H.R) for descriptions of phase separation in networks. N.D.A.W was supported by the European Union's Horizon 2020 research and innovation programme under the Marie Skłodowska-Curie grant agreement No. 101030516 for descriptions of overall approaches to network synthesis.

References

- (1) Gu, Y.; Zhao, J.; Johnson, J. A. Polymer Networks: From Plastics and Gels to Porous Frameworks. *Angew. Chemie Int. Ed.* **2020**, *59* (13), 5022–5049.
- (2) Patrickios, C. S. Polymer Networks: Recent Developments. In *Macromolecular symposia*; Wiley Online Library, 2010; Vol. 291, pp 1–11.
- (3) Varnava, C. K.; Patrickios, C. S. Polymer Networks One Hundred Years after the Macromolecular Hypothesis: A Tutorial Review. *Polymer (Guildf)*. **2021**, *215*, 123322.
- (4) Kaiser, T. Highly Crosslinked Polymers. *Prog. Polym. Sci.* **1989**, *14* (3), 373–450.
- (5) Danielsen, S. P. O.; Beech, H. K.; Wang, S.; El-Zaatari, B. M.; Wang, X.; Sapir, L.; Ouchi, T.; Wang, Z.; Johnson, P. N.; Hu, Y. Molecular Characterization of Polymer Networks. *Chem. Rev.* **2021**, *121* (8), 5042–5092.
- (6) Baekeland, L. H. Method of Making Insoluble Products of Phenol and Formaldehyde. Google Patents December 7, 1909.
- (7) Luscombe, C. K.; Moad, G.; Hiorns, R. C.; Jones, R. G.; Keddie, D. J.; Matson, J. B.; Merna, J.; Nakano, T.; Russell, G. T.; Topham, P. D. A Brief Guide to Polymerization Terminology (IUPAC Technical Report). *Pure Appl. Chem.* **2022**, *94* (9), 1079–1084.
- (8) Chan, C. H.; Chen, J.-T.; Farrell, W. S.; Fellows, C. M.; Keddie, D. J.; Luscombe, C. K.; Matson, J. B.; Merna, J.; Moad, G.; Russell, G. T. Reconsidering Terms for Mechanisms of Polymer Growth: The “Step-Growth” and “Chain-Growth” Dilemma. *Polym. Chem.* **2022**, *13* (16), 2262–2270.

- (9) Zhang, V.; Kang, B.; Accardo, J. V.; Kalow, J. A. Structure–Reactivity–Property Relationships in Covalent Adaptable Networks. *J. Am. Chem. Soc.* **2022**, *144* (49), 22358–22377.
- (10) Stepto, R. F. T.; Cail, J. I.; Taylor, D. J. R. Polymer Networks: Principles of Formation, Structure and Properties. *Polimery* **2000**, *45* (7–8), 455–464.
- (11) Panteli, P. A.; Patrickios, C. S. Multiply Interpenetrating Polymer Networks: Preparation, Mechanical Properties, and Applications. *Gels* **2019**, *5* (3), 36.
- (12) Hernández-Ortiz, J. C.; Vivaldo-Lima, E. Crosslinking. *Handb. Polym. Synth. Charact. Process.* **2013**, 187–204.
- (13) Zhang, B.; De Alwis Watuthantrige, N.; Wanasinghe, S. V.; Averick, S.; Konkolewicz, D. Complementary Dynamic Chemistries for Multifunctional Polymeric Materials. *Adv. Funct. Mater.* **2022**, *32* (8), 2108431.
- (14) Bagheri, A.; Fellows, C. M.; Boyer, C. Reversible Deactivation Radical Polymerization: From Polymer Network Synthesis to 3D Printing. *Adv. Sci.* **2021**, *8* (5), 2003701.
- (15) Blasco, E.; Wegener, M.; Barner-Kowollik, C. Photochemically Driven Polymeric Network Formation: Synthesis and Applications. *Adv. Mater.* **2017**, *29* (15), 1604005.
- (16) Palma-Cando, A.; Scherf, U. Electrochemically Generated Thin Films of Microporous Polymer Networks: Synthesis, Properties, and Applications. *Macromol. Chem. Phys.* **2016**, *217* (7), 827–841.
- (17) Kumar, A. R. S. S.; Padmakumar, A.; Kalita, U.; Samanta, S.; Baral, A.; Singha, N. K.; Ashokkumar, M.; Qiao, G. Ultrasonics in Polymer Science; Applications and Challenges. *Prog. Mater. Sci.* **2023**, 101113.
- (18) Schamboeck, V.; Iedema, P. D.; Kryven, I. Dynamic Networks That Drive the Process of Irreversible Step-Growth Polymerization. *Sci. Rep.* **2019**, *9* (1), 2276.
- (19) Choi, K. Y.; McAuley, K. B. Step-Growth Polymerization. *Polym. React. Eng.* **2007**, 273–314.
- (20) Ueda, M. Sequence Control in One-Step Condensation Polymerization. *Prog. Polym. Sci.* **1999**, *24* (5), 699–730.
- (21) De Keer, L.; Van Steenberge, P. H. M.; Reyniers, M.-F.; D’hooge, D. R. Going beyond the Carothers, Flory and Stockmayer Equation by Including Cyclization Reactions and Mobility Constraints. *Polymers (Basel)*. **2021**, *13* (15), 2410.
- (22) Shakiba, M.; Rezvani Ghomi, E.; Khosravi, F.; Jouybar, S.; Bigham, A.; Zare, M.; Abdouss, M.; Moaref, R.; Ramakrishna, S. Nylon—A Material Introduction and Overview for Biomedical Applications. *Polym. Adv. Technol.* **2021**, *32* (9), 3368–3383.
- (23) Flory, P. J. Molecular Size Distribution in Three Dimensional Polymers. I. Gelation1. *J. Am. Chem. Soc.* **1941**, *63* (11), 3083–3090.
- (24) Wen, C.; Odle, R.; Cheng, S. Molecular Weight Distribution of Branched Polymers: Comparison between Monte Carlo Simulation and Flory-Stockmayer Theory. *Polymers (Basel)*. **2023**, *15* (7), 1791.
- (25) Jin, F.-L.; Li, X.; Park, S.-J. Synthesis and Application of Epoxy Resins: A Review. *J. Ind. Eng. Chem.* **2015**, *29*, 1–11.
- (26) Pham, H. Q.; Marks, M. J. Epoxy Resins. *Ullmann’s Encycl. Ind. Chem.* **2000**.
- (27) Ferrer, M. C. C.; Babb, D.; Ryan, A. J. Characterisation of Polyurethane Networks Based on Vegetable Derived Polyol. *Polymer (Guildf)*. **2008**, *49* (15), 3279–3287.
- (28) Mahapatra, S. S.; Yadav, S. K.; Yoo, H. J.; Cho, J. W.; Park, J.-S. Highly Branched Polyurethane: Synthesis, Characterization and Effects of Branching on Dispersion of

- Carbon Nanotubes. *Compos. Part B Eng.* **2013**, *45* (1), 165–171.
- (29) Baekeland, L. H. The Synthesis, Constitution, and Uses of Bakelite. *Ind. Eng. Chem.* **1909**, *1* (3), 149–161.
- (30) Kazybayeva, D. S.; Irmukhametova, G. S.; Khutoryanskiy, V. V. Thiol-Ene “Click Reactions” as a Promising Approach to Polymer Materials. *Polym. Sci. Ser. B* **2022**, *64* (1), 1–16.
- (31) Chan, J. W.; Shin, J.; Hoyle, C. E.; Bowman, C. N.; Lowe, A. B. Synthesis, Thiol–Yne “Click” Photopolymerization, and Physical Properties of Networks Derived from Novel Multifunctional Alkynes. *Macromolecules* **2010**, *43* (11), 4937–4942.
- (32) Cramer, N. B.; Scott, J. P.; Bowman, C. N. Photopolymerizations of Thiol–Ene Polymers without Photoinitiators. *Macromolecules* **2002**, *35* (14), 5361–5365.
- (33) Cramer, N. B.; Reddy, S. K.; O’Brien, A. K.; Bowman, C. N. Thiol–Ene Photopolymerization Mechanism and Rate Limiting Step Changes for Various Vinyl Functional Group Chemistries. *Macromolecules* **2003**, *36* (21), 7964–7969.
- (34) Scranton, A. B.; Klier, J.; Peppas, N. A. Statistical Analysis of Free-Radical Copolymerization/Crosslinking Reactions Using Probability Generating Functions: Reaction Directionality and General Termination. *Macromolecules* **1991**, *24* (6), 1412–1415.
- (35) Plesch, P. H. *The Chemistry of Cationic Polymerization*; Elsevier, 2016.
- (36) Morton, M. *Anionic Polymerization: Principles and Practice*; Elsevier, 2012.
- (37) Fürstner, A. Olefin Metathesis and Beyond. *Angew. Chemie Int. Ed.* **2000**, *39* (17), 3012–3043.
- (38) Goethals, E. J.; Van Meirvenne, D.; Trossaert, G.; Deveux, R. Polymer Networks via Cationic Ring-opening Polymerization. In *Makromolekulare Chemie. Macromolecular Symposia*; Wiley Online Library, 1990; Vol. 32, pp 11–20.
- (39) Bainbridge, C. W. A.; Wangsadijaya, A.; Broderick, N.; Jin, J. Living Polymer Networks Prepared by Controlled Radical Polymerization Techniques. *Polym. Chem.* **2022**, *13* (11), 1484–1494.
- (40) Moad, C. L.; Moad, G. Fundamentals of Reversible Addition–Fragmentation Chain Transfer (RAFT). *Chem. Teach. Int.* **2020**, *3* (2), 3–17.
- (41) Matyjaszewski, K. Atom Transfer Radical Polymerization: From Mechanisms to Applications. *Isr. J. Chem.* **2012**, *52* (3–4), 206–220.
- (42) Truong, N. P.; Jones, G. R.; Bradford, K. G. E.; Konkolewicz, D.; Anastasaki, A. A Comparison of RAFT and ATRP Methods for Controlled Radical Polymerization. *Nat. Rev. Chem.* **2021**, *5* (12), 859–869.
- (43) Mann, J. L.; Rossi, R. L.; Smith, A. A. A.; Appel, E. A. Universal Scaling Behavior during Network Formation in Controlled Radical Polymerizations. *Macromolecules* **2019**, *52* (24), 9456–9465.
- (44) Lin, F.-Y.; Yan, M.; Cochran, E. W. Gelation Suppression in RAFT Polymerization. *Macromolecules* **2019**, *52* (18), 7005–7015.
- (45) Young, R. J.; Lovell, P. A. *Introduction to Polymers*; CRC press, 2011.
- (46) Okay, O. Kinetics of Gelation in Free Radical Crosslinking Copolymerization. *Polymer (Guildf)*. **1994**, *35* (12), 2613–2618.
- (47) Gao, H.; Matyjaszewski, K. Synthesis of Functional Polymers with Controlled Architecture by CRP of Monomers in the Presence of Cross-Linkers: From Stars to Gels. *Prog. Polym. Sci.* **2009**, *34* (4), 317–350.

- (48) Matyjaszewski, K. *Controlled/Living Radical Polymerization: Progress in ATRP, NMP, and RAFT*; ACS Publications, 2000.
- (49) Wiley, R. H. Crosslinked Styrene/Divinylbenzene Network Systems. *Pure Appl. Chem.* **1975**, *43* (1–2), 57–75.
- (50) Lopes-Rocha, L.; Ribeiro-Gonçalves, L.; Henriques, B.; Özcan, M.; Tiritan, M. E.; Souza, J. C. M. An Integrative Review on the Toxicity of Bisphenol A (BPA) Released from Resin Composites Used in Dentistry. *J. Biomed. Mater. Res. Part B Appl. Biomater.* **2021**, *109* (11), 1942–1952.
- (51) Kuhn, W.; Balmer, G. Crosslinking of Single Linear Macromolecules. *J. Polym. Sci.* **1962**, *57* (165), 311–319.
- (52) Odian, G. *Principles of Polymerization*; John Wiley & Sons, 2004.
- (53) Kricheldorf, H. R. *Handbook of Polymer Synthesis*; CRC press, 1991; Vol. 24.
- (54) Bagheri, R.; Marouf, B. T.; Pearson, R. A. Rubber-Toughened Epoxies: A Critical Review. *J. Macromol. Sci. Part C Polym. Rev.* **2009**, *49* (3), 201–225.
- (55) Tasdelen, M. A.; Kahveci, M. U.; Yagci, Y. Telechelic Polymers by Living and Controlled/Living Polymerization Methods. *Prog. Polym. Sci.* **2011**, *36* (4), 455–567.
- (56) Biedermann, F.; Appel, E. A.; Del Barrio, J.; Gruending, T.; Barner-Kowollik, C.; Scherman, O. A. Postpolymerization Modification of Hydroxyl-Functionalized Polymers with Isocyanates. *Macromolecules* **2011**, *44* (12), 4828–4835.
- (57) Elhalwagy, M. E.; Elsherbiny, A. S.; Gemeay, A. H. Amine-Rich Polymers for Water Purification Applications. *Mater. Today Chem.* **2023**, *27*, 101344.
- (58) Craig, D. The Vulcanization of Rubber with Sulfur. *Rubber Chem. Technol.* **1957**, *30* (5), 1291–1346.
- (59) de Souza, F. M.; Kahol, P. K.; Gupta, R. K. Introduction to Polyurethane Chemistry. In *Polyurethane Chemistry: Renewable Polyols and Isocyanates*; ACS Publications, 2021; pp 1–24.
- (60) Lee, H. S.; Wang, Y. K.; Hsu, S. L. Spectroscopic Analysis of Phase Separation Behavior of Model Polyurethanes. *Macromolecules* **1987**, *20* (9), 2089–2095.
- (61) Zhang, Q.; Zhang, G.; Xu, J.; Gao, C.; Wu, Y. RECENT ADVANCES ON LIGIN-DERIVED POLYURETHANE POLYMERS. *Rev. Adv. Mater. Sci.* **2015**, *40* (2).
- (62) Ban, H. T.; Kase, T.; Kawabe, M.; Miyazawa, A.; Ishihara, T.; Hagihara, H.; Tsunogae, Y.; Murata, M.; Shiono, T. A New Approach to Styrenic Thermoplastic Elastomers: Synthesis and Characterization of Crystalline Styrene– Butadiene– Styrene Triblock Copolymers. *Macromolecules* **2006**, *39* (1), 171–176.
- (63) Dair, B. J.; Honeker, C. C.; Alward, D. B.; Avgeropoulos, A.; Hadjichristidis, N.; Fetters, L. J.; Capel, M.; Thomas, E. L. Mechanical Properties and Deformation Behavior of the Double Gyroid Phase in Unoriented Thermoplastic Elastomers. *Macromolecules* **1999**, *32* (24), 8145–8152.
- (64) Matsumiya, Y.; Watanabe, H.; Takano, A.; Takahashi, Y. Uniaxial Extensional Behavior of (SIS) p-Type Multiblock Copolymer Systems: Structural Origin of High Extensibility. *Macromolecules* **2013**, *46* (7), 2681–2695.
- (65) Yang, J.-X.; Long, Y.-Y.; Pan, L.; Men, Y.-F.; Li, Y.-S. Spontaneously Healable Thermoplastic Elastomers Achieved through One-Pot Living Ring-Opening Metathesis Copolymerization of Well-Designed Bulky Monomers. *ACS Appl. Mater. Interfaces* **2016**, *8* (19), 12445–12455.
- (66) De Alwis Watuthanthrige, N.; Reeves, J. A.; Dolan, M. T.; Valloppilly, S.; Zanjani, M. B.;

- Ye, Z.; Konkolewicz, D. Wavelength-Controlled Synthesis and Degradation of Thermoplastic Elastomers Based on Intrinsically Photoresponsive Phenyl Vinyl Ketone. *Macromolecules* **2020**, *53* (13), 5199–5207.
- (67) Maji, P.; Naskar, K. Styrenic Block Copolymer-based Thermoplastic Elastomers in Smart Applications: Advances in Synthesis, Microstructure, and Structure–Property Relationships—A Review. *J. Appl. Polym. Sci.* **2022**, *139* (39), e52942.